University of Groningen

Investigation of inelastic light scattering in heavily electron-irradiated alkali halides

Shtyrkov, EI; Klimovikii, A; Den Hartog, HW; Vainshtein, DI

Published in:
Radiation Effects and Defects in Solids

DOI:
[10.1080/1042015021000052412](https://doi.org/10.1080/1042015021000052412)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2003

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Shtyrkov, EI., Klimovikii, A., Den Hartog, HW., & Vainshtein, DI. (2003). Investigation of inelastic light scattering in heavily electron-irradiated alkali halides. *Radiation Effects and Defects in Solids*, 158(1-6), 125-129. <https://doi.org/10.1080/1042015021000052412>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

INVESTIGATION OF INELASTIC LIGHT SCATTERING IN HEAVILY ELECTRON-IRRADIATED ALKALI HALIDES

E. I. SHTYRKOV^a, A. KLIMOVITKII^b, H. W. DEN HARTOG^{c,*} and
D. I. VAINSHTEIN^c

^aKazan Physical-Technical Institute, AS of Russia, 420029 Kazan, Russia; ^bKazan State University, 420000 Kazan, Russia; ^cSolid State Physics Laboratory, University of Groningen, 4 Nijenborgh, NL 9747 AG Groningen, The Netherlands

The properties of several unusual Raman scattering peaks observed in heavily irradiated NaCl with vast amounts of colloidal sodium are investigated. A new peak (at 3580 cm^{-1}) has been observed far beyond the cut-off limit of the one-phonon spectrum. This scattering phenomenon has been explained with an electron quantum confinement model where the electronic excitations are quantized as expected for wire-like structures of nano-particles of metallic sodium.

Keywords: Raman scattering; Alkali halides; Quantum confinement

Raman spectroscopy of doped, additively and electrolytically colored NaCl crystals have revealed changes in the spectra of inelastic light scattering due to the presence of small sized metallic nano-particles [1,2]. Strong changes in the low-frequency Raman Scattering (RS) spectra and the appearance of two additional peaks higher than the maximum frequency of the one-phonon spectrum of the NaCl matrix were also discovered in heavily irradiated, doped rock salt [3]. We have concluded from our differential scanning calorimetry (DSC) experiments that these peaks (at 330 and 550 cm^{-1}) are associated with ultrafine details of the small Na-particles available in our samples [4]. With the aim to learn more about the origin of inelastic light scattering in these materials, in this work, we have studied the Raman spectra of heavily damaged NaCl:KBF₄ and NaCl:K crystals as a function of the wavelength of the excitation light and the measuring temperature. We have measured the polarized and depolarized spectra with X(ZZ)Y and X(ZX)Y for 90°-geometries for samples that had been irradiated under different conditions. The polarized VV and VH Raman spectra were taken for all the samples at temperatures in the range 30–250 K. The Rayleigh elastic scattering results in a strong broadening mask the Stokes intensity for all frequencies below 100 cm^{-1} . To eliminate these temperature effects on the phonon spectrum close to frequency zero, we reduced the spectra by dividing the RS intensity by the factor $R_{s1}^{(1)} = (\bar{n} + 1)$, where the Bose coefficient $\bar{n}(\nu, T) = (e^{h\nu/kT} - 1)^{-1}$ and ν is the phonon vibration frequency.

* Corresponding author. Tel.: 31-50-363 4789; Fax: 31-50-363 4879; E-mail: h.w.den.hartog@phys.rug.nl

The main feature of the reduced inelastic scattering spectra is the strong dependence of the VV polarized scattering spectrum on the temperature in the low-frequency region (below 100 cm^{-1}) and the weak temperature dependence for higher frequencies for both polarization directions (see, for example Figure 1). The different temperature behavior for the VV and VH polarization directions close to zero-frequency shows that the probe laser light interacts with both the electronic and vibrational systems of the Na-colloids giving rise to electronic and vibrational Raman scattering bands below 100 cm^{-1} . As in semiconductors [5] the increasing scattering cross-section with decreasing temperature for small frequency shifts can be explained by single particle plasma-like excitations of the conduction electron gas in solids.

Due to the extensive disorder in our heavily irradiated NaCl samples, as in amorphous media and highly defective crystals, with small correlation lengths the selection rules for the phonon wave-vector break down partly and as a consequence we observe the forbidden first-order Raman scattering due to the NaCl phonon modes below 300 cm^{-1} . In our extensively disordered samples the density of the vibrational states is obtained [6] by dividing the RS intensity by $f = R_s^{(1)}/\nu$. In Figure 2 we show the averaged, reduced spectra for three samples with different amounts of Na. The averages have been taken over the results obtained for all measuring temperatures.

FIGURE 1 Reduced (a) VV and (b) VH spectra for NaCl:KBF₄ (12.4%Na) at measuring temperatures: 1–30 K, 2–40 K, 3–50 K, 4–60 K, 5–100 K, 6–11–(120 K, 130 K, 140 K, 150 K, 160 K, 170 K), 12–13 (200 K, 250 K).

FIGURE 2 Density of vibrational states for NaCl:KBF₄ and intensity of scattering higher than 300 cm⁻¹ at different concentrations of Na nano-particles: 1 – 1.1%Na, 2 – 6.3%Na, 3 – 12.4%Na.

Comparing the plots in Figure 2a we see that the DOS decreases with increasing damage. This observation can be explained by the increasing optical density of the sample and the small penetration depth of the excitation light. Taking into account this change of the penetration depth we have fitted the spectra and observed an increase of the intensities of the 330 and 550 peaks (Figure 2b) with increasing volume fraction of Na-colloids. As an alternative to local phonon modes, we have explained elsewhere [7] the appearance of these peaks beyond the limits of the one-phonon spectrum of NaCl in terms of electron quantum confinement in nano-wires consisting of Na-colloids with a mean size of about 6 nm.

Now we have succeeded in observing a new inelastic scattering line (at 3580 cm⁻¹, Figure 3) very far beyond the one-phonon cut-off frequency. In fact, inelastic scattering of these high frequencies can hardly be assigned to some sort of local phonon excitations. The concept of quantum confinement in inelastic scattering allows us to find the upward energy shift of the peaks associated with electrons, which are confined to a narrow potential well. In the case of one-dimensional colloids (quantum wires along the *z* direction) the behavior of the confined electrons can be described by a rectangular cylindrical potential well. The spectrum of energy eigenvalues for such a quantum well looks like [7]

$$E_{n,l,p_z} = \frac{\hbar^2 j_{n,l}^2}{2m^* \rho_0^2} + \frac{\rho_z^2}{2m^*}, \quad (1)$$

where $j_{n,l}$ is n th root of the Bessel function of l th order and $n = 1, 2, 3 \dots$

The upward frequency shift in the Raman spectra associated with transitions between the lowest neighboring energy states (*i.e.*, the Fermi level and the $1s$ -state with $n = 1, l = 0$) is

$$\nu_{1s}(\text{cm}^{-1}) = 1.21 \times 10^3 \cdot \frac{j_{1,0}^2}{qd^2}, \quad (2)$$

and using the value of the root $j_{1,0} = 3.83$ we obtain

$$d(\text{nm}) = \frac{133}{\sqrt{q\nu_{1s}(\text{cm}^{-1})}}, \quad (3)$$

where q is the ratio of the effective and free electron mass and the diameter of the wire d is expressed in nanometers. For sodium $q = 1.24$ and using the shift 3580 cm^{-1} we evaluate for the size of the Na colloid $d = 2 \text{ nm}$. Because in our case the observed energy shift (0.44 eV) is much larger than maximum value of kT (at room temperature kT is about

FIGURE 3 High-frequency inelastic scattering of NaCl doped with KCl or KBF_4 , for a wide range of Na-concentrations, observed at measuring temperatures of 30 and 250 K and with excitation wavelengths of 488 and 514 nm. a: 1-NaCl:K (6.4%Na, 514 nm), 2-NaCl:KBF₄ (12.4%Na, 488 nm), 3-NaCl:KBF₄ (7.8%Na, 488 nm), all at 30 K b: NaCl:KBF₄ (7.8%Na, 488 nm), at 30 K (1 – before, 2 – after annealing at 200 °C for 2 min), at 250 K (3 – before, 4 – after annealing).

0.03 eV) there is practically no dependence of the 3580 cm^{-1} -peak intensity on the measuring temperature (Figure 3b). Slight annealing of the samples (2 min at 200°C) results in a small decrease (a few cm^{-1}) of the mean frequency of the scattering peak, which might be caused by a small increase of the average colloid sizes due to rearrangements and a transition from the fcc- to the bcc-structure. We have observed a phase transformation of Na-colloids under the above mentioned annealing conditions by means of differential scanning calorimetry (for the sample with 7.7%Na). Prior to annealing the melting temperature of metallic Na was 107°C and it was 92.5°C after annealing. Thus the 3580 cm^{-1} peak can be explained by inelastic scattering caused by very small sodium particles with mean sizes of about 2 nm. We propose that the peak is caused by quantum confined electronic excitations. This conclusion is supported by recent observations of quantum well luminescence from Na-monolayers [8].

Acknowledgements

This work was supported financially by the Netherlands Organization for Scientific Research (NWO-Nederlandse Organisatie voor Wetenschappelijk Onderzoek) project number 047-008-021 and Russian Foundation for Basic Research project number 00-15-96615.

References

- [1] Rzepka, E., Lefrant, S. and Taurel, L. (1979). *Solid State Communications*, **30**, 801.
- [2] Duval, E., Mariotto, G., Montagna, M., Pilla, O., Viliani, G. and Barland, M. (1987). *Europhys. Lett.*, **3**, 333.
- [3] Groote, J. C., Weerkamp, J. R. W., Seinen, J. and den Hartog, H. W. (1994). *Phys. Rev. B*, **50**, 9798.
- [4] Seinen, J., Groote, J. C., Weerkamp, J. R. W. and den Hartog, H. W. (1994). *Phys. Rev. B*, **50**, 9793.
- [5] Wolf, P. A. (1968). In: *Proc. Int. Conf. Light Scattering Spectra of Solids*. Springer Verlag, New York, p. 273.
- [6] Shuker, R. and Gammon, R. (1970). *Phys. Rev. Lett.*, **25**, 222.
- [7] Shtyrkov, E. I., Klimovitskii, A., den Hartog, H. W. and Vainshtein, D. I. (2002). *J. Phys: Condens. Matter*, to be published.
- [8] Hoffman, G. and Berndt, R. (2002). *International Journal of Nanoscience*, **1**, 53.