University of Groningen

Synthesis of highly branched alpha-glucans with different structures using GH13 and GH57 glycogen branching enzymes

Zhang, Xuewen; Leemhuis, Hans; van der Maarel, Marc J. E. C.

Published in:
Carbohydrate Polymers

DOI:
[10.1016/j.carbpol.2019.04.038](https://doi.org/10.1016/j.carbpol.2019.04.038)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2019

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Zhang, X., Leemhuis, H., & van der Maarel, M. J. E. C. (2019). Synthesis of highly branched alpha-glucans with different structures using GH13 and GH57 glycogen branching enzymes. *Carbohydrate Polymers*, 216, 231-237. <https://doi.org/10.1016/j.carbpol.2019.04.038>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Synthesis of highly branched α -glucans with different structures using GH13 and GH57 glycogen branching enzymes

Xuwen Zhang^{a,*}, Hans Leemhuis^{a,b}, Marc J.E.C. van der Maarel^a

^a Department of Aquatic Biotechnology and Bioproduct Engineering, Engineering and Technology institute Groningen, University of Groningen, Groningen, 9747 AG, the Netherlands

^b Avebe Innovation Center, Groningen, 9747 AA, the Netherlands

ARTICLE INFO

Keywords:

Glycogen branching enzyme
Amylose
Amylopectin
 α -glucan
Glycoside hydrolase

ABSTRACT

Glycogen branching enzymes (GBEs) convert starch into branched α -glucan polymers. To explore if the amylose content of substrates effects the structure of the branched α -glucans, mixtures of amylose and amylopectin were converted by four thermophilic GBEs. The degree of branching and molecular weight of the products increased with an increasing percentage of amylose with the GH57 GBEs of *Thermus thermophilus* and *Thermococcus kodakarensis*, and the GH13 GBEs of *Rhodothermus marinus* and *Petrotoga mobilis*. The only exception is that the degree of branching of the *Petrotoga mobilis* GBE products is not influenced by the amylose content. A second difference is the relatively high hydrolytic activity of two GH57 GBEs, while the two GH13 GBEs have almost no hydrolytic activity. Moreover, the two GH13 GBEs synthesize branched α -glucans with a narrow molecular weight distribution, while the two GH57 GBEs products consist of two or three molecular weight fractions.

1. Introduction

Glycogen is produced by many microorganisms as a carbon and energy reserve (Roach, 2002). It is a branched polymer of anhydroglucose residues linked via α -1,4-glycosidic linkages and α -1 $\rightarrow$ 4,6-glycosidic bond branches. The branches are synthesized by glycogen branching enzymes (GBEs, EC 2.4.1.18), which cleave an α -1,4-glycosidic linkages in a linear chain and attach the cleaved off fragment onto the 6-hydroxyl group of an anhydroglucose moiety located in a chain segment of α -1,4-linked anhydroglucose residues (Devillers, Piper, Ballicora, & Preiss, 2003; Kajiura et al., 2011; H. Takata et al., 2010). GBEs are classified in two glycoside hydrolase (GH) families, 13 and 57 (Blesak & Janecek, 2012; Cantarel et al., 2009; Lombard, Ramulu, Drula, Coutinho, & Henrissat, 2014; Zona, Chang-Pi-Hin, O'Donohue, & Janecek, 2004). Although the GH13 and GH57 GBEs have a different three-dimensional structural fold (Feng et al., 2016; Hayashi et al., 2017; Na, Park, Jo, Cha, & Ha, 2017; Pal et al., 2010; Palomo et al., 2011; Santos et al., 2011), they use the same catalytic steps, involving a double displacement mechanism and a covalent glucosyl-enzyme intermediate (Chiba, 1997; Koshland, 1953).

While *in-vivo* GBEs act on growing α -glucan chains, *in-vitro* GBEs can be utilized to modify starch, amylose, and amylopectin. GBE modified starch, or (highly) branched maltodextrin, is characterized by the absence of long linear α -1,4-glucan chains and an increased percentage of

α -1 $\rightarrow$ 4,6 branches. The resulting product is highly soluble in water, and has no tendency to retrograde because of the absence of amylose and long linear α -1,4-linked chains. Various applications for highly branched maltodextrins have been reported, among which paper coating, slowly digestible starch, sport drinks ingredient, spray drying aid, and bio-friendly adhesive (Backer & Saniez, 2005; Ellis et al., 1998; Fuentes, Roturier, & Petitjean, 2005; M. J. E. C. Van der Maarel, Ter Veer, Vrieling-Smit, & Delnoye, 2014).

Currently, only the *Rhodothermus obamensis* GBEs is commercially available, under the tradename Branchzyme® from Novozymes. However, many more bacterial GH13 GBEs have been characterized, among which the GBEs of *Aquifex aeolicus* (Hiroki Takata, Ohdan, Takaha, Kuriki, & Okada, 2003; M. Van Der Maarel, Vos, Sanders, & Dijkhuizen, 2003), *Butyrivibrio fibrisolvens* (Rumbak, Rawlings, Lindsey, & Woods, 1991), *Deinococcus geothermalis* and *Deinococcus radiodurans* (Palomo, Kralj, van der Maarel, & Dijkhuizen, 2009), *Geobacillus stearothermophilus* (Hiroki Takata et al., 1994), *Geobacillus thermoglucosidans* (Ban et al., 2016; Liu et al., 2017), *Mycobacterium tuberculosis* (Garg, Alam, Kishan, & Agrawal, 2007), *Thermomonospora curvata* (Fan, Xie, Zhan, Chen, & Tian, 2016), and *Vibrio vulnificus* (Jo, Park, Jeong, Kim, & Park, 2015). Today only three GH57 GBEs have been characterized; *Pyrococcus horikoshii* (Na et al., 2017), *Thermococcus kodakarensis* (Murakami, Kanai, Takata, Kuriki, & Imanaka, 2006), and *Thermus thermophilus* (Palomo et al., 2011). The biochemical studies

* Corresponding author.

E-mail address: xuwen.zhang@rug.nl (X. Zhang).

<https://doi.org/10.1016/j.carbpol.2019.04.038>

Received 21 January 2019; Received in revised form 3 April 2019; Accepted 8 April 2019

Available online 09 April 2019

0144-8617/ © 2019 Elsevier Ltd. All rights reserved.

have reported variations in substrate specificity, with the GH57 GBEs having a higher catalytic activity with amylose than amylopectin, a substrate preference not seen with the GH13 GBEs. The GH57 GBEs have, in addition, a significant hydrolytic side activity, whereas the GH13 GBEs show hardly any hydrolytic activity (Jo et al., 2015; Palomo et al., 2009, 2011). The differences in reaction specificity are potentially advantageous in the starch processing industry, as it may lead to different types of highly branched α -glucan products.

Here the syntheses of branched α -glucan by four thermophilic GBEs is explored, revealing that the structure of the branched α -glucans is depended on the amylose content of the substrate and the GBE used.

2. Materials and methods

2.1. Materials

Amylose V and waxy potato starch (Eliane 100) were provided by Avebe (Veendam, Netherlands). Isoamylase (EC 3.2.1.68, specific activity 260 U/mg), pullulanase M1 (EC 3.2.1.41, specific activity 34 U/mg) and β -amylase (EC 3.2.1.2, specific activity 10,000 U/mL) were obtained from Megazyme (Wicklow, Ireland). General chemicals were obtained from Sigma Aldrich (Darmstadt, Germany) and VWR (Amsterdam, Netherlands).

2.2. Production and purification of glycogen branching enzymes

Codon optimized genes encoding the GBEs from *T. thermophilus* HB8 (Ttgb57) and *T. kodakarensis* KOD1 (Tkgb57) were synthesized by Baseclear (Leiden, The Netherlands), cloned into the pRSET A (Thermo Fisher Scientific, Waltham) expression vector and overexpressed in *E. coli* BL21 (DE3). The codon optimized genes encoding the GBEs from *R. marinus* (Rmgb13) and *P. mobilis* (Pmgb13) were synthesized by GeneScript (Hong Kong, China), and cloned into the pET28a expression vector and overexpressed in *E. coli* BL21 (DE3). The four encoded proteins carry a 6 $\times$ His-tag at their N-terminus. *E. coli* was cultivated in Luria-Bertani (LB) medium (10 g/L of tryptone, 5 g/L yeast extract, and 10 g/L NaCl). 100 μ g/mL ampicillin was supplemented for Ttgb57 and Tkgb57 expression and 50 μ g/mL kanamycin was applied for Rmgb13 and Pmgb13 expression. Gene expression was induced by 0.1 mM IPTG at 18 °C, and cultivation was continued for 20 h with shaking at 150 rpm. The cells were harvested by centrifugation (5000 $\times$ g, 10 min, 4 °C), washed twice with 5 mM phosphate buffer pH 7.0, and resuspended in binding buffer (20 mM sodium phosphate, 500 mM NaCl, and 20 mM imidazole, pH 7.4). Cells were lysed using a high-pressure homogenizer (Emulsiflex-B15; Avestin, Ottawa, Canada). The soluble fraction of the cell lysates was collected by centrifugation (20,000 $\times$ g, 20 min, 4 °C). The proteins were purified in two steps. The soluble fraction was incubated at 65 °C for 10 min, followed by removal of denatured proteins by centrifugation (20,000 $\times$ g, 20 min, 4 °C); the heat treatment was repeated once. Subsequently, the His-tagged proteins were purified using the HisPur™ Ni-NTA Resin according to the manufacturer's protocol. Protein concentrations were quantified using the Quick Start™ Bradford Protein Assay kit (Bio-Rad Laboratories, Veenendaal, Netherlands). The purity and molecular mass of the proteins were checked by SDS-PAGE.

2.3. Enzyme activity assays

Amylose V, dissolved in 1 M NaOH, and then neutralized to pH 7.0 with 1 M HCl, was used as a model substrate. Branched α -glucan products were prepared at the optimal reaction conditions: 0.125% (w/v) substrate, 35 μ g/mL TtGBE57, 65 °C, pH 6.5; 30 μ g/mL TkGBE57, 70 °C, pH 7.0; 3.0 μ g/mL RmGBE13, 65 °C, pH 7.0 and 3.0 μ g/mL PmGBE13, 50 °C, pH 7.0.

Branching activity, representing the newly synthesized α -1,6-glycosidic linkages, was quantified by measuring the increase in reducing

Fig. 1. SDS-PAGE of TtGBE57 (Lane 1), TkGBE57 (Lane 2), RmGBE13 (Lane 3), and PmGBE13 (Lane 4).

ends upon debranching of the product. The amount of reducing ends was measured by bicinchoninic acid (BCA) method (Waffenschmidt & Jaenicke, 1987). Briefly, 0.125% amylose V was incubated, with different GBEs, in 50 mM sodium phosphate buffer, as described above. Samples of 200 μ L were taken at regular time intervals and the reaction was stopped by boiling for 10 min. Of the samples taken, 50 μ L was debranched by adding 1 μ L of 0.1 M HCl (which lowers the pH to 5.0), 0.7 U isoamylase, 0.5 U pullulanase and 5 mM CaCl_2 , and incubating at 40 °C for 16 h. The hydrolytic activity was also quantified, by following the increase in reducing ends within the reaction mixture in time. Branching activity is simply the difference in the amount of reducing ends after debranching minus the amount of reducing ends before debranching. One unit of branching activity is defined as 1 μ mol of branches formed per minute (Palomo et al., 2011). The branching activity of TtGBE57, TkGBE57 and PmGBE13 on amylose was calculated from the increase in branches formed within the first 30 min (10 min for RmGBE13), while the hydrolytic activity is calculated from the increase in reducing ends over 24 h. The branching activity on amylopectin was calculated from the increase in branches formed within the first 15 min, while the hydrolytic activity is calculated from the increase in reducing ends over 24 h.

2.4. High performance anion exchange chromatography

Oligosaccharide analyses was carried out by High Performance Anion Exchange Chromatography (HPAEC) on a Dionex ICS-3000 system (Thermo Fisher Scientific) equipped with a 4 $\times$ 250 mm CarboPac PA-1 column. A pulsed amperometric detector with a gold electrode and an Ag/AgCl pH reference electrode was used. The system was run with a gradient of 30–600 mM NaAc in 100 mM NaOH 1 mL/min. Chromatograms were analyzed using Chromeleon 6.8 chromatography data system software (Thermo Fisher Scientific, Waltham). A mixture of glucose, maltose, maltotriose, maltotetraose, maltopentaose, maltohexaose, and maltoheptaose was used as reference for qualitative determination of elution time of each component.

The chain length distribution was determined by the debranching the branched α -glucans (2 mg/mL in 5 mM sodium acetate buffer pH 5.0) with 0.7 U/mL isoamylase and 0.5 U/mL pullulanase at 40 °C for 16 h. The debranching reactions were stopped by boiling for 5 min, and denatured proteins were removed by centrifugation, and analyzed by HPAEC.

2.5. ^1H -NMR spectroscopy

^1H -NMR spectra were recorded at a probe temperature of 323 K on a Varian Inova 500 spectrometer (NMR Center, University of Groningen). Before analysis, samples were exchanged twice in D_2O (99.9 atom% D, Sigma-Aldrich Chemical) with intermediate lyophilization, and then dissolved in 0.6 mL D_2O . Spectra were processed using MestReNova 5.3 software (Mestrelabs Research SL, Santiago de Compostella, Spain),

Table 1
The branching and hydrolytic activities of GBEs.

GBEs	Amylose as substrate			Amylopectin as substrate		
	Branching activity (mU/mg)	Hydrolytic activity (mU/mg)	Branching/Hydrolytic	Branching activity (mU/mg)	Hydrolytic activity (mU/mg)	Branching/Hydrolytic
TtGBE57	490	1.7	288	380	2.9	131
TkGBE57	560	2.6	215	450	4.3	105
PmGBE13	6,100	7.5	813	8,800	4.2	2095
RmGBE13	18,700	7.1	2,634	7,500	3.3	2272

Fig. 2. Branching and hydrolysis reaction progress.

Reaction progress is followed by quantifying the increase in reducing ends over time in the conversion of amylose V. TtGBE57 (A); TkGBE57 (B); RmGBE13 (C) and PmGBE13 (D). Black dot: the reducing end concentration of the reaction contents; Black square: the reducing end concentration increase upon debanching.

using Whittaker Smoother baseline correction and zero filling to 32 k complex points. Carbohydrate structures were determined using the previously developed $^1\text{H-NMR}$ structural-reporter-group concept of α -D-glucans (van Leeuwen, Leeftang, Gerwig, & Kamerling, 2008). The α -1,6-signal is presented at δ 4.98, originating from H1 in 1,4- α -glucose-1,6, and α -1,4-signal is at δ 5.36 from the H1 in 1,4- α -glucose-1,4 and 1 $\rightarrow$ 4,6- α -glucose-1,4 residues. The degree of branching (α -1,6-linkage ratio) was calculated by dividing the area of α -1,6-linkage peak by the total area of α -1,4-linkage and α -1,6-linkage peaks in the NMR spectra.

2.6. GPC-SEC

Molecular weight distributions were measured by GPC-SEC run with DMSO-LiBr. DMSO-LiBr (0.05 M) was prepared by stirring for 3 h at room temperature. Samples were dissolved at a concentration of 2 mg/mL in DMSO-LiBr at 80 °C for 3 h with shaking and then filtered through a 0.45 μm Millex PTFE membrane (Millipore Corporation, Billerica, USA). The Size Exclusion Chromatography (SEC) system setup (Agilent Technologies 1260 Infinity) from PSS (Mainz, Germany) consisted of an isocratic pump, auto sampler without temperature regulation, an online degasser, an inline 0.2 μm filter, a refractive index detector (G1362 A 1260 RID Agilent Technologies, Santa Clara), viscometer (ETA-2010 PSS, Mainz, Germany), and MALLS (SLD 7000 PSS, Mainz, Germany). WinGPC Unity software (PSS) was used for data processing. The samples were injected with a flow rate of 0.5 mL/min into a PFG guard-column and three PFG SEC columns 100, 300 and 4000 (PSS). The columns were held at 80 °C, and the detectors were held at 60 °C (Visco)

and 45 °C (RI). A standard pullulan kit (PSS) with molecular weights from 342 to 805,000 Da was used to generate a universal calibration curve, in order to determine the hydrodynamic volume from the elution volume. The specific RI increment value dn/dc was measured by PSS and is 0.072.

2.7. Fractionation of branched α -glucans

The branched α -glucans obtained from amylose by TtGBE57 modification were separated into a high and low molecular weight fractions using size-exclusion chromatography (HiPrep 26/60 Sephacryl S-500 h column). Briefly, 25 mg branched α -glucan in 5 mL was injected, and the column was run at 2.5 mL/min water with 0.02% NaN_3 . The collected fractions were freeze dried, and subsequently analyzed by NMR and GPC-SEC, as described above.

2.8. Modification of different amylose content substrates

The mixtures of amylose and amylopectin were prepared by combining solutions of amylose V and waxy potato starch at different ratios. Firstly, 5 mg/mL amylose V was dissolved into 1 M NaOH, and then neutralized to pH 7.0. Waxy potato starch (7.5 mg/mL) was dissolved in 50 mM phosphate buffer with pH 7 by boiling. The enzymatic reaction conditions were as above. The reactions were stopped by boiling for 10 min, the denatured proteins removed by centrifugation, and the supernatant dialyzed using a dialysis tube with a cutoff size of 100–500 Da. The samples were freeze dry and analyzed, as described

Fig. 3. Chain length distribution of the branched α -glucans derived from amylose V. TtGBE57 (A), TkGBE57 (B), RmGBE13 (C) and PmGBE13 (D). The branched α -glucans were debranched by isoamylase/pullulanase and analyzed by HPAEC-PAD.

above.

3. Results and discussion

3.1. Branching and hydrolytic activity of glycogen branching enzymes

Two GH57 *gbe* genes, from *T. thermophilus* and *T. kodakarensis*, and two GH13 *gbe* genes, from *R. marinus* and *P. mobilis*, were overexpressed in *E. coli* and the corresponding GBEs were purified by a combination of heat treatment and His-tag affinity chromatography (Fig. 1). The two GH13 GBEs have a considerable higher branching activity than the two GH57 GBEs, using amylose V and amylopectin as substrates (Table 1). The two GH57 GBEs have a slightly higher branching activity on amylose, the RmGBE13 shows 40% more branching activity with amylopectin, and PmGBE13 has two times more branching activity on amylose.

In addition to the branching activity, GBEs also possess a low hydrolytic activity, which results in the formation of oligo and polysaccharides smaller than the substrate. Acting on amylose V, both GH57 GBEs have a considerably lower ratio of branching over hydrolytic activity than the two GH13 GBEs (Table 1), which is in agreement with previous publications (Palomo et al., 2009, 2011). Indeed, upon prolonged incubation of amylose V with the two GH57 GBEs, about 15% of the catalytic actions had resulted in the formation of a new reducing end (hydrolysis activity), and 85% in the formation of a new branch (branching activity) (Fig. 2). The two GH57 GBEs are even more hydrolytic with amylopectin as substrate, with 40% hydrolysis and 60% branching (Supplementary Fig. S1). The two GH13 GBEs, in contrast, formed almost only branches, with both amylose and amylopectin (Fig. 2 and Supplementary Fig. S1). Indeed, HPAEC analysis shows

substantial amounts of short oligosaccharides in the products made by the two GH57 GBEs (Fig. 3), which are basically absent in the products made by the two GH13 GBEs. Thus, the two GH57 GBEs are far more hydrolytic than two GH13 GBEs, when acting *in-vitro* on pre-existing α -glucan polymers. Although out of scope for this publication, it remains an intriguing question whether GH57 GBEs are also relative hydrolytic *in-vivo*.

3.2. The structure of branched α -glucan made by GBEs is influenced by the amylose to amylopectin ratio

As native starches are composed of amylopectin and amylose, with the amylose content ranging from as low as 0 up to 70% in commercially available starches (Jane et al., 1999), it was explored if the amylopectin to amylose ratio affects the structure of the branched α -glucan synthesized. Therefore various ratios of amylose and amylopectin were incubated with the four GBEs and the obtained products were analyzed in detail. Firstly, the chain length distribution of the branched α -glucans derived from 100% amylose and 100% amylopectin were compared. This revealed that the two GH57 GBEs form products with a wider chain length distribution. While the products of the two GH13 GBEs are particular rich in chains up to DP 10, the two GH57 GBE products contain clearly more relative long chains of DP 10 to 15 (Figs. 3 & 4). The two GH57 GBE products derived from amylopectin even show a bimodal pattern, with maxima at DP7 and DP11 (Fig. 4). Although the products of the two thermophilic GH13 GBEs explored here have very similar chain length distribution, not all GH13 GBEs synthesize similar products. For examples, the potato SBEI and SBEII GH13 branching enzymes form branched α -glucans with distinct chain length distributions (Rydberg, Andersson, Andersson, Aman, & Larsson,

Fig. 4. Chain length distribution of the branched α -glucans derived from amylopectin. TtGBE57 (A), TkGBE57 (B), RmGBE13 (C) and PmGBE13 (D). The branched glucans were debranched by isoamylase/pullulanase and analyzed by HPAEC-PAD.

Fig. 5. The correlation between amylose content of the substrates and degree of branching. The amylose content was set by mixing amylose V and amylopectin, both from potato.

2001).

Subsequently the degree of branching of all samples was determined, demonstrating that the two GH13 GBEs form products with a higher degree of branching. Surprisingly, it was also observed that the degree of branching is positively correlated with the percentage of amylose in the substrate with the two GH57 GBEs (Fig. 5). The same correlation is seen with the RmGBE13, although the effect is somewhat milder, while the effect is absent with the PmGBE13 (Fig. 5). Since the initial branching activity of the two GH57 GBEs with amylose and amylopectin are quite similar (Table 1), the much higher degree of branching reached with amylose indicates that the branches are

distributed more efficiently starting with amylose, compared to amylopectin. However, a previous study reported that GBE formed slightly less branched α -glucans with increasing amylose content of the substrate (Sorndech et al., 2016). Sorndech et al. used high Mw (5500 kDa) barley amylose and waxy maize amylopectin, while in the current study potato amylose with a much lower Mw (100 kDa) was used. Possibly branching enzymes are more effective with shorter substrates.

3.3. Branched α -glucans derived from amylose and amylopectin have different molecular weight profiles

Besides the degree of branching and the chain length distributions also the molecular weight (Mw) is a key structural parameter of branched α -glucans. To determine if the Mw is influenced by the amylose content of the substrate the branched α -glucans derived from amylose and amylopectin were analyzed by GPC. The first observation is that the four GBEs synthesize branched α -glucans with distinct Mw distributions. Acting on amylose the two GH13 GBEs generate products with a relative mono disperse Mw distribution (Fig. 6); $\sim 1 \times 10^5$ Da for RmGBE13 and $\sim 2 \times 10^5$ Da for PmGBE13. The two GH57 GBEs surprisingly generated products consisting of a low and a high Mw fraction (Fig. 6). Separation of the high and low Mw fractions of the TtGBE57 product, using size-exclusion column chromatography, revealed that the low Mw fraction ($< 4 \times 10^4$ Da) contains only 5% branches and the high Mw fraction ($> 7 \times 10^4$ Da) contains 10% branches. This indicates that the low Mw fraction consist mainly of the products resulting from hydrolysis with mild branching, whereas the high Mw fraction is the result of the branching reaction.

The picture is distinctively different with amylopectin as substrate. The most remarkable difference being the lower Mw of the branched α -glucans derived from amylopectin compared to the products derived

Fig. 6. The molecular weight distribution of the branched α -glucans derived from amylose and amylopectin mixtures by TtGBE57 (A), TkGBE57 (B), RmGBE13 (C) and PmGBE13 (D) treatment. The analysis was performed by GPC-MALLS-RI run with DMSO containing 50 mM LiBr.

Table 2

The DB of pea and waxy corn starches following modifications with *T. thermophilus*, *T. kodakarensis*, *R. marinus*, and *P. mobilis* GBEs. Based on the results of triplicate analyses.

GH Family	GBE	Pea starch	Waxy corn starch
57	TtGBE57	6.2 ± 0.44	5.3 ± 0.65
	TkGBE57	6.2 ± 0.64	5.0 ± 0.21
13	RmGBE13	10.9 ± 0.20	10.2 ± 0.12
	PmGBE13	13.1 ± 0.30	12.7 ± 0.49

from amylose. Subsequently the mixtures of amylose and amylopectin were converted by the four GBEs revealing that the average Mw increases with increasing amylose content. The same phenomena has also been observed for the GH13 GBE from *Rhodothermus obamensis* (Sorndech et al., 2016), and now also in this study. From these observations it is concluded that GBEs convert the high Mw amylopectin into branched α -glucans with lower Mw, whereas amylose is converted into branched α -glucans with a Mw corresponding to that of amylose. The Mw distributions of the branched α -glucans derived from amylose and amylopectin show, however, also similarities. The GH13 RmGBE13 product is again rather mono disperse, whereas the two GH57 products consist of two or three Mw fractions (Fig. 6). The GH13 PmGBE13 derived from amylopectin product is special in the sense that consist of two Mw fractions, while the enzyme converts amylose in a mono disperse branched α -glucan (Fig. 6). Thus, the different GBEs create highly branched α -glucan with various Mw distributions, and the GH13 RmGBE13 is the best choice for the production of product with a

uniform Mw distribution.

3.4. Synthesis of branched α -glucans from a waxy starch and a high amylose starch

The question arises if the trends seen with the artificial mixtures of amylose and amylopectin also hold in the conversion of natural starches, which vary widely in their amylose content, (Knutson & Grove, 1994; Morrison & Laignelet, 1983). To test this waxy corn and a high amylose pea starch (with 35% amylose) (Jensen et al., 2013; Lourdin, Della Valle, & Colonna, 1995) were treated with the GBEs. NMR analysis of the branched α -glucans obtained demonstrated that the degree of branching of these products (Table 2) is in good agreement with the values obtained with the artificial mixtures of amylose or amylopectin (Fig. 5). Thus, the two GH13 GBEs synthesized branched α -glucans with a higher degree of branching than the two GH57 GBEs (Table 2). And secondly, the two GH57 GBEs create products with a higher degree of branching from the amylose rich pea starch than from the waxy maize starch, as predicted by the model system employing a mixture of amylose and amylopectin.

4. Conclusions

Here we report the synthesis of branched α -glucans by four thermophilic GBEs. Whereas amylose is converted in highly branched α -glucans by all four GBEs, conversion of amylopectin yields highly branched and modest branched products with the GH13 and GH57 GBEs, respectively. The two GH13 GBEs products have a narrow

molecular weight distribution, while the two GH57 GBEs products have a wide molecular weight distribution. We speculate that the production of branched α -glucans with a narrow molecular weight distribution requires GBEs with very low hydrolytic activity. Indeed, the commercially available RmGBE13 (Branchzyme, Novozymes) has the highest branching over hydrolysis specificity and synthesizes the branched α -glucan with the most mono disperse molecular weight distribution of the GBEs evaluated.

Acknowledgement

This work was financially supported by the China Scholarship Council (XZ) and the University of Groningen. We thank prof. dr. Lubbert Dijkhuizen (Microbial Physiology, University of Groningen) for kindly allowing us to use the HPAEC-PAD equipment and Albert J.J. Woortman (Macromolecular Chemistry and New Polymeric Materials, University of Groningen) for his assistance in molar mass distribution analysis.

Appendix A. Supplementary data

Supplementary material related to this article can be found, in the online version, at doi:<https://doi.org/10.1016/j.carbpol.2019.04.038>.

References

- Backer, D., & Saniez, M.-H. (2005). *Soluble highly branched glucose polymers and their method of production*. United States US2005142167 (A1).
- Ban, X., Li, C., Gu, Z., Bao, C., Qiu, Y., Hong, Y., et al. (2016). Expression and biochemical characterization of a thermostable branching enzyme from *Geobacillus thermoglucosidans*. *Journal of Molecular Microbiology and Biotechnology*, 26(5), 303–311.
- Blesak, K., & Janecek, S. (2012). Sequence fingerprints of enzyme specificities from the glycoside hydrolase family GH57. *Extremophiles: life under extreme conditions*, 16(3), 497–506.
- Cantarel, B. L., Coutinho, P. M., Rancurel, C., Bernard, T., Lombard, V., & Henrissat, B. (2009). The Carbohydrate-Active Enzymes database (CAZy): An expert resource for Glycogenomics. *Nucleic Acids Research*, 37, D233–D238.
- Chiba, S. (1997). Molecular mechanism in α -glucosidase and glucoamylase. *Bioscience, Biotechnology, and Biochemistry*, 61(8), 1233–1239.
- Devillers, C. H., Piper, M. E., Ballicora, M. A., & Preiss, J. (2003). Characterization of the branching patterns of glycogen branching enzyme truncated on the N-terminus. *Archives of Biochemistry and Biophysics*, 418(1), 34–38.
- Ellis, R. P., Cochrane, M. P., Dale, M. F. B., Duffus, C. M., Lynn, A., Morrison, I. M., et al. (1998). Starch production and industrial use. *Journal of Environmental Science and Health Part B, Pesticides, Food Contaminants, and Agricultural Wastes*, 77(3), 289–311.
- Fan, Q., Xie, Z. J., Zhan, J. L., Chen, H. L., & Tian, Y. Q. (2016). A glycogen branching enzyme from *Thermomonospora curvata*: Characterization and its action on maize starch. *Starch-Starke*, 68(3–4), 355–364.
- Feng, L., Fawaz, R., Hovde, S., Sheng, F., Nosrati, M., & Geiger, J. H. (2016). Crystal structures of *Escherichia coli* branching enzyme in complex with cyclodextrins. *Acta Crystallogr D*, 72, 641–647.
- Fuertes, P., Roturier, J.-M., & Petitjean, C. (2005). *Soluble highly branched glucose polymers*. United States US2005159329 (A1).
- Garg, S. K., Alam, M. S., Kishan, K. R., & Agrawal, P. (2007). Expression and characterization of α -(1,4)-glucan branching enzyme Rv1326c of *Mycobacterium tuberculosis* H37Rv. *Protein Expression and Purification*, 51(2), 198–208.
- Hayashi, M., Suzuki, R., Colleoni, C., Ball, S. G., Fujita, N., & Suzuki, E. (2017). Bound substrate in the structure of Cyanobacterial branching enzyme supports a new mechanistic model. *The Journal of Biological Chemistry*, 292(13), 5465–5475.
- Jane, J., Chen, Y., Lee, L., McPherson, A., Wong, K., Radosavljevic, M., et al. (1999). Effects of amylopectin branch chain length and amylose content on the gelatinization and pasting properties of starch. *Cereal Chemistry*, 76(5), 629–637.
- Jensen, S. L., Zhu, F., Vamadevan, V., Bertoft, E., Seetharaman, K., Bandsholm, O., et al. (2013). Structural and physical properties of granule stabilized starch obtained by branching enzyme treatment. *Carbohydrate Polymers*, 98(2), 1490–1496.
- Jo, H. J., Park, S., Jeong, H. G., Kim, J. W., & Park, J. T. (2015). *Vibrio vulnificus* glycogen branching enzyme preferentially transfers very short chains: N1 domain determines the chain length transferred. *FEBS Letters*, 589(10), 1089–1094.
- Kajiura, H., Takata, H., Akiyama, T., Kakutani, R., Furuyashiki, T., Kojima, I., et al. (2011). In vitro synthesis of glycogen: The structure, properties, and physiological function of enzymatically-synthesized glycogen. *Biologia*, 66(3), 387–394.
- Knutson, C., & Grove, M. J. C. C. (1994). Rapid method for estimation of amylose in maize starches. *Cereal Chemistry*, 71(5), 469–471.
- Koshland, D. E. (1953). Stereochemistry and the mechanism of enzymatic reactions. *Biological Reviews*, 28(4), 416–436.
- Liu, Y., Li, C., Gu, Z., Xin, C., Cheng, L., Hong, Y., et al. (2017). Alanine 310 is important for the activity of 1, 4- α -glucan branching enzyme from *Geobacillus thermoglucosidans* STB02. *International Journal of Biological Macromolecules*, 97, 156–163.
- Lombard, V., Ramulu, H. G., Drula, E., Coutinho, P. M., & Henrissat, B. (2014). The carbohydrate-active enzymes database (CAZy) in 2013. *Nucleic Acids Research*, 42(D1), D490–D495.
- Lourdin, D., Della Valle, G., & Colonna, P. J. C. P. (1995). Influence of amylose content on starch films and foams. *Carbohydrates Polymer*, 27(4), 261–270.
- Morrison, W. R., & Laignelet, B. (1983). An improved colorimetric procedure for determining apparent and total amylose in cereal and other starches. *The Journal of Cereal Science*, 1(1), 9–20.
- Murakami, T., Kanai, T., Takata, H., Kuriki, T., & Imanaka, T. (2006). A novel branching enzyme of the GH-57 family in the hyperthermophilic archaeon *Thermococcus kodakaraensis* KOD1. *Journal of Bacteriology*, 188(16), 5915–5924.
- Na, S., Park, M., Jo, I., Cha, J., & Ha, N. C. (2017). Structural basis for the transglycosylase activity of a GH57-type glycogen branching enzyme from *Pyrococcus horikoshii*. *Biochemical and Biophysical Research Communications*, 484(4), 850–856.
- Pal, K., Kumar, S., Sharma, S., Garg, S. K., Alam, M. S., Xu, H. E., et al. (2010). Crystal structure of full-length *Mycobacterium tuberculosis* H37Rv glycogen branching enzyme insights of N-terminal β -sandwich in substrate specificity and enzymatic activity. *The Journal of Biological Chemistry*, 285(27), 20897–20903.
- Palomo, M., Kralj, S., van der Maarel, M. J. E. C., & Dijkhuizen, L. (2009). The unique branching patterns of *Deinococcus* glycogen branching enzymes are determined by their N-terminal domains. *Applied and Environmental Microbiology*, 75(5), 1355–1362.
- Palomo, M., Pijning, T., Booiiman, T., Dobruchowska, J. M., van der Vliet, J., Kralj, S., et al. (2011). *Thermus thermophilus* glycoside hydrolase family 57 branching enzyme crystal structure, mechanism of action, and products formed. *The Journal of Biological Chemistry*, 286(5), 3520–3530.
- Roach, P. J. (2002). Glycogen and its metabolism. *Current Molecular Medicine*, 2(2), 101–120.
- Rumbak, E., Rawlings, D., Lindsey, G., & Woods, D. (1991). Characterization of the *Butyrivibrio fibrisolvens* glgB gene, which encodes a glycogen-branching enzyme with starch-clearing activity. *Journal of Bacteriology*, 173(21), 6732–6741.
- Rydberg, U., Andersson, L., Andersson, R., Aman, P., & Larsson, H. (2001). Comparison of starch branching enzyme I and II from potato. *European Journal of Biochemistry*, 268(23), 6140–6145.
- Santos, C. R., Tonoli, C. C. C., Trindade, D. M., Betzel, C., Takata, H., Kuriki, T., et al. (2011). Structural basis for branching-enzyme activity of glycoside hydrolase family 57: Structure and stability studies of a novel branching enzyme from the hyperthermophilic archaeon *Thermococcus kodakaraensis* KOD1. *Proteins*, 79(2), 547–557.
- Sorndech, W., Sagnelli, D., Meier, S., Jansson, A. M., Lee, B. H., Hamaker, B. R., et al. (2016). Structure of branching enzyme- and amyloamylase modified starch produced from well-defined amylose to amylopectin substrates. *Carbohydrates Polymer*, 152, 51–61.
- Takata, H., Akiyama, T., Kajiura, H., Kakutani, R., Furuyashiki, T., Tomioka, E., et al. (2010). Application of branching enzyme in starch processing. *Biocatal Biotransformation*, 28(1), 60–63.
- Takata, H., Ohdan, K., Takaha, T., Kuriki, T., & Okada, S. (2003). Properties of branching enzyme from hyperthermophilic bacterium, *Aquifex aeolicus*, and its potential for production of highly-branched cyclic dextrin. *Journal of Applied Glycoscience* (1999), 50(1), 15–20.
- Takata, H., Takaha, T., Kuriki, T., Okada, S., Takagi, M., & Imanaka, T. (1994). Properties and active center of the thermostable branching enzyme from *Bacillus stearothermophilus*. *Applied and Environmental Microbiology*, 60(9), 3096–3104.
- Van der Maarel, M. J. E. C., Ter Veer, B. C. A., Vrieling-Smit, A., & Delnoye, D. A. P. (2014). *Methods and means for coating paper by film coating*. Netherlands WO2014003556 (A1).
- Van Der Maarel, M., Vos, A., Sanders, P., & Dijkhuizen, L. (2003). Properties of the glucan branching enzyme of the hyperthermophilic bacterium *Aquifex aeolicus*. *Biocatal Biotransformation*, 21(4–5), 199–207.
- van Leeuwen, S. S., Leeflang, B. R., Gerwig, G. J., & Kamerling, J. P. (2008). Development of a ¹H-NMR structural-reporter-group concept for the primary structural characterisation of α -D-glucans. *Carbohydrate Research*, 343(6), 1114–1119.
- Waffenschmidt, S., & Jaenicke, L. (1987). Assay of reducing sugars in the nanomole range with 2,2'-bichinchonate. *Analytical Biochemistry*, 165(2), 337–340.
- Zona, R., Chang-Pi-Hin, F., O'Donohue, M. J., & Janecek, S. (2004). Bioinformatics of the glycoside hydrolase family 57 and identification of catalytic residues in amylopullulanase from *Thermococcus hydrothermalis*. *European Journal of Biochemistry*, 271(14), 2863–2872.