University of Groningen

Vortex Depinning in YBa₂Cu₃O₇

Hebard, A.F.; Palstra, T.T.M.

Published in:
Physica C: Superconductivity

DOI:
[10.1016/0921-4534\(89\)90643-6](https://doi.org/10.1016/0921-4534(89)90643-6)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
1989

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Hebard, A. F., & Palstra, T. T. M. (1989). Vortex Depinning in YBa₂Cu₃O₇: Resistive Transition Identification of the Crossover from Flux-Creep to Flux-Flow Behavior. *Physica C: Superconductivity*, 162(8). [https://doi.org/10.1016/0921-4534\(89\)90643-6](https://doi.org/10.1016/0921-4534(89)90643-6)

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

VORTEX DEPINNING IN $\text{YBa}_2\text{Cu}_3\text{O}_7$: RESISTIVE TRANSITION IDENTIFICATION OF THE CROSSOVER FROM FLUX-CREEP TO FLUX-FLOW BEHAVIOR

A.F. HEBARD and T. T. M. PALSTRA

AT&T Bell Laboratories, Murray Hill, New Jersey 07974

Analysis of resistive transitions of $\text{YBa}_2\text{Cu}_3\text{O}_7$ crystals reveals a scaling behavior which identifies the vortex-depinning critical field H_{cp} , hence the crossover in behavior from flux creep to flux flow. The inferred H_{cp} for $\text{YBa}_2\text{Cu}_3\text{O}_7$ crystals closely approximates the magnitude and temperature dependence of H_{cp} derived from penetration length measurements of thin films.

1. INTRODUCTION

A complete characterization of the resistive transitions of high- T_c materials necessitates an understanding of the temperature and field dependence of the energy barriers $U(T, H)$ which impede flux motion. Resistance measurements¹ at different fields H show clearly the importance of thermal activation over energy barriers (i.e., flux creep) where the resistance is proportional to $\exp(-U(T, H)/k_B T)$. In a complementary way, measurements of the penetration length λ at different H probe directly the curvature of these wells for small vortex displacements.²

Most importantly, both the resistance and the penetration length measurements share a common aspect by pointing to a field-dependent critical temperature $T_c(H)$ where $U(T, H)$ becomes negligible. In the resistance measurements³ this temperature is inferred by extrapolating the logarithmic slope $d(\ln R)/d(\ln T^{-1})$ to zero whereas in the penetration length measurements² this temperature is defined by extrapolating λ^{-1} to zero. Separately, the penetration length measurements show that in the field range $1 \text{ T} \leq H \leq 14 \text{ T}$ the linear dependence $H_{cp}^{1/2} \propto T$ is obeyed. We demonstrate here using a scaling argument that this same functional form for H_{cp} is manifest in the resistance transitions, shown in Fig. 1, of a $\text{YBa}_2\text{Cu}_3\text{O}_7$ crystal. Consequently, both measurements are consistent with the notion of a vortex-depinning

critical field $H_{cp}(T)$ which delineates the crossover from flux-creep to flux-flow behavior.

2. THE SCALING MODEL

The central assumption of our model is that there is a well-defined temperature $T_c(H)$ below which vortex motion is dominated by the presence of non-zero barriers and above which the vortices are free to flow unimpeded. At $H = H_{cp}$ where $U \sim k_B T$ there is no creep contribution to the resistivity ρ which can therefore be written in the

FIGURE 1
Resistive transitions at fields (H parallel to c -axis) of 1, 2, 5, 7.5, 10, and 12 T of a $\text{YBa}_2\text{Cu}_3\text{O}_7$ crystal.

form $\rho = H_{cp} \Phi_0 / c^2 \eta$, where Φ_0 is the flux quantum and η the vortex flow viscosity, assumed to be a constant.

With these assumptions, it is straightforward to analyze a family of $\rho(T)$ curves¹ taken at different fields such as shown in Fig. 1. We begin by choosing an arbitrary resistivity threshold, say $1.0 \mu\Omega \text{ cm}$ for the 1 T curve, and marking it with an identifier $\times$. In the flux flow regime the linear dependence of ρ on H_{cp} implies a linear scaling with H of the 1 T resistivity threshold. Thus $T_c(H)$ on the higher field curves can be identified and the locus of points ($\times$) plotted as shown in Fig. 1. Similar loci are shown for 1 T resistivity thresholds of $0.01 \mu\Omega \text{ cm}$ ($+$), $0.1 \mu\Omega \text{ cm}$ ($\square$) and $3.0 \mu\Omega \text{ cm}$ (∇).

3. RESULTS AND CONCLUSIONS

Having determined possible trajectories for $H_{cp}(T)$ in Fig. 1 which depend only on the initial guess of a threshold resistivity, we can now directly interpolate to find the dependence of H_{cp} on temperature. The resulting dependences for resistivity thresholds of $0.01 \mu\Omega \text{ cm}$ ($+$), $0.1 \mu\Omega \text{ cm}$ ($\square$), $1.0 \mu\Omega \text{ cm}$ ($\times$) and $3.0 \mu\Omega \text{ cm}$ (∇) are shown in the $H^{1/2}$ versus T plot of Fig. 2(a). For resistivity thresholds of $1.0 \mu\Omega \text{ cm}$ and smaller the agreement with the aforementioned $H_{cp}^{1/2} \propto T$ dependence found in penetration length measurements [see Fig. 2(a)] is excellent. We note that a higher resistivity threshold of $3.0 \mu\Omega \text{ cm}$ (∇) exhibits a pronounced deviation with positive curvature whereas lower resistivity thresholds ($+$ and $\square$) exhibit less pronounced deviations with increasing negative curvature.

ACKNOWLEDGEMENTS

The authors appreciate useful discussions with B. Batlogg, P. L. Gammel, P. Littlewood, and S. Martin.

REFERENCES

1. T. T. M. Palstra, B. Batlogg, L. F. Schneemeyer, and J. V. Waszczak, Phys. Rev. Lett. 61 (1988) 1662, and Appl. Phys. Lett. B54 (1989) 763.
2. A. F. Hebard, P. L. Gammel, C. E. Rice, and A. F. J. Levi, to be published in Phys. Rev. B.
3. T. T. M. Palstra, B. Batlogg, R. B. VanDover, L. F. Schneemeyer, and J. V. Waszczak, to be published.

FIGURE 2
Plots of $H_{cp}^{1/2}$ vs T for (a) interpolated temperature dependences using the trajectories in Fig. 1 defined by the symbols ($+$, $\square$, $\times$, ∇) common to both figures and for (b) the penetration depth measurements.