University of Groningen

Large coupled magnetoresponses in EuNbO₂N

Jorge, A. Belen; Oro-Sole, Judith; Bea, Ana M.; Mufti, Nandang; Palstra, Thomas T. M.; Rodgers, Jennifer A.; Attfield, J. Paul; Fuertes, Amparo

Published in:
Journal of the American Chemical Society

DOI:
[10.1021/ja804139g](https://doi.org/10.1021/ja804139g)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2008

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Jorge, A. B., Oro-Sole, J., Bea, A. M., Mufti, N., Palstra, T. T. M., Rodgers, J. A., Attfield, J. P., & Fuertes, A. (2008). Large coupled magnetoresponses in EuNbO₂N. *Journal of the American Chemical Society*, 130(38), 12572-+. <https://doi.org/10.1021/ja804139g>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Supporting Information for:

Large coupled magneto-responses in EuNbO_2N by A. Belén Jorge et al

Experimental Details

Samples of EuTaO_2N and EuNbO_2N were prepared by ammonolysis at 950 °C of EuTaO_4 and EuNbO_4 respectively. The oxide precursors were prepared by solid state reaction in air between Eu_2O_3 (Aldrich, 99.99 %) and Ta_2O_5 or Nb_2O_5 (Aldrich, 99.99 %). Eu_2O_3 was previously treated at 900 °C for 12 hours. The binary oxides were mixed in the stoichiometric proportions, pelletized and treated at 1000 °C for 12 hours, then retreated at 1400 °C for 12 hours with intermediate regrinding. These two cycles were performed three times, until no impurities were detected in the X-ray diffraction patterns. EuTaO_4 and EuNbO_4 were nitrided by two 15 hours treatments in flowing NH_3 (Carburos Metálicos, 99.9%) at a rate of 200 cm^3/min with subsequent quenching to room temperature in the ammonia atmosphere. The second treatment was done on a pellet of 7 mm diameter pressed at 3 tons for performing the electrical measurements.

N contents were determined by combustion analysis using a Carlo Erba instrument. Synchrotron powder X-ray diffraction data were collected at 290 K on instrument ID31 at the ESRF, Grenoble from capillary samples in the angular range $3 \leq 2\theta \leq 40^\circ$ with a wavelength of 0.3983 Å and electron diffraction patterns were obtained in a JEOL 1210 electron microscope operating at 120 kV (see Figure).

Magnetic measurements were performed between 2 and 300 K in fields of 0.0025 and 1 T using a Quantum Design SQUID magnetometer. $M(H)$ curves were measured up to 5 T for temperatures between 2 K and 20 K. The dielectric constant and resistivity were measured using an Agilent 4284A LCR meter and an Agilent 3458A multimeter, respectively. The magnetocapacitance was measured at several frequencies and we show the values measured at 100 kHz. The contacts were made using silver epoxy. The temperature and magnetic field were controlled through a Physical Properties Measurement System PPMS (Quantum Design), using a home-built insert and wiring.

Supporting Figure. Diffraction data for EuNbO_2N . (a) The fitted synchrotron X-ray diffraction profile. The expanded peak in the inset is split by the tetragonal lattice distortion. The data are fitted using a centrosymmetric $P4/mmm$ model. An acentric $P4mm$ refinement model that would be consistent with a ferroelectric distortion gave no significant improvement and was unstable. (b) Electron diffraction pattern along the $[0-11]$ zone axis with additional spots (arrowed) that reveal a further $\sqrt{2} \times \sqrt{2} \times 2$ body-centred superstructure.