University of Groningen

Characterization of ultra-heavily damaged NaCl

Hartog, H.W. den; Sugonyako, A.V.; Vainshtein, D.I.; Turkin, A.A.; Sulyanov, S.N.; Kheiker, D.M.; Dorovatovskii, P.V.

Published in:
Physica Status Solidi (C)

DOI:
[10.1002/pssc.200673768](https://doi.org/10.1002/pssc.200673768)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2007

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Hartog, H. W. D., Sugonyako, A. V., Vainshtein, D. I., Turkin, A. A., Sulyanov, S. N., Kheiker, D. M., & Dorovatovskii, P. V. (2007). Characterization of ultra-heavily damaged NaCl. *Physica Status Solidi (C)*, 4(3), 1079-1083. <https://doi.org/10.1002/pssc.200673768>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Characterization of ultra-heavily damaged NaCl

H. W. den Hartog^{*1}, A. V. Sugonyako¹, D. I. Vainshtein¹, A. A. Turkin², S. N. Sulyanov³,
D. M. Kheiker^{3,4}, and P. V. Dorovatovskii^{3,4}

¹ University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands

² National Science Centre, Institute of Physics and Technology, 61108 Kharkov, Ukraine

³ Institute of Crystallography, RAS, Leninsky pr. 59, 119333 Moscow, Russia

⁴ Kurchatov Centre of Synchrotron Radiation, Kurchatova pl. 1, 123182 Moscow, Russia

Received 7 July 2006, revised 2 November 2006, accepted 7 November 2006

Published online 9 March 2007

PACS 61.10.Nz, 61.80.Fe, 61.82.Ms, 65.40.Gr, 76.30.Lh, 82.70.Dd

In this paper we present the progress made to (i) characterize the defect state of ultra-heavily damaged rock salt samples with up to more than 20 at% Na colloids, which had been irradiated with 0.5 MeV electrons at 100 °C up to 10⁴ MGy (1000 GRad), and (ii) understand their physical properties. The explanation of the observations, made by means of a variety of experimental techniques, is not trivial and often the results obtained with different experimental techniques lead to conflicting interpretations.

© 2007 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim

1 Introduction We have carried out experimental investigations with several independent techniques on the defect structure of heavily irradiated NaCl. Recently we have extended the irradiation dose considerably. The maximum dose is now 1 TRad (10¹⁰ Gy) and far more heavily damaged samples have been obtained than before; we have reached concentrations as high as 25–30 at% metallic Na and chlorine, present in Na-colloids and Cl₂-bubbles, respectively. These precipitates were found to have complex and unexpected magnetic, melting, electric conductivity, optical and wide angle X-ray scattering (WAXS) properties. The results for Na-precipitates suggest that the defect structure consists of a dense network of quasi-1D coupled nano-particles, which in some cases shows a Metal-Insulator (M.I.) transition at low temperature [1–4]. Raman scattering experiments have provided evidence for the existence of narrow quasi-1D geometrical structures of sodium nano-particles with a width of a few nm [5]. In AC conductivity measurements as a function of T we have found a discontinuity, which becomes steeper with increasing damage percentage [1]. Compared with this, for chlorine only limited information is available. Our observations indicate that the properties of the chlorine precipitates are similar to those found for (i) implanted rare gas bubbles in metals and (ii) heterogeneous materials consisting of a matrix with nano-pores, which are filled with a condensed phase of gas atoms/molecules [6, 7]. In this paper we will present new electron spin resonance (ESR) and WAXS diffraction results for ultra-heavily damaged NaCl and we will attempt to interpret the available information in an effort to understand the defect structure of this exotic material. This is not a trivial task, because the diffraction data provide information about the overall structure of the precipitate system, which to some extent seems to be in contrast with results of differential scanning calorimetry (DSC), ESR, Raman scattering, etc., which provide information by means of local excitations. Therefore the experiments allow us to draw a local picture of the defect system.

* Corresponding author: e-mail: h.w.den.hartog@rug.nl

2 Experimental results

2.1 Melting results Melting of precipitates in NaCl, irradiated with 0.5 MeV electrons at 100 °C up to 10^4 MGy (1000 GRad), behaves anomalously. Three or even more Na melting peaks are observed, while at least one of them is affected by heat treatment at moderate temperatures [8]. Only one Cl melting peak is found, but often two freezing peaks are present (see Fig. 1a). A clear-cut explanation for this is not available yet. The pressure in the chlorine precipitates is estimated to be ~ 1 kbar. To calculate the pressure it is assumed that during the experiment in the heating mode high pressure exists in the precipitates, while in the cooling mode the pressure drops as soon as freezing starts. It can be shown that the difference in pressure during melting and freezing causes a difference in the latent heat effects. In addition, it is expected that the latent heat peak in the cooling has shifted by about 18–20 °C compared to the melting peak (heating mode). The presence of more than one freezing peak suggests that the pressure in the two types of bubbles is different, which is not unreasonable, because we are dealing with very heavily damaged NaCl, sometimes with >20 at% of the NaCl molecules transformed into Na and chlorine. Another explanation is that the extra freezing peaks are due to changes in the super-cooling. In Fig. 1 we show two examples of ultra-heavily damaged NaCl. In the first example (heavily irradiated pure NaCl, Fig. 1a) two freezing peaks can be observed clearly, while in the example (KBF_4 doped NaCl, Fig. 1b) we have observed only one well-defined freezing peak. The observation of two freezing peaks instead of one does not depend on the presence of impurities. With increasing dose the probability to observe two freezing peaks seems to increase gradually. For an extensive description of the melting phenomena of radiolytic Na in heavily damaged NaCl we refer to [8].

Fig. 1 Melting and freezing experiments of chlorine in ultra-heavily damaged NaCl observed in the heating and cooling mode, respectively. In the heating mode always one peak (the melting peak) is observed. In the cooling mode a well-defined peak at -123 °C is observed, often combined with a wide peak at -115 °C (a). In many cases in both the heating and cooling mode one well-defined peak is observed (b).

2.2 ESR results In heavily damaged samples the intensity and width of the ESR line of Na particles behave anomalously. At first sight room temperature ESR measurements indicate that with increasing damage (i.e. metallic Na) the size of the precipitates increases (Fig. 2). Low temperature ESR provides clear evidence that Na particles in heavily damaged NaCl are not isolated conducting objects in an insulator. Below some critical temperature T_c , which depends on the damage level, the intensity of the ESR line decreases, while the width increases (Fig. 3). Above T_c the ESR signal behaves as for bulk Na, although the line width is larger than for bulk Na. The observations are explained by assuming that the colloids form quasi-1D structures of Na nano-particles and the conduction electrons move freely in the precipitate structures. With increasing amount of damage the transition from the low-temperature to bulk metal-type behavior (at T_c) shifts downwards. With increasing damage % the density of the quasi-1D clustered metal phase increases and the spin relaxation time of the conduction electrons increases, because they move unaffected over larger distances. On the other hand the mean free path of the conduc-

tion electrons in the precipitates is considerably smaller than for bulk Na, because for the most heavily damaged samples (with more than 20 at % Na) we have observed a minimum value for the line width equal to about 11 Gauss, which should be compared with 7 Gauss for bulk Na. Obviously, the conduction electrons are scattered by the interface between the precipitates and the host crystal. Below T_c the line width increases significantly with decreasing T , which is probably due to localization of the unpaired electrons within the Na nano-particles. At the same time the intensity of the conduction electron spin resonance (CESR) line decreases by about a factor 2!

Fig. 2 CESR line in irradiated NaCl, measured at room temperature. The samples were irradiated at 100 °C. The irradiation doses are indicated.

Fig. 3 The intensity and width of the ESR line of Na-precipitates in ultra-heavily irradiated NaCl. Below T_c (≈ 110 K) the signal behaves anomalously, above T_c it behaves approximately like in a normal metal.

Fig. 4 Orientation relationship for Cl_2 -NaCl system. Knots of the Cl_2 and NaCl crystal lattice are shown.

2.3 X-ray diffraction Recently, heavily damaged NaCl crystals have been studied by means of WAXS and intriguing results were obtained for Na colloids and the NaCl matrix [9]. WAXS shows that (i) the ultra-heavily irradiated NaCl crystal is quite perfect and (ii) in contrast with the above-mentioned studies Na-precipitates of 140–340 Å are formed. In this study we have obtained the size of Na and Cl_2 precipitates in samples with > 20% damage by line broadening. The size increases with increasing damage. A full account of the calculation of the size and shape of the Cl_2 precipitates ($Cmca$) at $T=95\text{K}$ will be published [10]. For both precipitates strict orientation relationships (OR) with respect to the NaCl matrix are found. In addition to the earlier established Kurdjumov-Sachs OR for Na colloids, we found the OR for Cl_2 : $\{001\}_{\text{Cl}_2} // \{001\}_{\text{NaCl}}$, $\langle 110 \rangle_{\text{Cl}_2} // \langle 110 \rangle_{\text{NaCl}}$ (Fig. 4). Here we show results for Na and Cl_2 precipitates in a NaCl sample, irradiated to 1 TRad at 100 °C. Figure 5 presents reflections from Na and Cl_2 precipitates and the instrumental resolution function (IRF). The reflection lines represent averaged intensities from the precipitates, which may show distributions of shapes and sizes. There are 24 (maximum for the $m\bar{3}m$ NaCl point group) transformation matrices (TM) for the Na OR [9] and 12 independent matrices for the Cl_2 OR. Both 110 Na (among possible reflections for total multiplicity

are shown in Figure 5. The reflection lines represent averaged intensities from the precipitates, which may show distributions of shapes and sizes. There are 24 (maximum for the $m\bar{3}m$ NaCl point group) transformation matrices (TM) for the Na OR [9] and 12 independent matrices for the Cl_2 OR. Both 110 Na (among possible reflections for total multiplicity

factor 12x24) and 200 Cl₂ reflections (2x12, respectively) were chosen for different TM so, that the Cl₂ reflections correspond to perpendicular directions in the NaCl crystal and the Na reflections are close to perpendicular. It is seen that the line shape does not depend on the direction in the host crystal. For the samples studied the 002 Cl₂ peaks are at least twice wider than the 200 Cl₂ peaks at close Bragg angles. This can be explained by a reduction of the precipitate size along the *c*-axis. We were not able to register wider angles and we have not observed reflections with at least double indices to reliably separate the size and strain contributions to line broadening. The average size of the Na particles in spherical approximation is 580 Å while the ellipsoid model gives for the chlorine bubbles 460 and 1070 Å along the *c*- and *a*-axis, respectively.

Fig. 5 110-peaks from Na-precipitates (left) and 200 peaks of Cl₂-precipitates (right) corresponding to different point symmetry matrices of the host *fcc* crystal (see text) and the IRF. The NaCl sample contains 16% Na and Cl₂.

3 Concluding remarks Depending on the irradiation conditions and the dose, nanoparticles of Na of 200-700 Å and molecular Cl₂ of 200-1000 Å are present in NaCl. With increasing damage%, the average precipitate size increases.

Cl₂ precipitates show the following OR: {001}_{Cl} // {001}_{NaCl}, <110>_{Cl} // <110>_{NaCl}; the broadening of the Bragg peaks is anisotropic. It depends on the reflection (hkl) indices. The shape of the precipitates cannot be described fully by existing ellipsoid models, although these models have certain relevance. The Bragg peaks of the host NaCl crystal do not show notable broadening up to highest radiation doses, implying that the crystal structure is quite perfect. The results in this paper provide interesting information about the structure of the precipitate systems. The information obtained by WAXS is complementary to that obtained with DSC, ESR, nuclear magnetic resonance (NMR), and Raman scattering, which probe the local structure of the precipitates. The combined results show that the nano-particles, which obey strict orientation relationships, form large blocks with exactly the same alignment.

Acknowledgements The work was partly financed by NATO grant CLG 980994, RFFI grant N04-02-16150, NWO grant B-67-327, and State contr. N02.438.11.7051 FCNTP I.M.

References

- [1] D. I. Vainshtein, H. P. den Hartog, H. C. Datema, J. Seinen, and H. W. den Hartog, *Radiat. Eff. Defects Solids* **137**, 73 (1995).
- [2] D. I. Vainshtein and H.W. den Hartog, *Appl. Radiat. Isot.* **47**, 1503 (1996).
- [3] F. G. Cherkasov, R. G. Mustafin, S. G. L'vov, R. I. Khaibullin, H.W. den Hartog, D. I. Vainshtein, and A. Y. Vitol, *Vacuum* **51**, 239 (1998).
- [4] F. G. Cherkasov, S. G. L'vov, D. A. Tikhonov, H. W. den Hartog, and D. I. Vainshtein, *J. Phys.: Condens. Matter* **14**, 7311 (2002).

- [5] E. I. Shtyrkov, A. Klimovitskii, H. W. den Hartog, and D. I. Vainshtein, *J. Phys.: Condens. Matter* **14**, 9053 (2002).
- [6] G. Faraci, A. R. Pennisi, and J.-L. Hazemann, *Phys. Rev. B* **56**, 12553 (1997).
- [7] C. Faivre, D. Bellet, and G. Dolino, *Eur. Phys. J. B* **7**, 19 (1999).
- [8] J. Seinen, D. I. Vainshtein, H. C. Datema, and H. W. den Hartog, *J. Phys.: Condens. Matter* **7**, 705 (1995).
- [9] S. N. Sulyanov, D. M. Kheiker, D. I. Vainshtein, and H. W. den Hartog, *Solid State Commun.* **128**(11), 419 (2003).
- [10] S. N. Sulyanov, D. M. Kheiker, P. V. Dorovatovskii, A. V. Sugonyako, D. I. Vainshtein, and H. W. den Hartog, to be published (2006).