University of Groningen

Synthesis of C-59(CHPh(2))N from (C59N)(2) and C59HN. The first derivatization of C59N

Bellavia-Lund, C.; Gonzalez, R.; Hummelen, J.C.; Hicks, R.G.; Sastre, A.; Wudl, F.

Published in:
Journal of the American Chemical Society

DOI:
[10.1021/ja964447c](https://doi.org/10.1021/ja964447c)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
1997

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Bellavia-Lund, C., Gonzalez, R., Hummelen, J. C., Hicks, R. G., Sastre, A., & Wudl, F. (1997). Synthesis of C-59(CHPh(2))N from (C59N)(2) and C59HN. The first derivatization of C59N. *Journal of the American Chemical Society*, 119(12), 2946 - 2947. <https://doi.org/10.1021/ja964447c>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Synthesis of C₅₉(CHPh₂)N from (C₅₉N)₂ and C₅₉HN. The First Derivatization of C₅₉N

Cheryl Bellavia-Lund, Rosario González,
Jan Cornelis Hummelen, Robin G. Hicks, Angela Sastre, and
Fred Wudl*

*Institute for Polymers and Organic Solids
Departments of Chemistry and Materials
University of California
Santa Barbara, California 93106-5090*

Received December 30, 1996

Since the incorporation of heteroatoms into the fullerene skeleton is expected to modify its structural and electronic properties,¹ we prepared the first heterofullerene, "C₅₉N", which was isolated as its dimer, (C₅₉N)₂.² The isolation in the condensed phase of this nitrogen-substituted fullerene allows for the investigation of the chemical reactivity, physical properties,^{3,4} and possible applications of this new class of fullerenes. As part of our continued interest in the azafullerenes, we have initiated studies to prepare derivatives. Even though ¹⁵N-labeling experiments⁵ and the isolation and full characterization of C₅₉HN have given us confidence that the starred carbons (see eq 1, below) are sp³ hybridized, a principal reason for derivatization of C₅₉N was to glean information on the variability of the chemical shift of the carbon atoms in question as a function of substitution.

Two possible processes for derivatization of C₅₉N are (1) deprotonation of the azafullerene C₅₉HN⁶ followed by attack of an electrophile and (2) homolytic dissociation of the interdimer bond of (C₅₉N)₂ followed by free radical reactions. Here, we report on the derivatization of azafullerene via homolysis of its dimer.

According to theoretical calculations⁷ the interdimer bond of (C₅₉N)₂ is relatively weak (18 kcal/mol) and should, under photolysis or thermolysis conditions, undergo facile homolysis. In the presence of a good hydrogen atom donor or radical source,

the resulting azafullerenyl radical is expected to undergo free radical reactions.

Treatment of (C₅₉N)₂ with excess diphenylmethane in refluxing *o*-dichlorobenzene (ODCB) for 48 h afforded, upon chromatography (silica gel, toluene), a crude product. HPLC analysis indicated one major constituent, consisting of 71 % of the isolable mixture. This was shown to be the substituted azafullerene C₅₉(CHPh₂)N (**2**) by ¹H and ¹³C NMR, FTIR, UV-vis, mass spectrometry, and cyclic voltammetry. The heterofullerene **2** was obtained in 42% isolated yield after purification by HPLC on a Cosmosil Buckyprep semiprep column.⁸

The ¹H NMR spectrum of **2** showed signals corresponding to two equivalent phenyl groups and a singlet corresponding to the methine hydrogen at 6.09 ppm. The 34 lines observed between 156 and 124 ppm (30 from the C₅₉N moiety and 4 from the phenyl groups) in the ¹³C NMR spectrum are consistent with the expected C_s symmetry of **2** depicted in eq 1. Another peak at 65.2 ppm corresponds to the methine carbon atom and a signal at 86.3 ppm must be due to the starred sp³ carbon atom on the buckyball moiety. This carbon resonance is downfield shifted by 14 ppm relative to the sp³ carbon of C₅₉HN,⁶ as expected on going from hydrogen to alkyl substitution. This is in agreement with a "closed" structure in which the sp³ carbon atom is bound to the nitrogen atom and the CHPh₂ substituent, as shown in **2** above.

While the NOE effect identifies most of the phenyl resonances in the ¹³C NMR spectrum, proton-coupled ¹³C NMR distinguishes the resonance of the quaternary carbon of the phenyl group (quartet at 139 ppm) from the surrounding fullerene resonances. The coupled spectrum also supports the assignment of the methine carbon, revealing a doublet at 65.2 (¹J_{CH} = 127 Hz) and a *b*-coupled doublet at 86.7 (²J_{CH} = 5 Hz) for the sp³ carbon of the fullerene cage. Finally, positive ion electrospray MS shows a molecular ion at *m/z* = 889 and a strong peak at *m/z* = 722 corresponding to C₅₉N⁺.

The UV-vis absorption of C₅₉(Ph₂CH)N is almost identical to that of (C₅₉N)₂ and C₅₉HN showing a broad band in the visible at 448 nm; all three compounds are green in solution. The similarities of the electronic spectra of the azafullerenes supports the closed structure assigned to (C₅₉N)₂⁶ depicted for **1**, above.

The FTIR spectrum shows a typical pattern for a fullerene derivative, in particular having absorptions similar to C₅₉HN in the fingerprint region (480-590 cm⁻¹), where the strongest peak is at 529.3 cm⁻¹.

The diphenylmethane adduct of C₅₉N exhibits two quasi-reversible one-electron reduction waves; a third wave, which is completely irreversible was also observed. This contrasts the behavior of C₅₉HN in which the reduction processes are chemically irreversible. We interpreted the properties of the latter as arising from facile hydrogen atom loss on reduction, which is not possible in the diphenylmethane derivative. The reduction potentials are presented in Table 1, along with those of C₆₀, (C₅₉N)₂, and C₅₉HN for comparison. The potentials of the (diphenylmethyl)azafullerene and hydroazafullerene are comparable, and both are significantly more difficult to reduce than the dimer, an observation consistent with the high electronegativity of a heterofullerene "substituent". All of the azafullerene compounds possess irreversible oxidation waves at much lower potentials compared to those of C₆₀.

(8) (Ph₂CH)C₅₉N: Diphenylmethane (2.4 mL) was added to a degassed solution of (C₅₉N)₂ (30 mg) in HPLC grade 1,2-dichlorobenzene (25 mL). The mixture was refluxed under argon for 48 h and chromatographed on silica gel using toluene as eluent. The product was purified by HPLC using a semipreparative Cosmosil Buckyprep column (30% hexane in toluene, 5 mL/min, UV/326 nm). Solvents were removed under vacuum, and the product was washed with ether, centrifuged, and decanted three times to remove ether-soluble components, including toluene. It was finally dried under vacuum. Yield: 15 mg (42%). Please refer to Supporting Information for spectroscopic data.

(1) Andreoni, W.; Gygi, F.; Parrinello, M. *Chem. Phys. Lett.* **1992**, *190*, 159.

(2) Hummelen, J. C.; Knight, B.; Pavlovich, J.; González, R.; Wudl, F. *Science* **1995**, *269*, 1554. For C₅₉N in the gas phase, see: Averdung, J.; Luftmann, H.; Schlachter, I.; Mattay, J. *Tetrahedron* **1995**, *51*, 697. Lamparth, I.; Nuber, B.; Schick, A.; Skiebe, T.; Grosser, T.; Hirsch, A. *Angew. Chem., Int. Ed. Engl.* **1995**, *35*, 2257-2258. Another condensed phase approach was recently disclosed: Nuber, B.; Hirsch, A. *J. Chem. Soc., Chem. Commun.* **1996**, 1421.

(3) Prassides, K.; Keshavarz-K., M.; Hummelen, J. C.; Andreoni, W.; Giannozzi, P.; Beer, E.; Bellavia, C.; Cristofolini, L.; Gonzalez, R.; Lappas, A.; Murata, Y.; Malecki, M.; Srdanov, V. I.; Wudl, F. *Science* **1996**, *271*, 1833.

(4) Brown, C. M.; Cristofolini, L.; Kordatos, K.; Prassides, K.; Bellavia, C.; González, R.; Cheetham, A. K.; Zhang, J. P.; Andreoni, W.; Curioni, A.; Fitch, A. N.; Pattison, P. *Chem. Mater.* **1996**, *8*, 2548-2550.

(5) Bellavia-Lund, C.; Keshavarz-K., M.; González, R.; Hummelen, J.-C.; Hicks, R.; Wudl, F. *Phosphorus, Sulfur Silicon Relat. Elem.* **1997**, in press.

(6) Keshavarz-K., M.; González, M.; Hicks, R. G.; Srdanov, G.; Srdanov, V. I.; Collins, T. A.; Hummelen, J. C.; Bellavia-Lund, C.; Pavlovich, J.; Wudl, F. *Nature* **1996**, *383*, 147-150.

(7) Andreoni, W.; Curioni, A.; Holczer, K.; Prassides, K.; Keshavarz-K., M.; Hummelen, J.-C.; Wudl, F. *J. Am. Chem. Soc.* **1996**, *118*, 11335-11336.

Table 1. Redox Potentials for C₆₀ and some C₅₉N Derivatives^a

	C ₆₀	(C ₅₉ N) ₂	C ₅₉ NH	C ₅₉ N(CHPh ₂)
<i>E</i> ₁ ^{red}	-1123	-992 -1071	-1106 ^b	-1082
<i>E</i> ₂ ^{red}	-1450	-1424 -1485	-1500 ^b	-1470
<i>E</i> ₃ ^{red}	-1913	-1979 -2089		
<i>E</i> ^{ox}	+1300 ^{b,c} +1260 ^d	+886 ^b	+823 ^b	+867 ^b

^a All potentials are in mV vs Ferrocene, in ODCB unless stated otherwise. ^b Chemically irreversible. ^c Dubois, D.; Kadish, K. *J. Am. Chem. Soc.* **1991**, *113*, 7773. ^d Chemically reversible, in 1,1,2,2-tetrachloroethane solvent: Xie, Q.; Arias, F.; Echegoyen, L. *J. Am. Chem. Soc.* **1993**, *115*, 9818.

We can attribute the mechanism of formation of **2** to be a short free radical chain. As illustrated in eq 2, the initiation step is proposed to be the homolysis of the azafullerene dimer to C₅₉N[•]

Subsequently, the steps in eqs 3a and 3b are plausible propagation and termination steps. Hence, in the presence of the hydrogen donor diphenylmethane, formation of C₅₉NH was expected to be one of the major products (eq 3a); however, it was only 2% of the reaction mixture. The major product was the diphenylmethane derivative of the azafullerene radical, **2**, (eq 3b).

Two possible reasons for the low yield of C₅₉NH are (1) unlike **2**, which appears to be quite stable under the “harsh” reaction conditions, C₅₉NH decomposes or polymerizes to yield insoluble products or (2) C₅₉NH undergoes a free radical reaction to afford C₅₉N[•] (eq 4). In eq 4, “In” under the arrow

could be an adventitious initiator or C₅₉N[•] from (C₅₉N)₂ (see eq 5, below).

In a control experiment, treatment of C₅₉NH⁶ with diphenylmethane in refluxing ODCB for 24 h, afforded, upon chromatography (silica gel, toluene), one isolable band, HPLC analysis of the crude product revealed the presence of **2** (73%), (C₅₉N)₂ (7%), and unreacted C₅₉NH (5%). This experiment proves that equation 4 is operative and that In[•] is due to a combination of eqs 5 and 2.

In support of the above dimerization, fresh, HPLC single component samples of C₅₉NH were found to dimerize on standing at room temperature even in the solid state.

We have demonstrated above the relatively clean conversion of (C₅₉N)₂ to a stable, soluble derivative in good yield. This study shows that C₅₉NH can also undergo homolytic cleavage to yield the C₅₉N radical, where all three species C₅₉N[•], C₅₉NH, and (C₅₉N)₂ are involved in the process leading to **2**. Full characterization of the title molecule shows remarkable similarities to (C₅₉N)₂ and C₅₉NH, and in particular the UV-vis data demonstrate that the electronic structure of all three molecules is essentially identical. The ¹³C NMR spectra reveal a similar pattern in the sp² region of **2** to that of its precursors and an unmistakable sp³ carbon at 86.1 ppm, illustrating the chemical shift deviation as a result of substitution; an important stepping stone for the absolute determination of the (C₅₉N)₂ structure. Research is currently in progress utilizing this methodology to derive azafullerenes with unusual properties.

Acknowledgment. We thank the National Science Foundation for support through the Materials Research Laboratory and NSF DMR 95-00888, as well as individual investigator grants. R.G. and A.S. thank the Ministerio de Educación y Cultura (Spain) for postdoctoral fellowships. R.G.H. thanks the National Research Council of Canada for a postdoctoral fellowship.

Supporting Information Available: Experimental details for the preparation, purification, and characterization of **2** (6 pages). See any current masthead page for ordering and Internet access instructions.

JA964447C

(9) Bellavia-Lund, C.; Collins, T.; Wudl, F. Submitted.