University of Groningen

A high-frequency light-induced electron spin resonance study of conjugated polymer/fullerene composites

De Ceuster, J.; Goovaerts, E.; Bouwen, A.; Dyakonov, V.; Hummelen, J.C.

Published in:
 Synthetic Metals

DOI:
[10.1016/S0379-6779\(01\)00437-4](https://doi.org/10.1016/S0379-6779(01)00437-4)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
 Publisher's PDF, also known as Version of record

Publication date:
 2001

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

De Ceuster, J., Goovaerts, E., Bouwen, A., Dyakonov, V., & Hummelen, J. C. (2001). A high-frequency light-induced electron spin resonance study of conjugated polymer/fullerene composites. *Synthetic Metals*, 124(1), 99 - 101. [https://doi.org/10.1016/S0379-6779\(01\)00437-4](https://doi.org/10.1016/S0379-6779(01)00437-4)

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

A high-frequency light-induced electron spin resonance study of conjugated polymer/fullerene composites

J. De Ceuster^{a,*}, E. Goovaerts^a, A. Bouwen^a, V. Dyakonov^b, J.C. Hummelen^c

^aDepartment of Physics, University of Antwerp, Universiteitsplein 1, B-2610 Antwerpen, Belgium

^bEnergy and Semiconductor Research, University of Oldenburg, Carl von Ossietzky Str. 9, D-26121 Oldenburg, Germany

^cStratingh Institute and MSC, University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands

Abstract

Light-induced electron spin resonance (LESR) measurements are reported in composites of MDMO-PPV and PCBM, a soluble derivative of C₆₀. After illumination of the sample, two radicals are formed. One is the remaining positive polaron P⁺ on the polymer backbone and the other the C₆₁^{•−} radical anion. Using high-frequency (95 GHz) LESR, it was possible to separate these two contributions to the spectrum on the basis of their *g*-parameters, and to resolve the *g*-anisotropy of the radicals. The P⁺-polaron possesses axial symmetry whereas for C₆₁^{•−} a lower, rhombic symmetry was observed. © 2001 Elsevier Science B.V. All rights reserved.

Keywords: Electron spin resonance; Radicals; Symmetry properties

1. Introduction

The interest in organic donor–acceptor heterojunctions is steadily growing due to their use in active layers of photovoltaic devices. The efficient generation of charge carriers in these materials and their fate after creation are important issues to be addressed. Many studies before already proved the fast (<1 ps) spatial separation [1] of the charge carriers and the stability of the trapping centers.

This paper presents light-induced electron spin resonance (LESR) measurements on composites of conjugated polymers and fullerenes, in which radicals are created by optical excitation in the cavity.

Electron spin resonance (ESR) is a proven technique for the investigation of radical formation. LESR measurements on composites of conjugated polymers and fullerenes were already performed in a conventional X-band (9.5 GHz) spectrometer [2]. The most important findings were the creation of two radicals: the positive polaron P⁺ on the polymer and the C₆₁^{•−} anion radical on the fullerene.

Their ESR lines were found to overlap in the X-band, and could be distinguished by the different linewidth and saturation behavior.

Furthermore, X-band LESR measurements demonstrated the stability of the trapping states at low temperatures. After

switching off the light, the intensity of the LESR lines decreased slightly. The dependency on the light intensity of both light-on and light-off revealed a bimolecular annihilation process.

High-frequency (HF)-LESR can lead to a better understanding of the physics on the molecular scale. On the other hand, HF-LESR can distinguish better between both contributions to the LESR spectrum which are only slightly separated in *g*-value in the X-band. Also it is possible to resolve small *g*-anisotropies of each of the features.

2. Materials and sample preparation

As a conjugated polymer we used poly[2-methoxy-5-(3',7'-dimethyloctyloxy)-1,4-phenylene vinylene], hereafter denoted by MDMO-PPV. The absorption and photoluminescence curves, measured at room temperature are shown in Fig. 1. As a comparison, the absorption curve at 77 K is also given. Notice the small red-shift, indicating a better conjugation at lower temperatures. The fullerene used in the study was [6,6]-phenyl-C₆₁-butyricacidmethylester or PCBM, a soluble derivative of C₆₀. Both components were dissolved separately in a 1 wt.% solution of dimethylbenzene (xylene) whereafter they were mixed together in a 1:1 concentration. As a final step, the samples were dried from solution in the ESR sample tubes.

The high-frequency ESR spectrometer operates in the W-band (95 GHz). It consists of a Bruker frequency mixing

* Corresponding author. Tel.: +32-3-8202451; fax: +32-3-8202470.
E-mail address: jandc@uia.ua.ac.be (J. De Ceuster).

Fig. 1. In the left figure, the photoluminescence and absorption spectra are shown of MDMO-PPV both at room temperature and at 77 K. The right figure shows the absorption spectrum of PCBM. Each of the molecular structures is given in the insets.

microwave source (9.5 GHz + 84 GHz), a Bruker cylindrical cavity and an Oxford 6T superconducting magnet. The low temperature measurements were performed in an Oxford flow cryostat.

The samples were illuminated with the 488 nm (≈ 2.5 eV) line of an Ar⁺ laser. The light was guided to the sample through an optical fiber.

3. W-band LESR spectrum

The first goal of the study was to separate in the spectrum the lines of both the P⁺ and the C₆₁^{•−} radical. In contrast with the X-band LESR, well separated spectral features can be observed in the W-band measurements. As shown in

Fig. 2, these features are attributed to the positive polaron P⁺ (labeled by $g_{\perp}$ and $g_{\parallel}$) and the C₆₁^{•−} radical (labeled by g_x , g_y and g_z).

The positive polaron P⁺ radical and the C₆₁^{•−} radical have a different saturation behavior. In the X-band, one made use of this property to distinguish between the different contributions in the spectrum. In the W-band, a “fast passage effect” [3] was observed on the P⁺-lines, resulting from saturation at higher microwave powers.

Furthermore, HF-LESR resolves the g -anisotropy of both features, revealing the symmetry of the radicals. The axial symmetry of the P⁺ indicates that this radical is most likely localized on the phenyl unit of the PPV structure.

The dependence of both contributions in the LESR spectrum from 100 to 160 K was measured. Both show a $1/T$

Fig. 2. LESR spectrum of the MDMO-PPV/PCBM composite, showing the fullerene radical (C₆₁^{•−}), and the positive polaron (P⁺). The thin lines are simulations. Weak spurious Mn²⁺ lines, originating from the cavity are indicated in the spectrum.

Fig. 3. Temperature dependence of both contributions in the spectrum. The sample was under continuous illumination.

behavior. The parameters of the linear fits in this interval demonstrate that there is not only the Curie law but also another contribution that induces a decrease in the LESR intensities upon increasing temperature. Most likely, this is a thermally activated bimolecular annihilation process (Fig. 3).

To examine the P^+ -polaron, one can deliberately create the radical by doping a sample of pure MDMO-PPV with iodine (I_2). The ESR spectrum, however, only reveals one single broader line (≈ 15 G in comparison with the 5 G fit of the linewidth in the axial powder spectrum). The presence of counter ions leads to broadening of the ESR lines so that the axial symmetry of the P^+ is no longer resolved. Finally, a longer exposure to I_2 leads to a further increase in the broadening of this ESR transition.

Acknowledgements

This work is supported by the Fund for Scientific Research, Flanders (FWO). J.D.C. acknowledges the financial support from the Flemish Government in the GOA project.

References

- [1] D. Vacar, E.S. Maniloff, D.W. McBranch, A.J. Heeger, *Phys. Rev. B* 56 (1997) 4573.
- [2] V. Dyakonov, G. Zorinants, M. Scharber, C.J. Brabec, R.A.J. Janssen, J.C. Hummelen, N.S. Sariciftci, *Phys. Rev. B* 59 (1999) 8019.
- [3] C. Mailer, C.P.S. Taylor, *Biochim. Biophys. Acta* 322 (1973) 195.