University of Groningen

Self-organized supermolecules based on conducting polyaniline and hydrogen bonded amphiphiles

Kosonen, H.; Ruokolainen, J.; Knaapila, M.; Torkkeli, M.; Serimaa, R.; Bras, W.; Monkman, A.P.; ten Brinke, G.; Ikkala, O.

Published in:
Synthetic Metals

DOI:
[10.1016/S0379-6779\(00\)01185-1](https://doi.org/10.1016/S0379-6779(00)01185-1)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2001

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Kosonen, H., Ruokolainen, J., Knaapila, M., Torkkeli, M., Serimaa, R., Bras, W., Monkman, A. P., ten Brinke, G., & Ikkala, O. (2001). Self-organized supermolecules based on conducting polyaniline and hydrogen bonded amphiphiles. *Synthetic Metals*, 121(1-3), 1277 - 1278. [https://doi.org/10.1016/S0379-6779\(00\)01185-1](https://doi.org/10.1016/S0379-6779(00)01185-1)

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Self-organized supermolecules based on conducting polyaniline and hydrogen bonded amphiphiles

H. Kosonen^{a*}, J. Ruokolainen^a, M. Knaapila^a, M. Torkkeli^b,
R. Serimaa^b, W. Bras^c, A. P. Monkman^d,
G. ten Brinke^{a,e}, and O. Ikkala^{a*}

^a Department of Engineering Physics and Mathematics, Helsinki University of Technology, P.O. Box 2200, FIN-02015 HUT, Espoo, Finland

^b Department of Physics, University of Helsinki, P.O. Box 9, FIN-00014 Helsinki, Finland

^c Netherlands Organisation for Scientific Research (NWO) DUBBLE CRG / ESRF, c/o BP 220 Grenoble F38043, France

^d Department of Physics, University of Durham, Durham DH1 3LE, UK

^e Department of Polymer Science and Materials Science Center, University of Groningen; Nijenborgh 4, 9747 AG Groningen, The Netherlands

Abstract

We describe a concept to achieve comb-like supermolecules by hydrogen bonding camphor sulphonic acid (CSA) doped polyaniline (PANI) to 4-Hexyl resorcinol (Hres). The supermolecules, in turn, self-organize to form cylindrical nanostructures with the distances of 35 Å between the cylinders. The self-organized structures show improved conductivity in the bulk.

Keywords: polyaniline and derivatives, self-organization in macromolecules, supermolecules, recognition

1. Introduction

Self-organization based on competing interactions allows nanoscale polymeric structures[1] with interesting functional or controllable properties[2,3]. A simple prototype is provided by diblock copolymers which form self-organized spherical, cylindrical, gyroid, and lamellar structures[4]. Hairy rods are comb copolymers which have rigid backbones and a dense set of repulsive side chains (such as alkyl tails) as covalently bonded to the backbone[5]. They form typically lamellar or cylindrical structures with a periodicity of 20–30 Å[5,6].

Supermolecules are moieties held together by molecularly matching physical bonds (recognition)[7]. To achieve comb-shape supermolecules, ionic interactions[8, 9], coordination[10], and hydrogen bonds[11,12] can be used to bond the repulsive side chains to the backbone in order to allow polymer-amphiphile supermolecules. Polyaniline, protonated with a strong acid[13] is known to form a conducting polymeric salt. Self-organized lamellar structure of conjugated polyaniline has been observed, using alkyl containing strong acid[14].

Our aim was to form supermolecules of conducting PANI-salts and amphiphiles with matching physical bonds

to allow conducting self-organized cylinders to achieve “molecular wires”.

Fig 1. Interactions between PANI, CSA and Hres, and formation of self-organized hexagonal cylindrical structure. The hydrogen bonds (h.b.) probably take place to the sulphonates and the amines (so far not known in detail).

* Corresponding author. Tel: +358-9-451 3154, Fax: +358-9-451 3164
E-mail: Olli.Ikkala@hut.fi

2. Results and Discussion

Highly conducting films of PANI(CSA)_{0.5} complexes can be cast from *m*-cresol solution[15]. Generally, a longer repulsive alkyl chain (than the methyl contained in *m*-cresol) would be needed to achieve self-organization[11]. However, increasing the alkyl chain length in phenols typically leads to macroscopic phase separation in the case of PANI(CSA)_{0.5}. In this work, another hydroxyl group is introduced to overcome this problem to promote hydrogen bonding capability and 4-Hexyl resorcinol (Hres) proves to have a feasible combination between the repulsion (alkyl tail) and the attraction (hydrogen bondings). In SAXS measurements, sharp peaks ($1q_l$, $\sqrt{3}q_l$ and $2q_l$) indicate that PANI(CSA)_{0.5}(Hres)_{*y*} supermolecules form a self-organized hexagonal cylindrical structure with the distances between the cylinders of ca. 35 Å (Fig. 2). Increasing the mole fraction of Hres, the distances increase from 34.7 Å to 36.8 Å.

PANI(CSA)_{0.5} cast from formic acid shows relatively poor conductivity (see Fig. 3) as formic acid is a worse solvent as *m*-cresol. Note that all samples have been cast from highly volatile formic acid instead of *m*-cresol as the latter solvent would have been difficult to remove completely from the samples containing also another phenol Hres. However, the conductivities of PANI(CSA)_{0.5}(Hres)_{*y*} supermolecules increase about two decades to 1 S/cm when a mole fraction of Hres is increased and the cylindrical structure is formed. A probable explanation is that the conformations of PANI(CSA)_{0.5} chains are more extended upon confinement in the cylinders.

Fig. 2. SAXS patterns of PANI(CSA)_{0.5}(Hres)_{*y*} supermolecules indicate that they form cylindrical self-organized structures. The shown data is taken at 105 °C, i.e. above the crystallization temperature of Hres. Qualitatively similar result is obtained at room temperature.

3. Conclusions

Electrically conducting polyaniline supermolecules have been constructed based on hydrogen bonding amphiphiles to allow self-organized cylinders ("nanowires"). Such self-organization increases the conductivity.

Fig. 3. DC-conductivity of PANI(CSA)_{0.5}(Hres)_{*y*} supermolecules as a function of a mole fraction of Hres. Disordered structure is obtained for *y*=0 and 0.25 whereas cylindrical self-organization for *y*=0.5, 1.0, 1.5 and 2.0.

Acknowledgements

The research is supported by Technology Development Centre of Finland (TEKES).

References

1. M. Muthukumar, C.K. Ober, E.L. Thomas, *Science*, 277 (1997) 1225.
2. M. Brehmer, G. Mao, C.K. Ober, R. Zentel, *Macromol. Symp.*, 117 (1997) 175.
3. J. Ruokolainen, R. Mäkinen, M. Torkkeli, R. Serimaa, T. Mäkelä, G. ten Brinke, O. Ikkala, *Science*, 280 (1998) 557.
4. F.S. Bates, G.H. Fredrickson, *Annu. Rev. Phys. Chem.*, 41 (1990) 525.
5. M. Ballauff, *Angew. Chem. Int. Ed. Engl.*, 28 (1989) 253.
6. T. Vahlenkamp, G. Wegner, *Makromol. Chem. Phys.*, 195 (1994) 1933.
7. J.-M. Lehn (1995) *Supramolecular Chemistry*. VCH, Weinheim
8. M. Antonietti, J. Conrad, A. Thünemann, *Macromolecules*, 27 (1994) 6007.
9. C.K. Ober, G. Wegner, *Adv. Mat.*, 9 (1997) 17.
10. J. Ruokolainen, J. Tanner, G. ten Brinke, O. Ikkala, M. Torkkeli, R. Serimaa, *Macromolecules*, 28 (1995) 7779.
11. J. Ruokolainen, G. ten Brinke, O. Ikkala, M. Torkkeli, R. Serimaa, *Macromolecules*, 29 (1996) 3409.
12. J. Ruokolainen, J. Tanner, O. Ikkala, G. ten Brinke, E.L. Thomas, *Macromolecules*, 31 (1998) 3532.
13. J.-C. Chiang, A.G. MacDiarmid, *Synth. Met.*, 13 (1986) 193.
14. W.-Y. Zheng, R.-H. Wang, K. Levon, Z.Y. Rong, T. Taka, W. Pan, *Makromol. Chem. Phys.*, 196 (1995) 2443.
15. Y. Cao, P. Smith, A.J. Heeger, *Synth. Met.*, 48 (1992) 91.