University of Groningen

Three-dimensional chiral skyrmions with attractive interparticle interactions

Leonov, A. O.; Monchesky, T. L.; Loudon, J. C.; Bogdanov, A. N.

Published in:
Journal of Physics-Condensed Matter

DOI:
[10.1088/0953-8984/28/35/35LT01](https://doi.org/10.1088/0953-8984/28/35/35LT01)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2016

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Leonov, A. O., Monchesky, T. L., Loudon, J. C., & Bogdanov, A. N. (2016). Three-dimensional chiral skyrmions with attractive interparticle interactions. *Journal of Physics-Condensed Matter*, 28(35), [ARTN 35LT01]. <https://doi.org/10.1088/0953-8984/28/35/35LT01>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

LETTER

Three-dimensional chiral skyrmions with attractive interparticle interactions

To cite this article: A O Leonov *et al* 2016 *J. Phys.: Condens. Matter* **28** 35LT01

View the [article online](#) for updates and enhancements.

Recent citations

- [Chiral solitons in monoaxial chiral magnets in tilted magnetic field](#)
Yusuke Masaki *et al*
- [Reciprocal space tomography of 3D skyrmion lattice order in a chiral magnet](#)
Shilei Zhang *et al*
- [Interaction of Individual Skyrmions in a Nanostructured Cubic Chiral Magnet](#)
Haifeng Du *et al*

IOP | ebooks™

Bringing you innovative digital publishing with leading voices to create your essential collection of books in STEM research.

Start exploring the collection - download the first chapter of every title for free.

Letter

Three-dimensional chiral skyrmions with attractive interparticle interactions

A O Leonov^{1,2,3}, T L Monchesky^{1,4}, J C Loudon⁴ and A N Bogdanov^{1,2}

¹ Center for Chiral Science, Hiroshima University, Higashi-Hiroshima, Hiroshima 739-8526, Japan

² IFW Dresden, Postfach 270016, D-01171 Dresden, Germany

³ Zernike Institute for Advanced Materials, University of Groningen, Groningen, 9700AB, The Netherlands

⁴ Department of Physics and Atmospheric Science, Dalhousie University, Halifax, Nova Scotia, B3H 3J5, Canada

⁵ Department of Materials Science and Metallurgy, 27 Charles Babbage Road, Cambridge, CB3 0FS, UK

E-mail: a.leonov@ifw-dresden.de

Received 10 January 2016, revised 11 April 2016

Accepted for publication 11 April 2016

Published 1 July 2016

Abstract

We introduce a new class of isolated three-dimensional skyrmion that can occur within the cone phase of chiral magnetic materials. These novel solitonic states consist of an axisymmetric core separated from the host phase by an asymmetric shell. These skyrmions attract one another. We derive regular solutions for isolated skyrmions arising in the cone phase of cubic helimagnets and investigate their bound states.

Keywords: skyrmions, chiral magnets, Dzyaloshinskii–Moriya interaction

(Some figures may appear in colour only in the online journal)

The *Dzyaloshinskii–Moriya* (DM) interaction in noncentrosymmetric magnets is a result of their crystallographic handedness [1] and is responsible for the formation of long-range modulations with a fixed sense of the magnetization rotation [1, 2] and the stabilization of two-dimensional axisymmetric localized structures called *skyrmions* [3, 4]. Long-range homochiral modulations (*helices*) were found several decades ago in the noncentrosymmetric cubic ferromagnet MnSi and since then, other cubic ferromagnets with B20 structures have been investigated intensively [5–7] as have other chiral magnetic materials [8, 9]. Isolated chiral skyrmions have been recently discovered in PdFe/Ir(111) nanolayers with induced DM interactions and strong easy-axis anisotropy [10, 11].

Chiral skyrmions are two-dimensional topological solitons with an axisymmetric structure localized in nanoscale cylindrical regions. They exist as ensembles of weakly repulsive particles in the *saturated* phase of noncentrosymmetric magnets [4, 13, 14] in which all the atomic spins are parallel to an applied magnetic field. In cubic helimagnets, below a certain

critical field, H_D , the saturated phase transforms into the chiral helical state with the propagation direction along the applied field called the *cone* phase [2]. Unlike the saturated phase, the boundary values imposed by the longitudinal modulations of the cone phase violate the rotational symmetry of the system, and are thus incompatible with the axisymmetric arrangement of skyrmions investigated in [4, 10, 11, 13]. Then, the question arises: ‘Are there any localized states compatible with the encompassing cone phase?’

In our report we address this compatibility problem and derive regular solutions for asymmetric skyrmions embedded in the cone phase. We demonstrate that unlike the repulsive axisymmetric skyrmions existing in the saturated states, chiral solitons in the cone phase have an attractive interskyrmion potential and form biskyrmion and multiskyrmion states.

We consider the standard model for magnetic states in cubic non-centrosymmetric ferromagnets [1, 2],

$$w = A (\mathbf{grad} \mathbf{m})^2 + D \mathbf{m} \cdot \mathbf{rot} \mathbf{m} - \mu_0 M \mathbf{m} \cdot \mathbf{H}, \quad (1)$$

where $\mathbf{m} = (\sin \theta \cos \psi; \sin \theta \sin \psi; \cos \theta)$ is the unity vector along the magnetization $\mathbf{M}$, A is the exchange stiffness constant, D is the Dzyaloshinskii–Moriya (DM) coupling energy, and $\mathbf{H}$ is the applied magnetic field.

Chiral modulations along the applied field with the period $L_D = 4\pi A/|D|$ correspond to the global minimum of the functional (1) below the critical field $\mu_0 H_D = D^2/(2AM)$. The equilibrium parameters for the cone phase are expressed in analytical form [2] as:

$$\theta_c = \arccos(H/H_D), \quad \psi_c = 2\pi z/L_D, \quad (2)$$

where z is the spatial variable along the applied field.

At $H = H_D$, the cone phase transforms into the saturated state with $\theta = 0$. Within the saturated phase ($H > H_D$), isolated chiral skyrmions are described by axisymmetric solutions of type

$$\theta = \theta(\rho), \quad \psi = \varphi + \pi/2, \quad (3)$$

that are homogeneous along the skyrmion axis z where $\mathbf{r} = (\rho \cos \varphi, \rho \sin \varphi, z)$ are cylindrical coordinates for the spatial variable [4]. The equilibrium solutions for $\theta(\rho)$ are derived from the Euler equation for the energy functional [4]

$$w_s(\theta) = A\mathcal{J}_0(\theta) + D\mathcal{I}_0(\theta) - \mu_0 M H \cos \theta, \\ \mathcal{J}_0(\theta) = \theta_\rho^2 + \frac{1}{\rho^2} \sin^2 \theta, \quad \mathcal{I}_0(\theta) = \theta_\rho + \frac{1}{\rho} \sin \theta \cos \theta, \quad (4)$$

with the boundary conditions $\theta(0) = \pi, \theta(\infty) = 0$.

Below the saturation field ($H < H_D$), the structure of two-dimensional skyrmions is imposed by the arrangement of the cone phase (2). These solutions should be periodic with period L_D along the z -axis and are confined by the following in-plane boundary conditions:

$$\theta_{\rho=0} = \pi, \quad \theta_{\rho=\infty} = \theta_c, \quad \psi_{\rho=\infty}(z) = \psi_c(z). \quad (5)$$

The solutions for $\theta(\rho, \varphi, z)$, $\psi(\rho, \varphi, z)$ are derived by the minimization of the energy functional (1):

$$w = A\mathcal{J}(\theta, \psi) + D\mathcal{I}(\theta, \psi) - \mu_0 M H \cos \theta, \quad (6)$$

with the boundary conditions (5), where the exchange ($\mathcal{J}$) and Dzyaloshinskii–Moriya ($\mathcal{I}$) energy functionals are

$$\mathcal{J}(\theta, \psi) = \theta_\rho^2 + \theta_z^2 + \frac{1}{\rho^2} \theta_\varphi^2 + \sin^2 \theta \left(\psi_\rho^2 + \psi_z^2 + \frac{1}{\rho^2} \psi_\varphi^2 \right), \\ \mathcal{I}(\theta, \psi) = \sin(\psi - \varphi) \left(\theta_\rho + \frac{1}{\rho} \sin \theta \cos \theta \psi_\varphi \right) + \sin^2 \theta \psi_z \\ + \cos(\psi - \varphi) \left(\frac{1}{\rho} \theta_\varphi + \sin \theta \cos \theta \psi_\rho \right). \quad (7)$$

To investigate the solutions for asymmetric skyrmions, we use the discretized version of equation (1):

$$w = J \sum_{\langle i,j \rangle} (\mathbf{S}_i \cdot \mathbf{S}_j) - \sum_i \mathbf{H} \cdot \mathbf{S}_i \\ - D \sum_i (\mathbf{S}_i \times \mathbf{S}_{i+\hat{x}} \cdot \hat{x} + \mathbf{S}_i \times \mathbf{S}_{i+\hat{y}} \cdot \hat{y} + \mathbf{S}_i \times \mathbf{S}_{i+\hat{z}} \cdot \hat{z}) \quad (8)$$

We consider classical spins of unit length on a three-dimensional cubic lattice. $\langle i, j \rangle$ denotes pairs of nearest-neighbor

Figure 1. Magnetic structure of an isolated skyrmion in the cone phase: calculated color plots of $m_z(x, y)$ in three layers with $\Delta\psi_c = 2\pi/3$. Details of the magnetization distribution are given in figure 2.

spins. The Dzyaloshinskii–Moriya constant D defines the period of modulated structures p via the following relation: $D/J = \tan(2\pi/p)$. Or vice versa, one chooses the period of the modulations for the computing procedures and defines the corresponding value of DM constant. In what follows, the Dzyaloshinskii–Moriya constant is set to $0.7265J$ which corresponds to one-dimensional modulations with a period of 10 lattice spacings in zero field [15]. We note that throughout this article we consider periodic boundary conditions in all three directions. The discrete model (8) is particularly useful when the continuum model becomes invalid for localized solutions with sizes of a few lattice constants [12, 16]. The model is also able to operate with smaller arrays of spins as compared with the continuum model. The size of our numerical grid is set to $100 \times 100 \times p$.

Numerical calculations for $H = 0.57H_D$ (figures 1 and 2) show the main features of asymmetric skyrmions. The entire structure of a skyrmion within the cone phase can be thought of as a stack of layers (figure 1) rotating around the z axis with period L_D . These specific solitonic states are characterized by three-dimensional chiral modulations: the cone modulations along their axis and a double-twist rotation in the perpendicular plane.

Figures 2(a)–(c) present the equilibrium structures within a layer with a fixed value of z . The function $m_z(\rho, \varphi)$ consists of a strongly localized axisymmetric core separated from the outer region with a fixed value of the magnetization $\mathbf{m}(\theta_c, \psi_c)$ (2) by a broad strongly asymmetric transitional region we call the *shell*.

The contour lines of equal m_z in figure 2(a) and magnetization profiles along the skyrmion diameter, $m_z(\xi)$ in figure 2(c), display the details of the shell. Note especially, that the magnetization profile along $\varphi = \psi_c + \pi/2$ reaches the value $\theta = 0$. In figure 2(a), this point is enclosed by crescent-shaped contours. The unit spheres in figure 2 (d) demonstrate the difference between the solution for axisymmetric skyrmions in the saturated phase (3) and those within the cone phase (5).

Figure 2. Numerical solutions for asymmetric skyrmions (5) for $H = 0.57H_D$: contour plots of $m_z(x, y)$ (a) and energy density $e(x, y)$ (b) in a xy plane with a fixed value of ψ_c (2); (c) magnetization profiles $\theta(r)$ for different values of φ in the xy layer with $\psi_c = 0$ (ξ is the spatial variable along lines with fixed values of φ); (d) trajectories of the magnetization vector $\mathbf{m}$ for axisymmetric skyrmions (4) (top) and for asymmetric localized solitons (5) along the line $\varphi = \psi_c + \pi/2$ (bottom).

Figure 3. Variation of the energy density along the skyrmion diameter, $e(\xi)$ (a). Reduced energy for the interaction between two asymmetric skyrmions, E_{int}/E_s , as a function of the distance between the skyrmion centers r calculated for different values of the applied field (b). Inset shows minimal values of E_{int} as a function of the applied field. Contour plot of $m_z(x, y)$ for bound asymmetric skyrmions at $H/H_D = 0.57$ (c).

The former are described by OO_1 lines connecting the skyrmion center with $\theta = \pi$ (O_1) and the point O corresponding to the system ‘vacuum’, $\theta = 0$. Solutions for skyrmions within the cone phase are described by the lines connecting the skyrmion center (O_1) with the point C corresponding to the cone phase (2). In figure 2 (d) we indicate the magnetization trajectory along $\varphi = \psi_c + \pi/2$ direction.

The radial skyrmion energy density $e(\rho) = (2\pi L_D)^{-1} \int_0^{L_D} dz \int_0^{2\pi} d\varphi w_s(\theta, \psi)$ with positive exponentially decaying asymptotics (figure 3(a)) implies the *attractive* interaction between the skyrmions in the cone phase. Note that axisymmetric skyrmions in the saturated state of chiral magnets have a repulsive interskyrmion potential [13, 14, 17]. In figure 3(b) the reduced interaction energy between two asymmetric skyrmions, E_{int}/E_s is plotted as a function of their separation distance for different values of the applied magnetic field ($E_s = \int_0^\infty e(\rho) \rho d\rho$ is the total equilibrium energy of an isolated asymmetric skyrmion). The Lennard–Jones type potential profiles $E_{\text{int}}/E_s(r/L_D)$ show that the attractive interskyrmion coupling is characterized by a low potential barrier and a rather deep potential well establishing the equilibrium separation of skyrmions in the bound biskyrmion state (figure 3(c)).

In conclusion, regular solutions for isolated chiral skyrmions in the cone phase of cubic helimagnets have been derived

by numerically solving the corresponding micromagnetic equations (5) and (6). These novel solitonic states are characterized by three-dimensional chiral modulations and an attractive interskyrmion potential. Similar skyrmionic states can arise in the cone phases admissible in uniaxial chiral ferromagnets with C_n and D_n symmetry [1, 3]. Axisymmetric skyrmions exist in the saturated phase of chiral ferromagnets as ensembles of repulsive isolated particles [4, 10, 14]. Our findings show that below the transition field into the cone phase, the axisymmetric skyrmions transform into asymmetric attractive solitons and may form biskyrmion and multi-skyrmion states (clusters).

To date, no direct observations of isolated skyrmions or skyrmion clusters have been reported in the cone phases of chiral helimagnets. However, a few isolated observations such as a decomposition of a skyrmion lattice into cluster-like patterns [18] and the formation of skyrmionic droplets in MnSi plates [19], are in accord with our theoretical results and indicate possible directions for the investigation of this phenomenon.

Acknowledgments

The authors are grateful to K Inoue, J Kishine, and G Tatara for useful discussions. AOL acknowledges financial support by the FOM grant 11PR2928. ANB acknowledges support

by the Deutsche Forschungsgemeinschaft via Grant No. BO 4160/1-1.

References

- [1] Dzyaloshinskii I E 1964 *Sov. Phys.—JETP* **19** 960
- [2] Bak P and Jensen M H 1980 *J. Phys. C: Solid State Phys.* **13** L881
- [3] Bogdanov A N and Yablonsky A D 1989 *Sov. Phys.—JETP* **68** 101
- [4] Bogdanov A and Hubert A 1994 *J. Magn. Magn. Mater.* **138** 255
- [5] Ishikawa Y, Tajima K, Bloch D and Roth M 1976 *Solid State Commun.* **19** 525
- [6] Beille J, Voiron J, Roth M and Zhang Z Y 1981 *J. Phys. F: Met. Phys.* **11** 2153
- [7] Lebech B, Bernhard J and Freltoft T 1989 *J. Phys.: Condens. Matter* **1** 6105
- [8] Togawa Y, Koyama T, Takayanagi K, Mori S, Kousaka Y, Akimitsu J, Nishihara S, Inoue K, Ovchinnikov A S and Kishine J I 2012 *Phys. Rev. Lett.* **108** 107202
- [9] Porter N A *et al* 2015 *Phys. Rev. B* **92** 144402
- [10] Romming N, Hanneken C, Menzel M, Bickel J E, Wolter B, von Bergmann K, Kubetzka A and Wiesendanger R 2013 *Science* **341** 636
- [11] Romming N, Kubetzka A, Hanneken C, von Bergmann K and Wiesendanger R 2015 *Phys. Rev. Lett.* **114** 177203
- [12] Leonov A O, Monchesky T L, Romming N, Kubetzka A, Bogdanov A N and Wiesendanger R 2015 *New J. Phys.* **18** 065003
- [13] Bogdanov A 1995 *JETP Lett.* **62** 247
- [14] Rößler U K, Leonov A A and Bogdanov A N 2011 *J. Phys.: Conf. Ser.* **303** 012105
- [15] Keesman R, Leonov A O, Buhrandt S, Barkema G T, Fritz L and Duine R A 2015 *Phys. Rev. B* **92** 134405
- [16] Leonov A O and Mostovoy M 2015 *Nat. Commun.* **6** 8275
- [17] Komineas S and Papanicolaou N 2015 *Phys. Rev. B* **92** 064412
- [18] Yu X Z, Onose Y, Kanazawa N, Park J H, Han J H, Matsui Y, Nagaosa N and Tokura Y 2010 *Nature* **465** 901
- [19] Grigoriev S V, Potapova N M, Moskvina E V, Dyadkin V A, Dewhurst Ch and Maleyev S V 2014 *JETP Lett.* **100** 216