University of Groningen

Spin accumulation probed in multiterminal lateral all-metallic devices

Costache, M. V.; Zaffalon, M.; van Wees, B. J.

Published in:
Physical Review. B: Condensed Matter and Materials Physics

DOI:
[10.1103/PhysRevB.74.012412](https://doi.org/10.1103/PhysRevB.74.012412)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2006

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Costache, M. V., Zaffalon, M., & van Wees, B. J. (2006). Spin accumulation probed in multiterminal lateral all-metallic devices. *Physical Review. B: Condensed Matter and Materials Physics*, 74(1), art. - 012412. [012412]. <https://doi.org/10.1103/PhysRevB.74.012412>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Spin accumulation probed in multiterminal lateral all-metallic devices

M. V. Costache,^{*} M. Zaffalon,[†] and B. J. van Wees

Department of Applied Physics and Materials Science Center, University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands

(Received 27 March 2006; revised manuscript received 1 June 2006; published 31 July 2006)

We study spin accumulation in an aluminium island, in which the injection of a spin current and the detection of the spin accumulation are done by means of four cobalt electrodes that connect to the island through transparent tunnel barriers. Although the four electrodes are designed as two electrode pairs of the same shape, they nonetheless all exhibit distinct switching fields. As a result the device can have several different magnetic configurations. From the measurements of the amplitude of the spin accumulation, we can identify these configurations, and using the diffusion equation for the spin imbalance, we extract the spin relaxation length $\lambda_{sf}=400\pm50$ nm and an interface spin current polarization $P=(10\pm1)\%$ at low temperature and $\lambda_{sf}=350\pm50$ nm, $P=(8\pm1)\%$ at room temperature.

DOI: [10.1103/PhysRevB.74.012412](https://doi.org/10.1103/PhysRevB.74.012412)

PACS number(s): 72.25.Ba, 72.25.Hg, 73.23.-b, 85.75.-d

It is an interesting question what happens to the transport properties in nonmagnetic conductors if the carriers are spin polarized. This is both a fundamental question in the field of spintronics and has also practical applications.¹ In an all-electrical setup, spin polarized carriers are injected by driving a current from a ferromagnet. This induces an imbalance between the two spin populations, that, for diffusive systems, extends over a distance of order $\lambda_{sf}=\sqrt{D\tau_{sf}}$ from the interface. τ_{sf} is the spin lifetime and D the electron diffusion constant for the conductor. If a second ferromagnet is present within λ_{sf} from the injector, it can be used to detect the spin accumulation.

In order to study spin related transport in a nonmagnetic metal using a lateral device, a true multiterminal device is needed. By spatially separating the current path from the voltage probes, one can distinguish between truly spin-related effects and spurious, interface-dependent phenomena.

This technique, pioneered by Johnson and Silsbee,² has been successfully extended to the study of spin transport in diverse systems, from metallic systems at low and room temperature³⁻⁷ to carbon nanotubes,⁸ and to a lesser extent, in semiconductors,⁹ superconductors¹⁰ and organic materials.¹¹ In the case of metallic systems, the interface between the ferromagnet and the metal has been varied from transparent to tunneling. Valenzuela *et al.*¹² have used a lateral spin valve device to probe the magnitude and sign of the polarization of a ferromagnetic contact as a function of the injecting bias voltage.

Recently, the spin accumulation in a diffusive Al island, with all lateral dimensions smaller than λ_{sf} has been studied.¹³ The island is contacted by four Co electrodes via tunnel barriers for injection and/or detection of the spin accumulation. However, this system suffers from several drawbacks such as difficulty of fabrication and, more importantly, large magnetic fringing fields at the end of the electrodes, which can affect the spin accumulation. Also it is not straightforward to reduce the island's volume to increase the spin accumulation.

In this work, we focus on a one-dimensional (1D) system (only one lateral dimension larger than λ_{sf}) in which an Al island is contacted with four in-line Co electrodes, as shown in Fig. 1.

The orientation of the electrodes' magnetization is pinned along the electrode axis in the substrate plane by the shape anisotropy and can be switched by an external magnetic field in the $\hat{y}$ direction. The inner and/or outer electrode pairs are designed to have different widths.

As the switching field is lower for the wider (outer) electrodes, we have a control on the magnetization of the individual electrodes. However, we will see that the switching fields for identically designed Co electrodes may not be the same. This is due to the small differences produced during the fabrication and to magnetic interactions between the electrodes ends.

Here, we study the spin accumulation as a result of the different orientations of the four Co electrodes and we show how, from the magnitude of the spin accumulation, we can infer the magnetic configuration of the electrodes, as well as the polarization of the Co/Al₂O₃/Al contacts and the spin diffusion length λ_{sf} in Al.

FIG. 1. Scanning electron microscope (SEM) image of the device. Visible are the Al island and the four Co contacts of two different widths: the wider electrodes connecting the island at its ends, have a lower switching field. In the nonlocal measuring configuration, a current I is injected from Co2 to Co3 and the voltage difference $V=V^+-V^-$ is detected between Co3 and Co4. All measurements presented in this paper are taken in the nonlocal configuration.

The theoretical analysis of the spin imbalance in our Al strip is based on the model for diffusive transport introduced by van Son *et al.*,¹⁴ Johnson and Silsbee¹⁵ and refined by Valet and Fert.¹⁶ There transport was analyzed for transparent ferromagnetic and/or nonmagnetic (FM/N) interfaces. It was later understood¹⁷ that the efficiency of the injection, i.e., the ratio spin polarized current to total current, can be increased by interposing a spin dependent interface between FM and N, such as a high resistance tunnel barrier.

The devices (see Fig. 1) are made by electron beam lithography and two-angle shadow mask evaporation process. The shadow mask consists of a PMMA-MA/germanium/PMMA trilayer, the base resist having higher sensitivities than the top resist as to enable, by selective exposure, the making of a suspended mask with large undercuts. First, we deposit through the suspended mask 20 nm thick Al at 35° on the Si/SiO₂ substrate using electron-gun evaporation to form 1 $\mu\text{m} \times 150$ nm strip. Next, we expose Al to pure oxygen at a pressure of 10^{-2} mbar for a few minutes to form a thin Al₂O₃ layer. In the last step, four Co electrodes 30 nm thick are deposited perpendicular to contact the Al strip, without breaking the vacuum. The resistance of the Al/Al₂O₃/Co tunnel junctions ranges from 20–60 $\Omega \mu\text{m}^2$, depending on the oxidation time.

As mentioned above, the inner and/or outer Co electrodes have been designed to have different widths, with the outer contacts at 150 nm and the inner ones at 80 nm. This allows us to independently flip the magnetization direction of the electrodes, when an external magnetic field is slowly swept (≈ 1 –2 mT/s), along the contacts' direction. Nevertheless, we will present measurements in which sometimes the narrow contacts switch at lower fields than the wider ones.

Measurements were performed at about 2 K and at room temperature by standard ac lock-in techniques, with a modulation frequency of 7–17 Hz. We have measured five devices in detail.

All measurements presented here are taken in the *nonlocal* measuring configuration: a current I is injected from Co2 to Co1 and a voltage V is detected between Co3 and Co4. Since no charge current flows through the voltage detectors, our device is not sensitive to interface or bulk magnetoresistance related effects, but only to the spin degree of freedom.

Figure 2 shows two typical nonlocal spin valve measurements for different devices at low temperature. The plotted signal is $(V^+ - V^-)/I$, as a function of the in-plane (in the $\hat{y}$ direction) magnetic field. Referring to Fig. 2(a) device A, at +200 mT, all contacts' magnetization are aligned parallel to the external magnetic field, in the $+\hat{y}$ direction. We sweep the magnetic field toward negative values. At -80 mT, the two larger electrodes, namely Co1 and Co4, flip their magnetization (antiparallel configuration), and the detected signal increase to 90 m Ω above a zero background. Upon increasing the magnetic field further to -120 mT, the two smaller electrodes, Co2 and Co3, flip, the magnetization of the four contacts is parallel again, but now in the opposite direction ($-\hat{y}$). The reverse trace shows a similar behavior. Also for repeated sweeps, the field at which the magnetization switching occurs is within 20 mT of the given values.

Now, what happens if all four Co electrodes switch their magnetization at different fields? Figure 2(b) shows such a

FIG. 2. Nonlocal spin valve measurement: the transresistance V/I as a function of the in-plane magnetic field for positive and negative sweep direction. (a) Device A, two switch traces of the cobalt electrodes and (b) Device B, four switch traces, at low temperature (2 K).

measurement for device B. We interpret the additional steps in the signal as the fingerprint of different magnetic configurations of the electrodes. Again, at -170 mT, we start with a parallel configuration of the Co electrodes and with a background level of +70 m Ω (the nature of which is unknown). Ramping the field to positive values, at +75 mT, Co1 flips, the injectors are antiparallel and the signal increases above the background level by +17 m Ω . At +90 mT the other largest electrode, Co4, reverses, so that also the detectors are antiparallel to each other. The spin signal increases now by +90 m Ω above the background level. At 106 mT, Co3 strip flips, the detectors return to parallel and the signal drops by 20 m Ω below the background level. The electrodes stay in this configuration until reaching a field of +120 mT, when the other smallest electrode, Co2, switches and the signal reaches the background level. The sweep to negative fields shows a similar behavior, with a difference in the value of the spin signal, probably due to the presence of the magnetic domains in the Co strips.

It is worth mentioning at this point that, given the symmetric positions of the electrodes on the island, one cannot tell whether the electrode flipping at the lowest field, for example, in Fig. 2(b), is Co1 or Co4. This uncertainty could have been avoided, for instance if the electrodes were arranged in a wide, narrow, wide, narrow fashion (and if the switching field is determined by the lateral dimension of the electrode only).

Figure 3 top panel shows data for device C measured at room temperature. The behavior is similar to that of device B. The spin signal of 6–7 m Ω is smaller due to a lower spin relaxation length, and a somewhat smaller interface polarization at room temperature. For both positive and negative sweep directions of the magnetic field, we identify five magnetic configurations, a , b , $c+$, $c-$, and d .

To clearly illustrate the spin contributions in different

FIG. 3. (Top) Experimental data (dots) and fitting results (lines) using Eq. (1) for nonlocal spin valve at room temperature, device C. The letters *a* to *d* represent the different magnetic configurations as described below. (Bottom) Spatial dependence of $\mu_{\uparrow}$ and $\mu_{\downarrow}$ electrochemical potentials in the Al island for the magnetic configurations *a* to *d*, as in the top panel. The filled (open) dots indicate the potential measured by the V^+ and V^- probes.

magnetic configurations, we refer to Fig. 3 (bottom). Here we show schematically the spatial dependence of the spin-up ($\mu_{\uparrow}$) and spin-down ($\mu_{\downarrow}$) chemical potentials in the Al island, for the different magnetic configurations, when a charge current is injected from I^+ to I^- . V^+ and V^- represent the position of the voltage probes. Let us assume, for the moment, the contacts to be 100% spin polarized: V^+ , V^- would detect either $\mu_{\uparrow}$ or $\mu_{\downarrow}$, according to the magnetization direction of the contact.

In the configuration *a* in which all contacts are parallel, and the spin related signal arises from the spatial dependence of $\mu_{\downarrow}(x)$.

When Co1 flips, configuration *b*, the injectors are antiparallel, a nonuniform spin accumulation is present in the Al island, and relaxes from the points of injection, giving rise to a spin current $I_s \propto \sigma_N \cdot \nabla(\mu_{\uparrow} - \mu_{\downarrow})$. Note that the charge current $I \propto \nabla(\mu_{\uparrow} + \mu_{\downarrow})$ at Co3 and Co4 is absent. Although the detectors are still parallel and sensitive only to the spin-down channel, the signal is somewhat larger than in configuration *a*, as it can be seen in the measurement, by 1.6 mΩ.

When Co4 reverses, configuration *c+* (black dots), also the detectors are antiparallel, the V^+ electrode detects $\mu_{\downarrow}$ and V^- , $\mu_{\uparrow}$. In this configuration, with both injectors and detectors antiparallel to each other, we obtain the highest spin contribution, that is 6 mΩ in our measurement. When also Co3 flips, configuration *d*, the detectors now measure the spatial dependence of $\mu_{\uparrow}$, so that the magnitude of the signal is the same as in configuration *b* but with opposite sign. In the reverse trace, configuration *c-* (open dots) the notable difference is that Co3 flips before Co4 and the signal changes sign as V^+ is sensitive to spin-up while I^+ injects spin-down electrons.

To evaluate qualitatively the experimental results, we

model the system as (i) one dimensional and we assume injectors and detectors to be (ii) collinear (parallel or antiparallel to $\hat{y}$), and (iii) pointlike. Assumptions (i) and (iii) are justified by the fact that previous measurements reported $\lambda_{sf} = 500$ nm at RT,^{4,13} larger than the island's and contacts' width, and (ii) because shape anisotropy keeps the magnetization in-plane and in the direction of the contact. The contacts' positions of Co1, Co2, Co3, Co4 electrodes to the Al island are at d_1 , d_2 , d_3 , and d_4 , with $0 \leq d_1 < d_2 < d_3 < d_4 \leq L$. A charge current I is injected at d_2 and extracted at d_1 . As the injectors are ferromagnetic, the injected charge current is partially spin polarized, $I_s = P_i I$ ($P < 1$ and $i = 1, 2$). This produces a space dependent spin accumulation in the Al island $\mu(x) = \tilde{\mu}(x, d_2) - \tilde{\mu}(x, d_1)$ (the minus sign because of the opposite directions of the charge current) where $\tilde{\mu} = (\mu_{\uparrow} - \mu_{\downarrow})/2$. The spatial dependence of $\mu(x)$ in Al strip, can be calculated by solving the 1D spin coupled diffusion equation¹⁴ with the boundary conditions $d\mu_{\uparrow, \downarrow}/dx = 0$ at either end of the island $x = 0$ or $x = L$, that is, no charge or spin current at $x = 0, L$. The solution is¹⁸

$$\tilde{\mu}(x, d_i) = \frac{e\lambda_{sf}IP_i}{2\sigma A} \left[\exp\left(-\frac{|x - d_i|}{\lambda_{sf}}\right) + C_i \exp\left(-\frac{x}{\lambda_{sf}}\right) + D_i \exp\left(\frac{x - L}{\lambda_{sf}}\right) \right], \quad (1)$$

where σ and A are the conductivity and sectional area of the Al strip and C_i and D_i are given by

$$C_i = \frac{\cosh[(L - d_i)/\lambda_{sf}]}{\sinh(L/\lambda_{sf})}, \quad D_i = \frac{\cosh(d_i/\lambda_{sf})}{\sinh(L/\lambda_{sf})}. \quad (2)$$

In the limit $L \gg \lambda_{sf}$, one recovers the 1D equation⁴ and in the limit $L \ll \lambda_{sf}$, one finds the zero-dimensional (0D) expression.¹³ The ferromagnetic detectors positioned at d_3 and d_4 have polarization P_3 and P_4 . We measure the difference of the detectors' potentials at this point, $V(d_3) - V(d_4) = V^+ - V^-$, and the spin dependent resistance is $(V^+ - V^-)/I = [P_3\mu(x=d_3) - P_4\mu(x=d_4)]/eI$.

In the fitting, the free parameters are $|P_i| = P$ and λ_{sf} , the position of the electrodes are as determined from the SEM micrographs. Also, a constant background is added to the calculated signal. We find at low temperature a spin diffusion

FIG. 4. Nonlocal spin accumulation at room temperature, device D. The fitting based on Eq. (1) returns $\lambda_{sf} = (350 \pm 50)$ nm and a polarization of $P = (8 \pm 1)\%$.

length $\lambda_{\text{sf}}=400\pm 50$ nm and an interface polarization $P=(10\pm 1)\%$ and $\lambda_{\text{sf}}=350\pm 50$ nm, $P=(8\pm 1)\%$ at room temperature. Both these values are slightly smaller than previously found.^{4,12,13}

Figure 4 shows a nonlocal spin valve measurement at room temperature for device D. We observe, while sweeping at positive fields, at around +14 mT, an extra step in the signal and we interpret this as Co4 flipping its magnetization through an intermediate step. We also note in the reverse trace that Co3 reverses before Co4. Also here, the fit follows well the experimental data: this implies that all junctions have the same polarization.

In summary, we have studied spin accumulation in an Al island, connected by four Co electrodes through low resistance junctions. From the measurements of the amplitude of the spin accumulation we can identify the sequence of the magnetization switching of the ferromagnetic contacts. The analysis based on Eq. (1) allows us to extract λ_{sf} and P .

This work was supported by the Stichting Fundamenteel Onderzoek der Materie (FOM) and MSC^{plus}. The authors acknowledge useful discussions with Andrei Filip and Steven M. Watts and the technical support of Gert ten Brink and Pim van den Dool.

---

*Electronic address: m.v.costache@rug.nl

†Present address: Department of Condensed Matter, Weizmann Institute of Science, 76100 Rehovot, Israel.

¹For recent reviews, see D. D. Awschalom, D. Loss, and N. Samarth, *Semiconductor Spintronics and Quantum Computation* (Springer-Verlag, New York, 2002); I. Žutić, J. Fabian, and S. Das Sarma, *Rev. Mod. Phys.* **76**, 323 (2004).

²M. Johnson and R. H. Silsbee, *Phys. Rev. Lett.* **55**, 1790 (1985).

³F. J. Jedema, A. T. Filip, and B. J. van Wees, *Nature (London)* **410**, 345 (2001).

⁴F. J. Jedema, H. B. Heersche, A. T. Filip, J. J. A. Baselmans, and B. J. van Wees, *Nature (London)* **416**, 713 (2002); F. J. Jedema, M. V. Costache, H. B. Heersche, J. J. A. Baselmans, and B. J. van Wees, *Appl. Phys. Lett.* **81**, 5116 (2002).

⁵M. Urech, J. Johansson, V. Korenivski, and D. B. Haviland, *J. Magn. Magn. Mater.* **272**, E1469 (2004).

⁶T. Kimura, J. Hamrle, Y. Otani, K. Tsukagoshi, and Y. Aoyagi, *Appl. Phys. Lett.* **85**, 3501 (2004).

⁷S. Garzon, I. Žutić, and R. A. Webb, *Phys. Rev. Lett.* **94**, 176601 (2005).

⁸N. Tombros, S. van der Molen, and B. van Wees, *cond-mat/0506538* (to be published).

⁹Y. Ohno, D. K. Young, B. Beschoten, F. Matsukura, H. Ohno, and D. D. Awschalom, *Nature (London)* **402**, 790 (1999).

¹⁰D. Beckmann, H. B. Weber, and H. v. Löhneysen, *Phys. Rev. Lett.* **93**, 197003 (2004).

¹¹V. Dediu, M. Murgia, F. C. Maticcotta, C. Taliani, and S. Barbanera, *Solid State Commun.* **122**, 181 (2002).

¹²S. O. Valenzuela, D. J. Monsma, C. M. Marcus, V. Narayana-murti, and M. Tinkham, *Phys. Rev. Lett.* **94**, 196601 (2005).

¹³M. Zaffalon and B. J. van Wees, *Phys. Rev. Lett.* **91**, 186601 (2003).

¹⁴P. C. van Son, H. van Kempen, and P. Wyder, *Phys. Rev. Lett.* **58**, 2271 (1987).

¹⁵M. Johnson and R. H. Silsbee, *Phys. Rev. B* **37**, 5326 (1988).

¹⁶T. Valet and A. Fert, *Phys. Rev. B* **48**, 7099 (1993).

¹⁷A. T. Filip, B. H. Hoving, F. J. Jedema, B. J. van Wees, B. Dutta, and S. Borghs, *Phys. Rev. B* **62**, 9996 (2000); G. Schmidt, D. Ferrand, L. W. Molenkamp, A. T. Filip, and B. J. van Wees, *ibid.* **62**, R4790 (2000); E. I. Rashba, *ibid.* **62**, R16267 (2000).

¹⁸M. Zaffalon, Ph.D. thesis, University of Groningen (unpublished).