University of Groningen

An Improved Perylene Sensitizer for Solar Cell Applications

Li, Chen; Yum, Jun-Ho; Moon, Soo-Jin; Herrmann, Andreas; Eickemeyer, Felix; Pschirer, Neil G.; Erk, Peter; Schoeneboom, Jan; Muellen, Klaus; Graetzel, Michael

Published in:
Chemsuschem

DOI:
[10.1002/cssc.200800068](https://doi.org/10.1002/cssc.200800068)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2008

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Li, C., Yum, J.-H., Moon, S.-J., Herrmann, A., Eickemeyer, F., Pschirer, N. G., Erk, P., Schoeneboom, J., Muellen, K., Graetzel, M., Nazeeruddin, M. K., Müllen, K., & Grätzel, M. (2008). An Improved Perylene Sensitizer for Solar Cell Applications. *Chemsuschem*, 1(7), 615-618.
<https://doi.org/10.1002/cssc.200800068>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

An Improved Perylene Sensitizer for Solar Cell Applications

Chen Li,^[a] Jun-Ho Yum,^[b] Soo-Jin Moon,^[b] Andreas Herrmann,^[c] Felix Eickemeyer,^[d] Neil G. Pschirer,^[d] Peter Erk,^[d] Jan Schöneboom,^[d] Klaus Müllen,^[a] Michael Grätzel,^[b] and Mohammad K. Nazeeruddin^{*,[b]}

Dye-sensitized solar cells (DSSCs) based on nanocrystalline semiconductors have been the subject of intense investigation owing to their potential low cost, easy processing and good performance.^[1] In these cells, a dye monolayer is adsorbed on a mesoporous film of titania. Upon light absorption, the dye injects electrons into the TiO₂ conduction band, where they are transported to the anode. The neutral dye is regenerated by electron transfer either from an electrolyte containing a redox system or from a solid-state hole conductor. With a closed external circuit and under illumination, the device then constitutes a photovoltaic energy-conversion system, which is regenerative and stable. In this technology, ruthenium complexes maintained a clear lead in performance amongst the thousands of dyes tested, yielding power conversion efficiencies of 10–11%.^[2] However, in view of the cost and availability of 4d metals as well as their environmental non-compatibility, many metal-free organic dyes have been developed.^[3]

As metal-free dyes, perylene derivatives have been widely applied in various optical devices owing to their outstanding chemical, thermal and photochemical stability and non-toxicity.^[4] Several perylene dyes have been used as sensitizers in DSSCs, however, they exhibited very low overall power conversion efficiencies ($\eta = 1\text{--}2\%$).^[5] Recently, we reported diphenylamino-substituted perylene monoanhydrides as sensitizers which show an improved efficiency of up to 3.9%.^[6] Herein, we present a novel perylene molecule **5** that bears two thiophenol groups in the 1 and 6 positions (see Scheme 1 and Experimental Section). Substituents at the 1 and 6 positions in perylene tune the HOMO and LUMO energies and thereby the absorption wavelength of the molecule. Another aspect of introducing (bulky) side groups is their ability to suppress dye aggregation on TiO₂ resulting in more efficient electron injection.^[7] In this type of molecule, light absorption is associated with an intramolecular charge transfer (ICT) excitation from the donor to the acceptor moiety of the dye, which is anchored to the surface of the TiO₂, resulting in efficient electron transfer from the excited dye into the TiO₂ conduction band.

Figure 1 shows the UV/Vis absorption spectra of **5** measured in CH₂Cl₂ solution and adsorbed on a TiO₂ electrode. The solution absorption spectrum of **5** shows two peaks at $\lambda = 620\text{ nm}$ ($\epsilon = 22\,727\text{ M}^{-1}\text{ cm}^{-1}$) and at 462 nm ($\epsilon = 13\,704\text{ M}^{-1}\text{ cm}^{-1}$). From time-dependent density functional theory (DFT) calculations^[8] at the B3LYP/TZVP level,^[9,10] the first excitation (predicted at $\lambda = 639\text{ nm}$) corresponds to the ICT from the HOMO located mainly on the diphenylamino group to the LUMO (π^*) located

Scheme 1. Synthesis of **5**. 1) Br₂, chloroform, reflux, 6 h, 86%; 2) thiophenol, K₂CO₃, NMP, RT, 3 h, 56%; 3) di(*p*-*tert*-octylphenyl)amine, [Pd₂(dba)₃], P(*t*Bu)₃, *t*BuONa, overnight, 83%; 4) KOH, isopropanol, overnight, 80%. (dba = dibenzylideneacetone.)

Figure 1. Normalized UV/Vis absorption spectra of **5** in dichloromethane (solid line) and adsorbed on a nanocrystalline 6- μm transparent TiO₂ film (dashed line).

[a] C. Li, Prof. Dr. K. Müllen

Max Planck Institute for Polymer Research
Ackermannweg 10, 55128 Mainz (Germany)

[b] Dr. J.-H. Yum, S.-J. Moon, Prof. Dr. M. Grätzel, Dr. M. K. Nazeeruddin

Laboratory of Photonics and Interfaces, EPFL SB ISIC LPI
CH-1015 Lausanne (Switzerland)
Fax: (+41) 21-6934-1111
E-mail: mdkhaja.nazeeruddin@epfl.ch

[c] Prof. Dr. A. Herrmann

Department of Polymer Chemistry, Zernike Institute for Advanced Materials
University of Groningen, Nijenborgh 4
9747 AG Groningen (The Netherlands)

[d] Dr. F. Eickemeyer, Dr. N. G. Pschirer, Dr. P. Erk, Dr. J. Schöneboom

BASF SE, Research Specialty Chemicals, 67056 Ludwigshafen (Germany)

mainly on the perylene. The second band (predicted at $\lambda = 473$ nm) is a transition from a mixed thiophenyl-perylene π orbital to the LUMO. When absorbed onto TiO_2 , compound **5** shows a blue-shifted absorption ($\lambda_{\text{max}} = 506$ nm). This effect is attributed to the ring opening of the anhydride group on the perylene to form two carboxylates, which provide strong chemical interactions with the oxide surface. This phenomenon is well known for perylene anhydride sensitizers.^[5,6]

Figure 2 shows the cyclic voltammogram^[11] of **5** which exhibits reversible waves both in the oxidation and reduction regions, indicating the electrochemical stability of **5**, a vital pa-

Figure 2. Cyclic voltammetry (CV) traces of **5** measured in a CH_2Cl_2 solution containing 0.1 M tetrabutylammonium hexafluorophosphate (Bu_4NPF_6) as supporting electrolyte. The reference electrode was an Ag wire internally calibrated with ferrocene/ferrocenium (Fc/Fc^+) in the measurement.

rameter for the durability of solar cells. The HOMO and LUMO are observed at 0.48 V and -1.08 V (vs Fc/Fc^+), respectively. When the dye adsorbs to TiO_2 , it undergoes a transition to the dicarboxylate, that is, a ring-opened structure, which results in a negative shift in the HOMO potential. From DFT calculations of the anhydride and the dicarboxylate, we obtain a shift of 0.5 eV in the ionization potential. Also, the optical gap is increased upon ring opening to the dicarboxylate, resulting in an additional negative shift to the injecting excited-state energy level (see above). Hence, the energetic alignment of the HOMO and LUMO of the dye is well suited for electron injection into the TiO_2 conduction band as well as regeneration by the triiodide/iodide redox couple or alternatively by a hole conductor.

To fabricate the solar cell, a 6- μm thick transparent mesoporous TiO_2 with 4- μm thick scattering mesoporous TiO_2 was prepared and treated with a 40 mM solution of titanium tetrachloride using a previously reported procedure.^[1b] The films were heated at 500°C in air and sintered for 30 min before use. The solutions of sensitizer **5** were prepared in chlorobenzene at a concentration of 0.15 mM. The films were immersed into the dye solution for 16–18 h at room temperature and were then rinsed with acetonitrile to remove any unadsorbed dye and used as such for photovoltaic measurements in completely sealed devices. Figure 3 shows the incident monochromatic photon-to-current conversion efficiency (IPCE) and the J – V (current density vs voltage) curve for the solar cell sensitized

Figure 3. a) IPCE spectrum and b) J – V curve of **5**-sensitized solar cells based on a volatile electrolyte (active area 0.2 cm^2). The redox electrolyte was composed of 0.6 M 1-butyl-3-methylimidazolium iodide, 0.05 M iodine, 0.1 M LiI and 0.5 M *tert*-butylpyridine in 15:85 (v/v) valeronitrile/acetonitrile.

with **5**. The IPCE curve of **5** plotted as a function of excitation wavelength exhibits a strikingly high plateau value of 87%.

The solar cell sensitized with **5** shows an unprecedented efficiency under solar simulated light irradiation (100 mW cm^{-2} , 1.5 AM global) of 6.8% with a short-circuit current density $J_{\text{sc}} = (12.60 \pm 0.20)\text{ mA cm}^{-2}$, an open-circuit voltage $V_{\text{oc}} = (728 \pm 15)\text{ mV}$ and a fill factor $\text{FF} = 0.74 \pm 0.01$. As far as we know, this is the highest efficiency ever reported for a perylene/ TiO_2 DSSC. Integrating the IPCE curve over the solar spectrum results in a short-circuit current of 11.8 mA cm^{-2} in agreement with the photocurrent of the measured device. At the low intensities, 9.3 and 51.4% sun, the J_{sc} values are 1.24 and 6.74 mA cm^{-2} , respectively, which are linearly proportional to the light intensity. The efficiencies at 9.3 and 51.4% sun are 6.7 and 7.0%, respectively.

We fabricated complete solid-state dye-sensitized solar cells, where 2,2',7,7'-tetrakis(*N,N*-di-*p*-methoxyphenylamine)-9,9'-spirobifluorene (Spiro-MeOTAD) as an organic hole-transporting material replaces the liquid electrolyte. In this setup, interfacial hole transfer from the perylene sensitizer **5** to Spiro-MeOTAD takes place and regenerates the oxidized dye.^[12] Figure 4 shows the solid-state solar cell J – V characteristics measured under AM 1.5 solar conditions. At 100 mW cm^{-2} , $J_{\text{sc}} = 2.83\text{ mA cm}^{-2}$, $V_{\text{oc}} = 838\text{ mV}$ and $\text{FF} = 0.75$ and the corresponding power conversion efficiency is 1.78%. The cell demonstrated an almost linear behavior under different light intensities ranging from 9.2 to 99% sun with a slightly higher efficiency ($\sim 1.84\%$) at low intensity.

In summary, we have molecularly engineered a highly efficient novel perylene sensitizer, which yields 87% IPCE and

Figure 4. Current–voltage characteristics obtained with solid-state solar cells derivatized with **5**.

6.8% power conversion efficiency under standard AM 1.5 solar conditions. We have also demonstrated the possibility to utilize perylenes for solid-state solar cells yielding 1.8% power conversion efficiency under standard illumination conditions. Comparing these results with other perylene sensitizers,^[6] we conclude that the thiophenol groups in **5** contribute strongly to the obtained high efficiencies. Work to extend the spectral response of these sensitizers further into the red and near-IR spectral region is in progress.

Experimental Section

N-(2,6-Diisopropylphenyl)-perylene-3,4-dicarboximide (**1**) was supplied by BASF-SE (Ludwigshafen). Di(*p*-*tert*-octylphenyl)amine was purchased from MP Biomedicals Inc. All other starting materials and catalysts were purchased from Aldrich, Acros or ABCR and used as received. ¹H and ¹³C NMR spectra were recorded on Bruker AMX250 NMR spectrometers using the residual proton or the carbon signal of the deuterated solvent as an internal standard. Chemical shifts are reported in parts per million. FD mass spectra were performed with a VG Instrument ZAB 2-SE-FDP. UV/Vis absorption spectra were recorded on a Perkin–Elmer Lambda 40 spectrophotometer. Elemental analyses were carried out by the Microanalytical Laboratory at the Johannes Gutenberg University.

The synthesis of *N*-(2,6-diisopropylphenyl)-1,6,9-tribromoperylene-3,4-dicarboximide (**2**, Scheme 1) was described before.^[13]

Synthesis of 3: Compound **2** (1 g, 1.4 mmol), thiophenol (153 mg, 1.4 mmol) and potassium carbonate (128 mg, 1.4 mmol) were stirred in *N*-methylpyrrolidone (NMP, 80 mL) at room temperature. After 1.5 h, additional thiophenol (76 mg, 0.6 mmol) and potassium carbonate (128 mg, 1.4 mmol) were added to the reaction mixture, which was stirred at the same temperature for another 1.5 h. After cooling to room temperature, the reaction mixture was precipitated and washed with water and dried. The product was purified by column chromatography on silica gel using dichloromethane and pentane (1:4) as eluent to give a dark red solid (600 mg, 56%). ¹H NMR (300 MHz, CD₂Cl₂, 25 °C, TMS): δ = 8.63 (d, *J* = 8 Hz, 1H), 8.50–8.41 (m, 4H), 8.11 (d, *J* = 8 Hz, 1H), 7.91 (t, 1H), 7.47–7.26 (m, 13H), 2.64 (m, 2H; CH isopropyl), 1.07 ppm (d, *J* = 7 Hz, 12H; CH₃ isopropyl); ¹³C NMR (75 MHz, CD₂Cl₂, 25 °C, TMS): δ = 163.88 (C=O), 146.51, 136.02, 135.77, 135.49, 135.40, 135.10, 133.35, 133.31, 131.75, 131.70, 131.29, 131.10, 130.30, 129.83, 129.33, 128.61, 128.09, 127.32, 125.95, 125.83, 124.45, 120.96, 29.55 (CH isopropyl), 24.17 ppm (CH₃ isopropyl); MS: *m/z* 775.5 (100%) [*M*⁺] (calcd

776.82); IR (KBr): $\tilde{\nu}_{\text{max}}$ = 2944, 1908, 1701, 1589, 1488, 1390, 1338, 1238, 1119, 1012, 938, 868, 810, 774, 725, 708, 655, 544 cm⁻¹; elemental analysis (%) calcd for C₄₆H₃₄BrNO₂S₂: C 71.12, H 4.41, N 1.80, S 8.26; found: C 70.79, H 4.56, N 1.73, S 7.93; UV/Vis (CH₂Cl₂): λ_{max} (log ϵ) = 515 (4.47), 475 nm (4.46).

Synthesis of 4: A mixture of **3** (0.3 g, 0.39 mmol), di(*p*-*tert*-octylphenyl)amine (0.22 g, 0.58 mmol), [Pd₂(dba)₃] (20 mg, 0.022 mmol), tri-*tert*-butylphosphine (20 mg, 0.10 mmol), sodium *tert*-butyl alcohol (55 mg, 0.57 mmol) and toluene (100 mL) was stirred at 80 °C under argon atmosphere overnight. The solvent was removed under reduced pressure, and the crude product was purified by column chromatography using toluene as eluent on silica to give a green solid (0.35 g, 83%). ¹H NMR (300 MHz, CD₂Cl₂, 25 °C, TMS): δ = 8.68 (d, *J* = 8 Hz, 1H), 8.52 (d, *J* = 7 Hz, 1H), 8.47 (s, 1H), 8.43 (s, 1H), 8.16 (d, *J* = 8 Hz, 1H), 7.52–7.27 (m, 19H), 7.01 (d, *J* = 9 Hz, 4H), 2.66 (m, 2H; CH isopropyl), 1.73 (s, 4H), 1.37 (s, 12H), 1.08 (s, 12H; CH₃ isopropyl), 1.08 (d, *J* = 7 Hz, 12H), 0.77 ppm (s, 18H); ¹³C NMR (75 MHz, CD₂Cl₂, 25 °C, TMS): δ = 163.81 (C=O), 147.79, 146.55, 146.36, 145.17, 136.65, 136.55, 135.92, 135.80, 134.50, 133.17, 132.77, 132.19, 131.70, 131.65, 130.00, 129.92, 129.67, 129.23, 128.86, 128.56, 128.34, 127.57, 126.22, 125.08, 124.59, 124.24, 123.13, 120.37, 119.67, 57.38, 38.49, 32.66, 31.88, 31.62, 29.34 (CH isopropyl), 23.98 ppm (CH₃ isopropyl); MS: *m/z* 1088.9 (100%) [*M*⁺] (calcd 1089.57); IR (KBr): $\tilde{\nu}_{\text{max}}$ = 2944, 2362, 1705, 1670, 1568, 1461, 1385, 1326, 1239, 1202, 1050, 937, 866, 829, 770, 725, 698, 562 cm⁻¹; elemental analysis (%) calcd for C₇₄H₇₆N₂O₂S₂: C 81.58, H 7.03, N 2.57, S 5.89; found: C 80.80, H 7.47, N 2.49, S 5.81; UV/Vis (CH₂Cl₂): λ_{max} (log ϵ) = 606 (4.14), 462 nm (3.89).

Synthesis of 5: A mixture of **4** (300 mg, 0.28 mmol), potassium hydroxide (500 mg, 9 mmol) and isopropanol (50 mL) was refluxed under stirring overnight. The reaction mixture was cooled down to room temperature and then poured into acetic acid, and the solution was stirred at 40 °C for 4 h. The solvent was removed in vacuum. The crude product was washed with water. Column chromatography using toluene as eluent on silica yielded **5** as a green solid (200 mg, 80%). ¹H NMR (300 MHz, CD₂Cl₂, 25 °C, TMS): δ = 8.54 (d, *J* = 8 Hz, 1H), 8.45 (d, *J* = 7 Hz, 1H), 8.32 (d, *J* = 7 Hz, 2H), 8.20 (d, *J* = 8 Hz, 1H), 7.54–7.38 (m, 12H), 7.31 (d, *J* = 9 Hz, 4H), 7.02 (d, *J* = 9 Hz, 4H), 1.73 (s, 4H), 1.36 (s, 12H), 0.77 ppm (s, 18H); ¹³C NMR (75 MHz, CD₂Cl₂, 25 °C, TMS): δ = 160.62 (C=O), 160.53, 148.47, 146.52, 145.44, 137.16, 137.03, 136.35, 135.72, 135.63, 135.49, 135.36, 134.40, 133.53, 133.12, 132.02, 131.87, 130.26, 130.19, 129.40, 129.22, 129.17, 129.06, 128.69, 128.02, 127.64, 127.29, 125.11, 124.09, 123.33, 116.07, 115.21, 57.37, 38.51, 32.65, 31.87, 31.61 ppm. MS: *m/z* 929.5 (100%) [*M*⁺] (calcd 930.29); IR (KBr): $\tilde{\nu}_{\text{max}}$ = 3056, 2962, 2361, 1938, 1766, 1564, 1458, 1406, 1364, 1326, 1270, 11186, 1014, 980, 908, 830, 802, 770, 749, 688, 580, 548 cm⁻¹; elemental analysis (%) calcd for C₆₂H₅₉NO₃S₂: C 80.05, H 6.39, N 1.51, S 6.89; found: C 79.96, H 6.38, N 1.43, S 6.87. UV/Vis (CH₂Cl₂): λ_{max} (log ϵ) = 620 (4.35), 462 nm (4.13).

Electrochemical experiments were carried out with an EG&G Princeton Applied Research potentiostat model 273. The working electrode consisted of an inlaid platinum disk (1.5-mm diameter) that was polished on a felt pad with alumina (0.05 μm) and sonicated in milli-Q water for 5 min before each experiment. A platinum wire was used as the counter electrode, and an Ag wire was used as the reference electrode internally calibrated with ferrocene/ferrocenium (Fc/Fc⁺) in the measurement.

Dye-sensitized solar cells: The photoanodes composed of nanocrystalline TiO₂ were prepared using a previously reported procedure.^[1b] A paste composed of 20-nm anatase TiO₂ particles for the

transparent nanocrystalline layer was coated on FTO glass plates (Nippon Sheet Glass, 4 mm thickness) pretreated with TiCl_4 (40 mM) by repetitive screen printing to obtain a thickness of 6 μm . Then, a paste for the scattering layer containing 400-nm-sized anatase particles (CCIC, HPW-400) was deposited onto the transparent nanocrystalline layer. The resulting layer had a thickness of around 4 μm . The TiO_2 electrodes were gradually sintered under a programmed flow: at 325 °C for 5 min, at 375 °C for 5 min, at 450 °C for 15 min and finally at 500 °C for 15 min. The TiO_2 electrodes were treated again by TiCl_4 under 70 °C for 30 min and sintered again at 500 °C for 30 min before they were dipped into dye solution. The TiO_2 electrodes were immersed into the solutions of 5 (150 μM) in chlorobenzene and kept at room temperature for 16–18 h. The dye-adsorbed TiO_2 electrode and thermally platinized counter electrode were assembled into a sealed sandwich-type cell with a gap of a hot-melt ionomer film (Surlyn, thickness 1702.25 μm , DuPont). An electrolyte solution (0.6 M 1-butyl-3-methylimidazolium iodide, 0.05 M iodine, 0.1 M LiI and 0.5 M *tert*-butylpyridine in 15:85 (v/v) valeronitrile/acetonitrile) was used for the redox couple. To reduce scattered light from the edge of the glass electrodes of the dyed TiO_2 layer, a light-shading mask was used onto the DSSCs so the active area of the DSSCs was fixed to 0.2 cm^2 .

For the solid-state solar cell, details of the process were described in a previous report.^[12] The cell consists of a F-doped SnO_2 glass substrate (15 $\Omega/\square$, Pilkington) onto which a compact layer of approximately 100 nm was deposited by spray pyrolysis. The nanoporous layer (~1.8 μm) of 20-nm diameter TiO_2 was coated by doctor-blading. After the TiO_2 layer had been annealed at 500 °C for 30 min under oxygen flow, the film was treated with 0.02 M aqueous TiCl_4 solution overnight. The TiO_2 electrode was soaked in the dye solution and kept at room temperature for overnight. The hole-conducting matrix was applied by spin-coating of a solution of 2,2',7,7'-tetrakis(*N,N*-dimethoxyphenylamine)-9,9'-spirobifluorene (Spiro-MeOTAD) in chlorobenzene containing *tert*-butylpyridine and $\text{Li}(\text{CF}_3\text{SO}_2)_2\text{N}$. Fabrication of the device was completed by evaporating a 50-nm gold electrode on top. For the photovoltaic measurement of solid-state solar cells, their active areas were fixed to 0.14 cm^2 .

For photovoltaic measurements of the DSSCs, the irradiation source was a 450 W xenon light source (Osram XBO 450, USA), whose power of an AM 1.5 solar simulator was calibrated by using a Tempax 113 solar filter (Schott). The output power of an AM 1.5 solar simulator was calibrated by using a reference Si photodiode equipped with a colour-matched IR cutoff filter (KG-3, Schott) in order to reduce the mismatch in the region of 350–750 nm between the simulated light and AM 1.5 to less than 2%.^[1b] The measurement delay time of *J*–*V* characteristics of DSSCs was fixed to 40 ms. The measurement of incident photon-to-current conversion efficiency (IPCE) was plotted as a function of excitation wavelength by using the incident light from a 300 W xenon lamp (ILC Technology, USA), which was focused through a Gemini-180 double monochromator (Jobin Yvon Ltd.).

Acknowledgements

We gratefully acknowledge financial support from the German Science Foundation SFB 625, Korean–German IRTG and Korean–Swiss GBL.

Keywords: dye-sensitized solar cells • fused-ring systems • photoelectrochemical cells • sensitizers

- [1] a) Md. K. Nazeeruddin, M. Grätzel, *Struct. Bonding (Berlin)* **2007**, 123, 113–175; b) M. K. Nazeeruddin, P. Péchy, T. Renouard, S. M. Zakeeruddin, R. Humphry-Baker, P. Comte, P. Liska, L. Cevey, E. Costa, V. Shklover, L. Spiccia, G. B. Deacon, C. A. Bignozzi, M. Grätzel, *J. Am. Chem. Soc.* **2001**, 123, 1613–1624; c) Z.-S. Wang, T. Yamaguchi, H. Sugihara, H. Arakawa, *Langmuir* **2005**, 21, 4272–4276; d) Md. K. Nazeeruddin, F. De Angelis, S. Fantacci, A. Selloni, G. Viscardi, P. Liska, S. Ito, T. Bessho, M. Grätzel, *J. Am. Chem. Soc.* **2005**, 127, 16835–16847.
- [2] a) P. Wang, S. M. Zakeeruddin, J. E. Moser, R. Humphry-Baker, P. Comte, V. Aranyos, A. Hagfeldt, Md. K. Nazeeruddin, M. Grätzel, *Adv. Mater.* **2004**, 16, 1806–1811; b) Y. Chiba, A. Islam, Y. Watanabe, R. Komiya, N. Koide, L. Han, *Jpn. J. Appl. Phys.* **2006**, 45, 638–640.
- [3] a) K. Hara, T. Sato, R. Katoh, A. Furube, Y. Ohga, A. Shinpo, S. Suga, K. Sayama, H. Sugihara, H. Arakawa, *J. Phys. Chem. B* **2003**, 107, 597–606; b) T. Horiuchi, H. Miura, K. Sumioka, S. Uchida, *J. Am. Chem. Soc.* **2004**, 126, 12218–12219; c) S. Kim, J. K. Lee, S. O. Kang, J. Ko, J.-H. Yum, S. Fantacci, F. De Angelis, D. Di Censo, M. K. Nazeeruddin, M. Grätzel, *J. Am. Chem. Soc.* **2006**, 128, 16701–16707; d) D. P. Hagberg, T. Edvinsson, T. Marinado, G. Boschloo, A. Hagfeldt, L. Sun, *Chem. Commun.* **2006**, 2245–2247.
- [4] a) J. Jacob, S. Sax, T. Piok, E. J. W. List, A. C. Grimsdale, K. Müllen, *J. Am. Chem. Soc.* **2004**, 126, 6987–6995; b) B. A. Jones, M. J. Ahrens, M.-H. Yoon, A. Facchetti, T. J. Marks, M. R. Wasielewski, *Angew. Chem.* **2004**, 116, 6523–6526; *Angew. Chem. Int. Ed.* **2004**, 43, 6363–6366; c) V. Lemaire, M. Steel, D. Beljonne, J.-L. Bredas, J. Cornil, *J. Am. Chem. Soc.* **2005**, 127, 6077–6086; d) E. E. Neuteboom, S. C. J. Meskers, P. A. Van Hal, J. K. J. Van Duren, E. W. Meijer, R. A. J. Janssen, H. Dupin, G. Pourtois, J. Cornil, R. Lazzaroni, J.-L. Bredas, D. Beljonne, *J. Am. Chem. Soc.* **2003**, 125, 8625–8638; e) L. Schmidt-Mende, A. Fichtenkötter, K. Müllen, E. Moons, R. H. Friend, J. D. Mackenzie, *Science* **2001**, 293, 1119–1122; f) F. Wuerthner, Z. Chen, F. J. M. Hoebe, P. Osswald, C.-C. You, P. Jonkheijm, J. von Herrikhuysen, A. P. H. J. Schenning, P. P. A. M. van der Schoot, E. W. Meijer, E. H. A. Beckers, S. C. J. Meskers, R. A. J. Janssen, *J. Am. Chem. Soc.* **2004**, 126, 10611–10618; g) X. Zhan, Z. Tan, B. Domercq, Z. An, X. Zhang, S. Barlow, Y. Li, D. Zhu, B. Kippelen, S. R. Marder, *J. Am. Chem. Soc.* **2007**, 129, 7246–7247.
- [5] a) S. Ferrere, B. A. Gregg, *New J. Chem.* **2002**, 26, 1155–1160; b) Y. Shibano, T. Umeyama, Y. Matano, H. Imahori, *Org. Lett.* **2007**, 9, 1971–1974; c) C. Zafer, M. Kus, G. Turkmen, H. Dincalp, S. Demic, B. Kuban, Y. Teoman, S. Iclli, *Sol. Energy Mater. Sol. Cells* **2007**, 91, 427–431; d) T. Dentani, K. Funabiki, J. Y. Jin, T. Yoshida, H. Minoura, M. Matsui, *Dyes Pigm.* **2006**, 72, 303–307.
- [6] T. Edvinsson, C. Li, N. G. Pschirer, J. C. Schöneboom, F. Eickemeyer, R. Sens, G. Boschloo, A. Herrmann, K. Müllen, A. Hagfeldt, *J. Phys. Chem. C* **2007**, 111, 15137–15138.
- [7] a) N. Koumura, Z. Wang, S. Mori, M. Miyashita, E. Suzuki, K. Hara, *J. Am. Chem. Soc.* **2006**, 128, 14256–14257; b) Y. Ooyama, A. Ishii, Y. Kagawa, I. Imae, Y. Harima, *New J. Chem.* **2007**, 31, 2076–2082.
- [8] a) R. Ahlrichs, M. Bär, M. Häser, H. Horn, C. Kölmel, *Chem. Phys. Lett.* **1989**, 162, 165–169; b) R. Bauernschmitt, R. Ahlrichs, *Chem. Phys. Lett.* **1996**, 256, 454–464.
- [9] a) A. D. Becke, *J. Chem. Phys.* **1993**, 98, 5648–5652; b) C. Lee, W. Yang, R. G. Parr, *Phys. Rev. B* **1988**, 37, 785–789.
- [10] A. Schäfer, C. Huber, R. Ahlrichs, *J. Chem. Phys.* **1994**, 100, 5829–5835.
- [11] The cyclic voltammograms (CVs) were measured in a solution of Bu_4NPF_6 (0.1 M) in dry dichloromethane with a scan rate of 50 mV s^{−1} at room temperature under argon.
- [12] a) H. J. Snaith, L. Schmidt-Mende, M. Grätzel, *Phys. Rev. B* **2006**, 74, 045306; b) H. J. Snaith, M. Grätzel, *Appl. Phys. Lett.* **2006**, 89, 262114; c) L. Schmidt-Mende, U. Bach, R. Humphry-Baker, T. Horiuchi, H. Miura, S. Ito, S. Uchida, M. Grätzel, *Adv. Mater.* **2005**, 17, 813–815.
- [13] U. Rohr, C. Kohl, K. Müllen, *J. Mater. Chem.* **2001**, 11, 1789–1799.

Received: March 3, 2008

Revised: April 16, 2008

Published online on June 6, 2008