University of Groningen

Silanization of quartz, silicon and mica surfaces with light-driven molecular motors

London, Gabor; Carroll, Gregory T.; Feringa, Ben L.

Published in:
Organic & Biomolecular Chemistry

DOI:
[10.1039/c3ob40276b](https://doi.org/10.1039/c3ob40276b)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2013

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

London, G., Carroll, G. T., & Feringa, B. L. (2013). Silanization of quartz, silicon and mica surfaces with light-driven molecular motors: construction of surface-bound photo-active nanolayers. *Organic & Biomolecular Chemistry*, 11(21), 3477-3483. <https://doi.org/10.1039/c3ob40276b>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Supporting Information

Silanization of quartz, silicon and mica surfaces with
light-driven molecular motors: construction of a
surface-bound photo-active nanolayer

Gábor London,^a Gregory T. Carroll^a and Ben L. Feringa^{a}*

Centre for Systems Chemistry, Stratingh Institute for Chemistry, University of Groningen,
Nijenborgh 4, 9747AG Groningen, The Netherlands.

b.l.feringa@rug.nl

General remarks

General remarks for synthetic procedures:

Reagents were purchased from Aldrich, Acros, Merck or Fluka and were used as provided unless otherwise stated. All solvents were reagent grade and were dried and distilled before use according to standard procedures. All reactions were performed in oven- or flame-dried round bottomed flasks fitted with rubber septa under a positive pressure of nitrogen, unless otherwise noted. Air- and moisture-sensitive liquids and solutions were transferred via syringe or stainless steel cannula. Organic solutions were concentrated by rotary evaporation at 30–40 °C. Flash column chromatography was performed as described by Still et al. (Still, W. C.; Kahn, M.; Mitra, A. J. *Org. Chem.* 1978, 43, 2923-2925.) Chromatography: silica gel, Merck type 9385 230-400 mesh.

TLC: silica gel 60, Merck, 0.25 mm, impregnated with a fluorescent indicator (254 nm).

General remarks for instrumentation:

Mass spectra (HRMS) were recorded on an AEI MS-902. Melting points were recorded on a Büchi B-545 melting point apparatus. ¹H and ¹³C NMR spectra were recorded on a Varian VXR-300 a Varian Mercury Plus, or a Varian Inova 500 operating at 299.97, 399.93, and 499.98 MHz, respectively, for the ¹H nucleus, and at 75.43, 100.57 and 124.98 MHz for the ¹³C nucleus.

Chemical shifts for protons are reported in parts per million scale (δ scale) downfield from tetramethylsilane and are referenced to residual protium in the NMR solvents CHCl₃: δ 7.26, CDHCl₂: δ 5.32). Chemical shifts for carbon are reported in parts per million (δ scale) downfield from tetramethylsilane and are referenced to the carbon resonances of the solvent (CDCl₃: δ 77.0). Data are represented as follows: chemical shift, multiplicity (s = singlet, d = doublet, t = triplet, q = quartet, quin = quintet, m = multiplet), coupling constant in Hz, integration. Irradiation experiments were performed using a Spectroline model ENB-280C/FE lamp at λ = 365 nm, ± 30 nm. NMR samples were placed 2-3 cm from the lamp. Solution UV spectra were obtained using Hewlet-Packard HP 8543 FT or a Jasco V-630 spectrophotometer in a 1 cm quartz cuvette.

Synthesis of compounds and intermediates

Scheme S1 Synthesis of compound **M1**.

5,6-bis(dec-9-enyloxy)-2,7-dimethyl-2,3-dihydro-1H-indene-1-one (2)

K_2CO_3 (2.5 g, 18 mmol) and 10-bromo-1-decene (2.3 mL, 11.5 mmol) were added to a solution of 5,6-dihydroxy-2,7-dimethyl-indene-1-one (**1**)¹ (0.70 g, 3.64 mmol) in acetonitrile (30 mL) and the mixture was heated at reflux overnight. The reaction was quenched by the addition of water (50 mL). The mixture was extracted with EtOAc (3×50 mL). The combined organic layers were washed with water and brine and dried (Na_2SO_4). After the evaporation of the solvent the crude product was purified by flash chromatography (SiO_2 , *n*-heptane : EtOAc = 7 : 1) to give 1.05 g (2.24 mmol, 62 %) of colourless oil. ¹H NMR (400 MHz, CDCl_3) δ 1.26 (d, J = 7.2 Hz, 3H), 1.33-1.42 (m, 16H), 1.45-1.53 (m, 4H), 1.77 (quin, J = 8.0 Hz, 2H), 1.85 (quin, J = 8.0 Hz, 2H), 2.04 (q_{apparent} , J = 6.8 Hz, 4H), 2.55 (s, 3H), 2.59-2.67 (m, 2H), 3.23 (dd, J = 7.6, 16.4 Hz, 1H), 3.85 (t, J = 6.4 Hz, 2H), 4.02 (t, J = 6.4 Hz, 2H), 4.91-4.92 (m, 1H), 4.93-4.95 (m, 1H), 4.96-4.97 (m, 1H), 5.00-5.02 (m, 1H), 5.76-5.86 (m, 2H), 6.71 (s, 1H). ¹³C NMR (100 MHz, CDCl_3) δ 10.87, 16.65, 26.08, 26.11, 28.88, 28.91, 29.04, 29.10, 29.11, 29.27, 29.41, 29.46, 29.48, 30.32, 33.76, 33.78, 34.50, 42.61, 68.47, 72.99, 106.43, 114.11, 114.16, 126.95, 132.18, 139.05, 139.12, 146.06, 151.57, 157.70, 208.99. HRMS (APCI) calcd for $\text{C}_{31}\text{H}_{48}\text{O}_3$ 469.3676 (M^+), found 469, 3658 (M^+).

5,6-bis(dec-9-enyloxy)-2,7-dimethyl-2,3-dihydro-1H-indene-1-thione (3)

Lawesson's reagent (202 mg, 0.5 mmol) was added to a solution of **2** (110 mg, 0.23 mmol) in toluene (10 mL). The mixture was heated to 75°C for 2 h and then filtered over celite. The solid residue was washed with toluene until it became colorless. The filtrate was concentrated *in vacuo* and purified by flash chromatography (SiO_2 , *n*-pentane : diethyl ether = 10 : 1) to give 86 mg (0.18 mmol, 78 %) of a purple oil. ¹H NMR (400 MHz, CDCl_3) δ 1.33-1.42 (m, 19H), 1.45-1.54 (m, 4H), 1.75-1.82 (m, 2H), 1.83-1.90 (m, 2H), 2.05 (q, J = 6.7 Hz, 4H), 2.70-2.75 (m, 1H), 2.73 (s, 3H), 2.97-3.05 (m, 1H), 3.32 (dd, J = 7.0, 17.3 Hz, 1H), 3.84 (t, J = 6.6 Hz, 2H), 4.06 (t, J = 6.4 Hz, 2H), 4.92-4.97 (m, 3H), 5.01 (s, 1H), 5.76-5.86 (m, 2H), 6.76 (s, 1H). ¹³C NMR (APT, 100 MHz, CDCl_3) δ 13.1, 21.7, 26.0, 26.1, 28.8,

28.9, 29.0, 29.1, 29.2, 29.3, 29.4, 29.5, 30.2, 33.7, 33.8, 39.0, 55.3, 68.5, 73.1, 105.7, 114.1, 114.2, 134.2, 137.5, 139.0, 139.1, 146.3, 153.5, 157.5, 248.2. (1 C not observed due to overlap.) HRMS (ESI) calcd for C₃₁H₄₈O₂S 485.3448 (MH⁺), found 485.3627 (MH⁺).

Dialkene-motor (M1)

Diazo fluorenone **3** (577 mg, 3.0 mmol) was added to a solution of thioketone **2** (700 mg, 1.45 mmol) in toluene (10 mL). The mixture was heated to 75°C for 3 h. The formation of the episulfide was monitored by ¹H NMR spectroscopy by following the shift of the aromatic proton of the thioketone from 6.76 ppm to 6.41 ppm. PPh₃ (650 mg, 2.5 mmol) was added to the reaction mixture and it was heated for additional 2 h at 75°C. The reaction mixture was concentrated *in vacuo*. Diethyl ether (20 mL) was added to the mixture which resulted in the precipitation of PPh₃S as yellow crystals. The precipitate was filtered and the procedure was repeated once more. To remove the excess PPh₃, CH₃I (1.0 mL, 16.1 mmol) was added to the ether phase and the mixture was stirred for 1 h. The resulting precipitate was filtered. After the evaporation of the solvent the crude product was purified by flash chromatography (SiO₂, *n*-heptane : toluene = 5 : 1) to give alkene **M1** as yellow oil which solidified to a waxy solid upon standing in the fridge (560 mg, 0.91 mmol, 63 %).

¹H NMR (500 MHz, CDCl₃) δ 1.33-1.42 (m, 19H), 1.49-1.56 (m, 4H), 1.82 (quin, *J* = 8.0 Hz, 2H), 1.88 (quin, *J* = 8.0 Hz, 2H), 2.06 (quin, *J* = 7.5 Hz, 4H), 2.18 (s, 3H), 2.53 (d, *J* = 14.5 Hz, 1H), 3.30 (dd, *J* = 5.5, 14.5 Hz, 1H), 3.92 (q_{apparent}, *J* = 6.5 Hz, 1H), 4.00-4.15 (m, 4H), 4.92-5.03 (m, 4H), 5.77-5.87 (m, 2H), 6.83 (s, 1H), 7.11 (t, *J* = 7.0 Hz, 1H), 7.27 (t, *J* = 7.5 Hz, 1H), 7.34-7.36 (m, 2H), 7.38 (d, *J* = 8.0 Hz, 1H), 7.76 (d, *J* = 7.5 Hz, 1H), 7.81-7.83 (m, 1H), 7.86-7.88 (m, 1H). ¹³C NMR (125 MHz, CDCl₃) δ 16.33, 19.34, 26.49, 29.22, 29.39, 29.43, 29.66, 29.71, 29.77, 29.80, 29.85, 30.76, 34.09, 41.83, 45.07, 68.70, 72.99, 107.92, 114.41, 114.46, 119.36, 119.86, 123.72, 123.87, 126.63, 126.67, 126.89, 126.98, 128.77, 132.06, 133.33, 138.23, 139.35, 139.42, 139.46, 139.87, 139.99, 143.45, 145.95, 152.74, 153.76. (3 C not observed due to overlap.) HRMS (ESI) calcd for C₄₄H₅₆O₂Na 639.4173, found 639.4194.

Irradiation experiment to generate unstable isomer of dialkene-motor M1:

Motor **M1** (~2 mg) was dissolved in CD₂Cl₂ (~1 ml). This sample was placed in an NMR tube and irradiated with 365 nm light at -50°C at a distance of 2-3 cm from the centre of the lamp. ¹H NMR spectra of the sample were taken before, during and after irradiation at -50°C. No further changes were observed after 4 h of irradiation. The relative integration of the absorptions from the two isomers revealed a photostationary state of unstable-**M1** to stable-**M1** with a ratio of 1 : 2. After warming the sample to rt, only the stable form was observed by ¹H NMR spectroscopy.

stable-M1 ¹H NMR (500 MHz, CD₂Cl₂, -50°C) δ 1.19-1.36 (m, H), 1.37-1.50 (br m, H), 1.69-1.76 (br m, 2H), 1.76-1.84 (br m, 2H), 1.98 (br q, *J* = 6.5 Hz, 4H), 2.05 (s, 3H), 2.52 (d, *J* = 14.8 Hz, 1H), 3.23 (dd, *J* = 5.6, 14.6 Hz, 1H), 3.78 (q_{apparent}, *J* = 6 Hz, 1H), 3.96-4.07 (m, 4H), 4.87 (m, 2H), 4.93 (d, *J* = 5.2 Hz, 1H), 4.97 (d, *J* = 5.6 Hz, 1H), 5.73-5.83 (m, 2H), 6.85 (s, 1H), 7.10 (t, *J* = 5.9 Hz, 1H), 7.25-7.27 (m, 2H), 7.31-7.36 (m, 2H), 7.75 (d, *J* = 7.6 Hz, 1H), 7.84 (d, *J* = 6.8 Hz, 1H)

unstable-M1 ¹H NMR (500 MHz, CD₂Cl₂, -50°C) δ 1.25-1.82 (absorptions in this region could not be resolved due to overlap with remaining stable-**M1**), 1.90 (s, 3H), 1.97-2.00 (absorptions in this region could not be resolved due to overlap with remaining stable-**M1**), 2.93 (dd, *J* = 5.8, 15.9 Hz, 1H), 3.37 (dd, *J* = 8.1, 16.3 Hz, 1H), 3.69 (q_{apparent}, *J* = 7.1 Hz, 1H), 3.90-5.82 (absorptions in this region could not be resolved due to overlap with remaining stable-**M1**), 6.80 (s, 1H), 7.14 (t, *J* = 7.5 Hz, 1H), 7.22-7.36 (absorptions in this region could not be resolved due to overlap with remaining stable-**M1**), 7.68

(d, $J = 7.0$ Hz, 1H) 7.75-7.85 (absorptions in this region could not be resolved due to overlap with remaining stable-**M1**).

Disilane motor (**M2**)

A mixture of dialkene-motor **M1** (50 mg, 0.081 mmol) triethoxysilane (0.5 ml, 2.7 mmol) and PtO_2 (5 mg, 0.022 mmol) under inert atmosphere (Ar) was heated to 75°C for 30 min. The crude mixture was purified by column chromatography (SiO_2 , heptane : EtOAc 10 : 1) to give alkene **M2** as a yellow oil. (The isolated yields varied between 30-50%).

¹H NMR (400 MHz, CDCl_3) δ 0.61-0.67 (m, 2H), 0.89 (q, $J = 6.0$ Hz, 2H), 1.21 (d, $J = 4.0$ Hz, 3H), 1.25 (t, $J = 6.8$ Hz, 18H), 1.24-1.46 (br m, 24H), 1.48-1.55 (m, 4H), 1.78-1.91 (m, 4H), 2.18 (s, 3H), 2.53 (d, $J = 14.8$ Hz, 1H), 3.29 (dd, $J = 5.7, 14.6$ Hz, 1H), 3.86 (q, $J = 7.2$ Hz, 12H), 3.99-4.15 (m, 5H), 6.83 (s, 1H), 7.11 (t, $J = 7.5$ Hz, 1H), 7.27 (t, $J = 7.4$ Hz, 1H), 7.32-7.37 (m, 2H), 7.39 (d, $J = 7.9$ Hz, 1H), 7.75 (d, $J = 7.5$ Hz, 1H), 7.79-7.82 (m, 1H), 7.86-7.89 (m, 1H). HRMS (ESI) calcd for $\text{C}_{56}\text{H}_{88}\text{O}_8\text{Si}_2\text{Na}$ 967.5910, found 967.5909.

Figure S1 Further irradiation (365 nm) of **MS-2** followed by standing in the dark resulted in further morphological changes. (Image size $10 \times 10 \mu\text{m}$)

References

- (1) For the synthesis of compound **1** see: G. London, G. T. Carroll, T. F. Landaluce, M. M. Pollard, P. Rudolf, B. L. Feringa, *Chem. Commun.* **2009**, 1712. (Supp. Inf.)

NMR Spectra

^1H -NMR spectrum of the photostationary state ($\lambda = 365\text{ nm}$) of stable-**M1** and unstable-**M1**