University of Groningen

Synthesis of CaCO₃ nanoparticles by carbonation of lime solutions in reverse micellar systems

Heeres, H.J.; Jain, R.; Mehra, A.; Dagaonkar, M.V.

Published in:
Chemical Engineering Research and Design

DOI:
[10.1205/cerd.82.11.1438.52028](https://doi.org/10.1205/cerd.82.11.1438.52028)

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Document Version
Publisher's PDF, also known as Version of record

Publication date:
2004

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Heeres, H. J., Jain, R., Mehra, A., & Dagaonkar, M. V. (2004). Synthesis of CaCO₃ nanoparticles by carbonation of lime solutions in reverse micellar systems. *Chemical Engineering Research and Design*, 82(A11), 1438-1443. <https://doi.org/10.1205/cerd.82.11.1438.52028>

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

SYNTHESIS OF CaCO₃ NANOPARTICLES BY CARBONATION OF LIME SOLUTIONS IN REVERSE MICELLAR SYSTEMS

M. V. DAGAONKAR¹, A. MEHRA², R. JAIN² and H. J. HEERES^{1*}

¹Stratingh Instituut, Chemie and Chemische Technologie, State University of Groningen, Groningen, The Netherlands

²Department of Chemical Engineering, Indian Institute of Technology, Bombay Powai, Mumbai, India

Application of reverse micelles for the synthesis of nano-sized calcium carbonate particles in different solvents (cyclohexane, decane and heptane) has been investigated. The effect of the mole ratio of water-to-surfactant (R) and type of solvent has been studied on the size and nature of the carbonate particles. The results indicate that an increase in water-to-surfactant ratio results in a larger particle size.

Keywords: nanoparticles; calcium carbonate; reverse micellar systems; Ca-OT.

INTRODUCTION

Particulate products possessing specific characteristics are very important in the chemical process industry. Reverse micelles or water-in-oil microemulsions are being explored as a medium for the synthesis of nanoparticles because individual micelles act as nanoreactors/precipitators. The size of the precipitated particles is profoundly affected by the inherent physico-chemical properties of the micellar system as well as by the exchange of material between micelles.

The recipe for obtaining such fine particles usually involves conducting the precipitation in the cores of reverse micelles formed by the dissolution of a surfactant moiety (with and without co-surfactants) in an oil (solvent) phase. In these systems, nanodrops (3–30 nm) of the aqueous phase are trapped within aggregates of surface-active molecules dispersed in an external oil phase. The micellar core contains water plus the dissolved reactant, and the type/concentration of the surfactant, co-surfactant and amount of water present determine the characteristics of the precipitated product. It is necessary for the gaseous solute to enter the micellar core, via the continuous oil phase, in order to react with the aqueous reactant. The reverse micelles provide a cage-like effect that can control nucleation, growth and agglomeration. The solubilized reactant species are effectively distributed in separate nanoreactors at the molecular level. In addition, the ability to vary the size of the micellar core, by simply altering the water to surfactant ratio provides a very convenient handle to control the particle sizes. Ideally, the particles should not grow larger than the polar cores of the reversed micelles,

i.e. the micelle acts as a cage, preventing unlimited growth. However, under real conditions intermicellar exchange of material may lead to formation of particles larger than the core micellar volumes.

Many experimental studies have been undertaken using a reverse micellar system to precipitate nanoparticles. Copper nanoparticles (Pileni, 1997), silver and silver halides (Manna *et al.*, 2001; Dirk *et al.*, 1998; Bagwe and Khilar, 1997; Pileni, 1997), gold (Arcoleo and Liveri, 1996), BaCO₃ (Kandori *et al.*, 1988b), Fe₃O₄, Pt, Pd, Rh, Cu, Fe and Ir (Boutonnet *et al.*, 1982; Blanco *et al.*, 1994), CdSe (Stigerwald *et al.*, 1988), Ni, FeNi (Rivas and Lopez-Quintela, 1990), CdS, ZnS, PbS and Ag₂S (Khiew *et al.*, 2003; Cheng *et al.*, 1998; Hirai *et al.*, 1995; Suzuki *et al.*, 1996; Motte, 1996; Petit *et al.*, 1990; Lianos and Thomas, 1987), metal oxides like ZnO, TiO₂ (Chhabra *et al.*, 1995; Lal *et al.*, 1998; Wang and Li, 1999; Hingorani *et al.*, 1993) have been prepared by such means.

Calcium carbonate particles produced by carbonation of lime solutions or lime slurries are industrially important and find uses in diverse areas such as in the manufacture of tooth-pastes, lubricants, paints, textiles, plastics, adhesives, waste water treatment, rubber, ink and ceramic materials. Preparation of calcium carbonate particles has been reported in various types of reactors, e.g. stirred bubbling tank or column, rotating packed bed reactor (RPBR), Couette-Taylor reactor (Swinney *et al.*, 1982; Yagi *et al.*, 1984a,b; 1988 Wachi and Jones, 1991a,b; Jones *et al.*, 1992; Hostomsky and Jones, 1995; Wei *et al.*, 1997; Jung *et al.*, 2000). Many of these processes apply the concept of gas-liquid reactive precipitation. The particle size using these methods is restricted to the micrometer range. Of special interest is the production of nanoparticles of CaCO₃. Although such particles have been known for a very long time, their preparation has only received some attention in the last two decades, on account of special properties associated with them.

*Correspondence to: Professor H. J. Heeres, Stratingh Instituut, Chemie and Chemische Technologie, State University of Groningen, Nijenborgh 4, 9747 AG Groningen, The Netherlands.
E-mail: H.J.Heeres@chem.rug.nl

Limited information is available in the literature so far for the synthesis of nanoparticles of calcium carbonate particles using reverse micelle technique (Kandori *et al.*, 1987; Kandori *et al.*, 1988a,b; Roman *et al.*, 1991). Kandori *et al.* (1988a,b) absorbed carbon dioxide into swollen reverse micelles of Ca-OT [calcium 1,2-bis-(2-ethylhexyl-oxycarbonyl)-1-ethane sulphonate], whose cores contained pre-dissolved calcium hydroxide. They obtained mean particle sizes of calcium carbonate of 50–125 nm and found that the number of particles to the number of micelles was about 10^{-8} . Micrometer-sized calcium hydroxide particles suspended in reverse micellar solutions were carbonated by Roman *et al.* (1991) to finally obtain carbonate particles of about 6 nm size. Both these experimentally significant studies have given rise to speculations about the mechanism of formation of the carbonate particles. Apart from the usual phenomena of nucleation and growth of the product particles, other mechanisms that are likely to be important in gas-micellar systems are: intermicellar collisions driven by the Brownian motion of the micelles, the subsequent exchange of the contents of the colliding micelles and, for the case of suspended reactant, the solubilization of the reactant into the micellar core by micelle-particle collisions.

There has been some progress in the modelling of these precipitation systems. Nagy (1989) proposed one of the earliest models for the formation of nanoparticles. Hatton *et al.* (1993) have proposed a population balance approach to model the population dynamics of reverse micellar precipitation systems. A more complete modelling of the formation of nanoparticles in reverse micelles was done using population balances (Ramesh *et al.*, 2004; Natarajan *et al.*, 1996) and many experimentally observed trends have been reproduced. Li and Park (1999) carried out Monte Carlo simulations to construct particle size distributions for the synthesis of nanoparticles using reverse micelles assuming instantaneous nucleation and reaction in their model. Tojo *et al.* (1997) also carried out Monte Carlo simulations, using the random walk approach, for systems where the reaction rate is very fast. They have shown the influence of autocatalysis and ripening on the final size distribution of the nanoparticles formed, using film flexibility as a parameter. Bandyopadhyaya *et al.* (2000) removed some of the aforementioned limitations by incorporating a finite nucleation rate in the Monte Carlo models.

Thus, there are very few experimental studies available on gas-liquid and gas-slurry systems. Hence, the present investigation deals with the generation of extensive data for the production of nano-sized particles of CaCO₃. The effect of operating variables such as water-to-surfactant ratio and type of solvent on the particle size distribution has been investigated experimentally.

METHODS AND MATERIALS

Sodium bis-(2-ethylhexyl)-sulphosuccinate or Aerosol-OT (AOT) was purchased from Acros Organics and was used without any further processing. Calcium chloride, calcium hydroxide, methanol, cyclohexane, diethyl ether were used without any further purification. Water used was distilled and deionized. N₂ and CO₂ were supplied by AGA BV, The Netherlands.

Preparation of Surfactant

Ca-OT [calcium 1,2-bis-(2-ethylhexyl-oxycarbonyl)-1-ethane sulphonate] was prepared by the metathesis reaction of methanolic Aerosol-OT and aqueous CaCl₂ as described in the literature (Kandori *et al.*, 1988a,b).

Preparation of the Reverse Micellar Solution

A representative example for the preparation of a reverse micellar solution in cyclohexane is as follows: 0.835 ml of a Ca(OH)₂ solution (0.02 mol l⁻¹, 1.67×10^{-5} mol Ca²⁺, 3.34×10^{-5} mol OH⁻) was added to a solution of Ca-OT (8.82 g, 0.01 mol) in cyclohexane (100 g) at room temperature and stirred well until a clear solution was obtained. This resulted in an *R* value of 4.64 ($R = [\text{H}_2\text{O}]/[\text{Ca-OT}]$). Water was added to the system to set *R* to the desired value. A molar ratio of 1.67×10^{-3} was maintained for Ca(OH)₂ to Ca-OT for each experiment.

Samples of the reverse micellar solution were analysed using dynamic light scattering (DLS) to measure the diameter of the reverse micelles before the carbonation. A Zetasizer 5000 from Malvern Instruments, UK, was used for the measurements. The He-Ne laser operated at 633 nm was used as a light source.

Carbonation Procedure

A volume of 0.1×10^{-3} m³ of the reaction mixture [surfactant + solvent, i.e. cyclohexane-heptane-decane+aqueous Ca(OH)₂] was transferred into a cylindrical bubbler as shown in Figure 1 (capacity = 0.15×10^{-3} m³). The solution was bubbled with N₂ through a metal filter for 20 min to generate an inert atmosphere. The particles of CaCO₃ were prepared by bubbling CO₂ into this reaction mixture for 3 min at 4×10^{-5} m³ min⁻¹. The reaction was stopped by replacing the CO₂ flow with N₂. The amount of CO₂ used was sufficient to obtain a theoretical yield of 100% of CaCO₃ particles in any experiment.

Identification and Size of CaCO₃ Particles

The shape and size of the CaCO₃ particles were measured by a Philips XL30 PEG scanning electron microscope

Figure 1. Experimental set-up for the carbonation experiments (V₁, V₂, V₃ are manually operated valves).

(SEM). The procedure for preparation of the sample is as follows. The reaction mixture was sprayed on a thin film of methanol on a glass plate and was dried under atmospheric conditions until all the solvent was evaporated. The residue was washed with methanol several times to remove the surfactant. The sample was dried again under atmospheric conditions till all the solvent was evaporated. The glass plate was then inserted in the SEM to obtain the images.

SEM-EDAX was applied to determine the elemental composition of the particles. The molar ratio of oxygen to calcium for these samples was found to be about 3:1, suggesting that the particles are indeed composed of CaCO_3 . The presence of calcium carbonate particles was further confirmed by transmission electron microscope (TEM) using a Jeol 2010F field-emission gun. It was operated at 200 kV and was equipped with an EDAX detector with a super ultrathin window for an energy-dispersive X-ray spectrometry and a Gatan imaging filter model 2000 for energy-filtered imaging. The carbonated sample was sprayed onto a glass surface with a carbon grid and then dried under atmospheric conditions. It was then washed several times with methanol and dried again under atmospheric conditions before analysing with TEM.

The size distribution of the particles was determined using a scanning probe image analyser (SPIA). The analyser gave the results in form of the particle number, length, width and the surface area of the particle. The diameter of the individual particle was calculated from the surface area assuming the particles to be spherical. The particle size distribution is based on an average of 100 particles measured during the analysis.

RESULTS AND DISCUSSION

Micellar Solubilization of $\text{Ca}(\text{OH})_2$

To prepare nano-sized CaCO_3 particles, it is essential to have some insight into the factors which determine the solubility of aqueous $\text{Ca}(\text{OH})_2$ in the micellar solutions. Therefore, a small quantity of aqueous $\text{Ca}(\text{OH})_2$ of 0.02 mol kg^{-1} was added to the solvent containing 0.10 mol kg^{-1} Ca-OT. Water was further added to the systems to adjust the molar ratio of water to Ca-OT ($R = [\text{H}_2\text{O}]/[\text{Ca-OT}]$). The solubility of water was measured from the transparency of the solvent at room temperature as a function of amount of water added to the systems. The maximum amount of solubilization of water was found to be dependent on the type of solvent. The value of R at which the solution became turbid was $R = 30$ for cyclohexane and $R = 40$ for heptane and decane. Thus it can be concluded that the operating window for heptane and decane is higher than for cyclohexane.

Formation of Water-in-oil Microemulsions

The size of the reverse micelles is expected to be an important parameter in the process of making CaCO_3 nanoparticles. The micellar size as a function of the mole ratio R ($R = [\text{H}_2\text{O}]/[\text{Ca-OT}]$) was measured in the range $R = 5\text{--}30$ using cyclohexane as the solvent. These experiments were carried out in the presence of $\text{Ca}(\text{OH})_2$. Figure 2 shows the changes in the average diameter of micelle (as calculated from the dynamic light scattering)

Figure 2. The change in D_m with R for CaOT–cyclohexane systems ($T = 298 \text{ K}$, $P = 1 \text{ atm}$, $[\text{Ca-OT}] = 0.10 \text{ mol kg}^{-1}$, $[\text{Ca}(\text{OH})_2]/[\text{Ca-OT}] = 1.67 \times 10^{-3}$).

with R using cyclohexane as a solvent. It is evident that the average micellar diameter increases with the increase in R value. Thus, it is clear that the initial size of the reverse micelle core may be tuned with the R values. This is in accordance with the results provided by Kandori *et al.* (1988a).

Formation of Particles

The actual precipitation reactions were carried out in reverse micellar solutions consisting of a continuous hydrocarbon phase (cyclohexane, heptane or decane) and a dispersed phase consisting of an aqueous $\text{Ca}(\text{OH})_2$ solution stabilized with a surfactant Ca-OT. The precipitation reaction was started by introduction of gaseous CO_2 to the system. All experiments were carried out at room temperature, atmospheric pressure, in a set-up as given in the experimental section (Figure 1). After an experiment, the resulting solution was analysed using SEM.

Typical SEM micrographs of CaCO_3 particles formed are shown in Figures 3 and 4 ($R = 15$ and 30, respectively), using cyclohexane as a solvent. The particles had an average size of 62 nm for the lowest value of R . When the R value was increased, the particle size also increased.

Figure 3. SEM micrograph for Ca-OT–cyclohexane system at $R = 15$.

Figure 4. SEM micrograph for Ca-OT-cyclohexane system at $R = 30$.

At $R = 30$, particles of an average size of 194 nm were formed. Also at $R = 30$, particle agglomerates of the carbonate particles can be seen. The average diameters of the particles are summarised in Table 1 together with the values of the micellar diameter. The graphical illustration is presented in Figure 5.

It is of interest to compare the size of the initial micelle with the particle size at the end of the experiment. It can be concluded that the size of the particles is much larger

Table 1. Sizes of reverse micelles and CaCO₃ particles in Ca-OT-cyclohexane systems ($[Ca-OT] = 0.10 \text{ mol kg}^{-1}$, $[Ca(OH)_2]/[Ca-OT] = 1.67 \times 10^{-3}$).

R	$D_m \text{ (nm)}$	$D_p \text{ (nm)}$
5	13	62
10	16	68
15	16	101
20	20	137
25	23	173
30	30	194

Figure 5. Effect of the water-to-surfactant mole ratio on the size of the carbonated particles for Ca-OT-cyclohexane systems ($T = 298 \text{ K}$, $P = 1 \text{ atm}$, $[Ca-OT] = 0.10 \text{ mol kg}^{-1}$, $[Ca(OH)_2]/[Ca-OT] = 1.67 \times 10^{-3}$).

than the initial size of the reverse micelle. Various explanations are possible for these observations, such as intermicellar exchange of material and/or agglomeration of already formed particles. However, more data and modeling activities will be required for a definite conclusion. Similar observations have been also reported by Kandori *et al.* (1987, 1988a). Figures 6 and 7 represent the particle size distribution of the carbonate particles at different R . The particle size distribution of the carbonate particles has not been reported elsewhere for this system and this is the first study to do so. Kandori *et al.* (1988a) have reported the values of the particle size in the range of 48–120 nm for R ranging from 5 to 30 at similar surfactant loading.

Effect of the Properties of the Continuous Phase on the Carbonation Process

The effect of the physical properties of the continuous oil phase on the formation of the carbonate particles has not been studied before. CaCO₃ nanoparticles were prepared in Ca-OT microemulsions with cyclohexane, heptane and

Figure 6. Particle size distribution for calcium carbonate nanoparticles in the Ca-OT-cyclohexane system at $R = 15$.

Figure 7. Particle size distribution for calcium carbonate nanoparticles in the Ca-OT-cyclohexane system at $R = 30$.

Table 2. Average particle size of the CaCO₃ particles at different water-to-surfactant ratio (*R*).

<i>R</i>	Particle diameter (nm)		
	Cyclohexane	Heptane	Decane
5	62	25	43
10	68	42	71
15	101	57	81
20	137	72	92
25	173	88	114
30	194	167	125

decane as the continuous oil phase. The average diameters of the particles are summarised in Table 2 for all the solvents. It was observed that the particles produced in heptane and decane were smaller in size as compared with those in cyclohexane (see Table 2). For instance, at *R* = 25, the average size of the carbonate particles was 88 nm using heptane and 114 nm using decane compared with 173 nm using cyclohexane. In all cases, it was found that the size of the particles increased with the increase in water-to-surfactant mole ratio. It was observed that agglomerates were formed at higher ranges of *R* and their size increased with *R*. The size distributions obtained for various solvents are similar in nature to the typical ones shown for cyclohexane. The experimental data suggest that particle size variation by changing the solvent is possible and is a valuable tool to tune the particle sizes of the product.

CONCLUSIONS

This work deals with the synthesis of nanoparticles of CaCO₃ using CO₂ gas and Ca(OH)₂ as the reactants. The reverse micellar solution was prepared using a continuous oil phase (cyclohexane, heptane or decane), a surfactant (Ca-OT) and the aqueous Ca(OH)₂ solution. Carbonation experiments were carried out at fixed hydroxide-to-surfactant ratio and fixed surfactant concentration. The effect of change in water-to-surfactant ratio and the solvent was studied for the synthesis nanoparticles of calcium carbonate. The size of the reverse micelles before the addition of CO₂ was determined and found to be about 10–25 nm using cyclohexane. An increase in the *R* value resulted in an increase in the particle size. Values of *R* higher than 30 were not attainable due to the formation of turbid solutions. The value of *R* depended on the solvent applied. The solutions became turbid at *R* = 40 using heptane and decane. Carbonation experiments indicate that an increase in the water-to-surfactant ratio results in an increase in the size of the for all three solvents used. The particles produced in heptane and decane were smaller in size as compared with those in cyclohexane. The experimental data obtained in this study may be used to validate theoretical models for the production of nanoparticles in reverse micellar solutions.

NOMENCLATURE

<i>D_m</i>	micellar diameter (nm)
<i>D_p</i>	particle diameter (nm)
<i>R</i>	molar ratio of water to Ca-OT (mol mol ⁻¹)

REFERENCES

- Arcoletto, V. and Liveri, V.T., 1996, AFM investigation of gold nanoparticles synthesized in water/AOT/n-heptane microemulsions, *Chem Phys Lett*, 258: 223–227.
- Bagwe, R.P. and Khilar, K.C., 1997, Effects of intermicellar exchange rate and cations on the size of silver chloride nanoparticles formed in reverse micelles of AOT, *Langmuir*, 13: 6432–6438.
- Bandyopadhyaya, R., Kumar, R., Gandhi, K.S. and Ramakrishna, D., 2000, Simulation of precipitation reactions in reverse micelles, *Langmuir*, 16: 7139–7149.
- Blanco, M.C., Meira, A., Baldomir, D., Rivas, J. and Quintela, M.A.L., 1994, UV–VIS spectra of small iron particles, *IEEE Trans Magn*, 30: 739–741.
- Boutonnet, M., Kizling, J., Stenius, P. and Marie, G., 1982, The preparation of monodisperse colloidal metal particles from microemulsions, *Colloid Surfaces*, 5: 209–225.
- Chhabra, V., Pillai, V., Mishra, B.K., Morrone, A. and Shah, D.O., 1995, Synthesis, characterization, and properties of microemulsion-mediated nanophase TiO₂ particles, *Langmuir*, 11: 3307–3311.
- Cheng, G.X., Shen, F., Yang, L.F., Ma, L.R., Tang, Y., Yao, K.D. and Sun, P.D., 1998, On properties and structure of the AOT–water–isooctane reverse micellar microreactor for nanoparticles, *Mater Chem Phys*, 56: 97–101.
- Dirk, L., Hyning, V. and Zukoski, C.F., 1998, Formation mechanisms and aggregation behaviour of borohydride reduced silver particles, *Langmuir*, 14(24): 7034.
- Hatton, T.A., Bommarius, A.S. and Holzwarth, J.F., 1993, Population dynamics of small systems. 1. Instantaneous and irreversible reactions in reversed micelles, *Langmuir*, 9(5): 1241–1253.
- Hingorani, S., Pillai, V., Kumar, P., Multani, M.S. and Shah, D.O., 1993, Microemulsion mediated synthesis of zinc-oxide nanoparticles for varistor studies, *Mater Res Bull*, 28: 1303–1310.
- Hirai, T., Sato, H. and Komazawa, I., 1995, Mechanism of formation of composite CdS–ZnS ultrafine particles in reverse micelles, *Ind Eng Chem Res*, 34: 2493–2498.
- Hostomsky, J. and Jones, A.G., 1995, A penetration model of the gas–liquid reactive precipitation of calcium carbonate crystals, *Trans IChemE*, 73(Part A): 241–245.
- Jones, A.G., Hostomsky, J. and Li, Z., 1992, On the effect of liquid mixing rate on primary crystal size during the gas–liquid precipitation of calcium carbonate, *Chem Eng Sci*, 47(13/14): 3817–3824.
- Jung, W.M., Kang, S.H., Kim, W.S. and Choi, C.K., 2000, Particle morphology of calcium carbonate precipitated by gas–liquid reaction in a Couette–Taylor reactor, *Chem Eng Sci*, 55: 733–747.
- Kandori, K., Shizuka, N., Ko-No, K. and Kitahara, A., 1987, Preparation of CaCO₃ particles in water pool in nonionic surfactant solutions, *J Disp Sci Technol*, 8(5–6): 477–491.
- Kandori, K., Ko-No, K. and Kitahara, A., 1988a, Formation of ionic water/oil microemulsions and their application in the preparation of CaCO₃ particles, *J Coll Interf Sci*, 122(1): 78–82.
- Kandori, K., Ko-No, K. and Kitahara, A., 1988b, Preparation of BaCO₃ particles in ionic w/o microemulsions, *J Disp Sci Technol*, 9(1): 61–73.
- Khiew, P.S., Radiman, S., Huang, N.M. and Soot Ahmad, Md., 2003, Studies on the growth and characterization of CdS and PbS nanoparticles using sugar–ester nonionic water–oil microemulsion, *J Crystal Growth*, 254: 235–243.
- Lal, M., Chhabra, V., Ayyub, P. and Maitra, A., 1998, Preparation and characterization of ultrafine TiO₂ particles in reverse micelles by hydrolysis of titanium di-ethylhexylsulfosuccinate, *J Mater Res*, 3(5): 1249–1254.
- Li, Y. and Park, C.W., 1999, Particle size distribution in the synthesis of nanoparticles using microemulsions, *Langmuir*, 15: 952–956.
- Lianos, P. and Thomas, J.K., 1987, Small CdS particles in inverted micelles, *J Colloid Interface Sci*, 117(2): 505–512.
- Motte, L., 1996, Synthesis in situ of nanosize silver sulfide semiconductor particles in reverse micelles, *J Mater Sci*, 31: 38.
- Manna, A., Imae, T., Iida, M. and Hitamatsu, N., 2001, Formation of silver nanoparticles from a *N*-hexadecylethylenediamine silver nitrate complex, *Langmuir*, 17(19): 6000–6004.
- Nagy, J.B., 1989, Multinuclear NMR characterization of microemulsions: preparation of monodisperse colloidal metal boride particles, *Colloid Surf*, 35(1): 201–220.
- Natarajan, U., Handique, K., Mehra, A., Bellare, J.R. and Khilar, K.C., 1996, Ultrafine metal particle formation in reverse micellar systems: effects of intermicellar exchange on the formation of particles, *Langmuir*, 12: 2670–2678.

- Petit, C., Lixon, P. and Pileni, M.P., 1990, Synthesis of CdS *in situ* in reverse micelles 2. Influence of the interface on the growth of the particles, *J Phys Chem*, 94: 1598–1603.
- Pileni, M.P., 1997, Nanosized particles made in colloidal assemblies, *Langmuir*, 13: 3266–3276.
- Ramesh, A.K., Hota, G., Mehra, A. and Khilar, K.C., 2004, Modeling of nanoparticles formation by mixing of two reactive microemulsions, *AIChE J*, 50: 1556–1567.
- Rivas, J. and Lopez-Quintela, M.A., 1990, *Structure, Dynamics and Equilibrium Properties of Colloidal Systems*, Wyn-Jones, E. and Bloor, D. (eds) (Kluwer, Dordrecht).
- Roman, J.P., Hoornaert, P., Faure, D., Biver, C., Jacquet, F. and Martin, J.M., 1991, Formation and structure of carbonate particles in reverse microemulsion, *J Colloid Interf Sci*, 144(2): 324–339.
- Stigerwald, M.L., Alivisatos, A.P., Gibson, J.M., Harris, T.D., Kortan, R. and Muller, A.J., 1988, Surface derivatization and isolation of semiconductor cluster molecules, *J Am Chem Soc*, 110: 3046–3050.
- Suzuki, K., Harada, M. and Shioi, A., 1996, Growth mechanism of CdS ultrafine particles in water in oil microemulsion, *J Chem Eng Japan*, 29: 264–276.
- Swinney, L.D., Stevens, J.D. and Peters, R.W., 1982, Calcium carbonate crystallization kinetics, *Ind Eng Chem Fundam*, 21: 31–36.
- Tojo, C., Blanco, M.C. and Lopez-Quintela, M.A., 1997, Preparation of nanoparticles in microemulsions: a Monte Carlo study of the influence of the synthesis variables, *Langmuir*, 13: 4527–4234.
- Wachi, S. and Jones, A.G., 1991a, Mass transfer with chemical reaction and precipitation, *Chem Eng Sci*, 46(4): 1027–1033.
- Wachi, S. and Jones, A.G., 1991b, Effect of gas–liquid mass transfer on crystal size distribution during the batch precipitation of calcium carbonate, *Chem Eng Sci*, 46(12): 3289–3293.
- Wang, G.H. and Li, G.H., 1999, Synthesis of nanometer-sized TiO₂ particles by a microemulsion method, *Nanostructured Mater*, 11(5): 663–668.
- Wei, S.H., Mahuli, S.K., Agnihotri, R. and Fan, L.S., 1997, High surface area calcium carbonate: pore structural properties and sulfation characteristics, *Ind Eng Chem Res*, 36: 2141–2148.
- Yagi, H., Okamoto, K., Naka, K. and Hikita, H., 1984a, Chemical absorption of CO₂ and SO₂ into Ca(OH)₂ slurry, *Chem Eng Commun*, 26: 1–9.
- Yagi, H., Iwazawa, A., Sonebe, R., Matsubara, T. and Hikita, H., 1984b, Crystallization of calcium carbonate accompanying chemical absorption, *Ind Eng Chem Fundam*, 23: 153–158.
- Yagi, H., Nagashima, S. and Hikita, H., 1988, Semibatch precipitation accompanying gas–liquid reaction, *Chem Eng Commun*, 65: 109–119.

ACKNOWLEDGEMENT

We would like to thank the Nederlandse Organisatie voor Wetenschappelijk Onderzoek (NWO) for providing financial support to A.M. for a three month research visit to the University of Groningen.

The manuscript was received 25 February 2004 and accepted for publication after revision 3 September 2004.