

University of Groningen

## Catalytic Methane Combustion in Microreactors

He, Li

DOI:  
[10.33612/diss.131751231](https://doi.org/10.33612/diss.131751231)

**IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.**

*Document Version*  
Publisher's PDF, also known as Version of record

*Publication date:*  
2020

[Link to publication in University of Groningen/UMCG research database](#)

*Citation for published version (APA):*  
He, L. (2020). *Catalytic Methane Combustion in Microreactors*. University of Groningen.  
<https://doi.org/10.33612/diss.131751231>

### Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

### Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

# **Catalytic Methane Combustion in Microreactors**

**Li He**



university of  
 groningen

faculty of science  
 and engineering



UNIVERSITÉ DE NANTES



Engineering and Technology institute Groningen



The work described in this thesis was conducted at University of Groningen (Department of Chemical Engineering), the Netherlands and Université de Nantes (Laboratoire de Thermique et Energie de Nantes), France.

This doctoral project was financially supported by University of Groningen in the Netherlands and Region Pays de la Loire in France (Chaire Connect Talent ODE).

Cover design: Li He, background picture is downloaded from [www.shutterstock.com](http://www.shutterstock.com)

Print: ProefschriftMaken

Copyright©Li He, 2020. All rights reserved.



university of  
 groningen



UNIVERSITÉ DE NANTES

# Catalytic Methane Combustion in Microreactors

## PhD thesis

to obtain the degree of PhD at the  
University of Groningen  
on the authority of the  
Rector Magnificus Prof. C. Wijmenga  
and in accordance with  
the decision by the College of Deans

and

to obtain the degree of PhD of  
Université de Nantes  
on the authority of the  
President Prof. Carine Bernault  
and in accordance with  
the decision by the College of Deans.

Double PhD degree

This thesis will be defended in public on

04 September 2020 at 11:00 hours

by

**Li He**

born on 19 June 1986

in Liaoning, China

## **Supervisors**

Prof. J. Yue  
Prof. H.J. Heeres  
Prof. L. Luo  
Prof. J. Bellettre

## **Assessment Committee**

Prof. F. Picchioni  
Prof. W. de Jong  
Prof. J.M. Commenge  
Prof. J. Legrand

Dedicated to my beloved family.

谨以此书献给我亲爱的家人



# Table of contents

<b>Abstract</b> .....	<b>I</b>
<b>Chapter 1. Aim and scope of the thesis</b> .....	<b>1</b>
1.1. Research objective.....	2
1.2. Thesis outline .....	3
<b>Chapter 2. A review on catalytic methane combustion at low temperatures: catalyst, mechanisms, reaction conditions and reactor designs</b> .....	<b>5</b>
2.1. Introduction .....	7
2.2. Catalysts for methane combustion.....	13
2.2.1 Catalyst category .....	13
2.2.2 Shaping of catalyst.....	17
2.3. Mechanism and kinetic study of CMC .....	19
2.4. Effect of operational conditions on CMC .....	23
2.4.1. Effect of temperature.....	23
2.4.2. Effect of space velocity and residence time .....	25
2.4.3. Effect of oxygen to methane molar ratio .....	26
2.4.4. Effect of (synthetic) natural gas composition.....	28
2.4.5. Effect of operating pressure .....	30
2.5. Types of catalytic reactors .....	46
2.5.1. Fixed-bed reactor .....	46
2.5.2. Wall-coated reactor .....	48
2.5.3. Membrane reactor .....	55
2.5.4. Fluidized bed reactor .....	56
2.6. Summary and prospect.....	65
References .....	67
<b>Chapter 3. Preparation of Pt/<math>\gamma</math>-Al<sub>2</sub>O<sub>3</sub> catalyst coating in microreactors for catalytic methane combustion</b> .....	<b>79</b>
3.1. Introduction .....	82
3.2. Experimental .....	85
3.2.1. Materials .....	85
3.2.2. Catalyst preparation .....	86
3.2.3. Washcoat adhesion test.....	88
3.2.4. Catalytic methane combustion in microreactors .....	88
3.2.5. Analytical procedure.....	89
3.2.6. Definitions.....	90
3.3. Results and discussion .....	90
3.3.1. Effect of preparation procedures on the washcoat adhesion .....	90
3.3.2. Catalytic methane combustion over the coated Pt/ $\gamma$ -Al <sub>2</sub> O <sub>3</sub> catalyst in the multi-channel microreactor .....	105
3.4. Conclusions .....	112
Appendix 3.A.....	113
Appendix 3.B.....	113
Appendix 3.C .....	115
Appendix 3.D.....	115
Appendix 3.E .....	116
References .....	118
<b>Chapter 4. Capillary microreactors with single- and multi-layer Pt/<math>\gamma</math>-Al<sub>2</sub>O<sub>3</sub> catalyst coatings for catalytic methane combustion</b> .....	<b>123</b>
4.1. Introduction .....	126



4.2. Experimental .....	129
4.2.1. Materials .....	129
4.2.2. Catalyst preparation and coating procedures .....	129
4.2.3. Catalytic methane combustion in microreactors .....	133
4.2.4. Analytics.....	134
4.2.5. Definitions.....	135
4.2.6. Error analysis.....	136
4.3. Results and discussion .....	136
4.3.1. Reaction performance of the single-layer Pt/ $\gamma$ -Al <sub>2</sub> O <sub>3</sub> catalyst system.....	136
4.3.2. Reaction performance of the multi-layer Pt/ $\gamma$ -Al <sub>2</sub> O <sub>3</sub> catalyst system.....	146
4.3.3. Catalyst stability .....	151
4.4. Conclusions .....	153
Appendix 4.A.....	154
Appendix 4.B.....	155
Appendix 4.C .....	156
References .....	158
<b>Chapter 5. Catalytic methane combustion in plate-type microreactors with different channel configurations: an experimental study .....</b>	<b>163</b>
5.1. Introduction.....	166
5.2. Experimental .....	169
5.2.1. Experimental setup and procedures .....	169
5.2.2. Reactor design and fabrication .....	170
5.2.3. Catalyst preparation and coating procedures .....	172
5.2.4. Analytical procedure.....	174
5.2.5. Definitions.....	175
5.3. Results and discussion .....	176
5.3.1. CMC performance of the straight parallel channel microreactor.....	176
5.3.2. Comparison of the CMC performance in microreactors with different internal channel configurations .....	184
5.4. Conclusions and prospects.....	194
Appendix 5.A.....	195
References.....	198
<b>Chapter 6. Catalytic methane combustion: conclusions, challenges and future prospects.....</b>	<b>203</b>
6.1. Summary of the current thesis .....	204
6.2. Short-term research work as a continuation of the current thesis.....	206
6.2.1. Noble metal catalyst.....	206
6.2.2. Coating preparation .....	207
6.2.3. Catalyst deactivation.....	208
6.2.4. Kinetics and mechanisms .....	210
6.2.5. Mass transfer characterization .....	210
6.2.6. Partial methane oxidation .....	211
6.3. Future prospects for long term research.....	211
6.3.1. Catalysts .....	211
6.3.2. Catalytic methane combustion coupling with endothermic reactions .....	212
References.....	216
<b>Samenvatting .....</b>	<b>221</b>
<b>Résumé.....</b>	<b>225</b>
<b>Acknowledgements.....</b>	<b>229</b>
<b>List of publications .....</b>	<b>233</b>
<b>List of attended conferences.....</b>	<b>234</b>

## *Abstract*

The current thesis deals with the catalytic methane combustion in microreactors with wall-coated Pt/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub> catalyst. The Pt/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub> washcoat preparation, the single- and multi-layer catalytic coating systems, and the different designs of microreactor geometries were particularly investigated. Various aspects were thus addressed, including the preparation procedures of the catalyst coating (e.g., the binder properties, pH value, initial Al<sub>2</sub>O<sub>3</sub> particle size), the optimization of different reaction conditions with single- and multi-layer coating systems (e.g., temperature, flow rate, O<sub>2</sub>/CH<sub>4</sub> molar ratio, Pt loading and coating thickness), the effect of internal channel configurations in the microreactor (i.e., involving straight parallel channels, cavity, double serpentine channels, obstructed parallel channels, meshed circuit and vascular network) on the reaction performance.

The thesis starts with a comprehensive literature review on the catalytic methane combustion at low temperatures, including catalyst, mechanisms, reaction conditions and reactor designs. Then, the preparation procedures of Pt/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub> washcoat catalyst have been studied in details, in order to improve its adhesion and uniformity on FeCrAlloy and stainless steel microreactors. A good adhesion could be obtained by using the slurry with 20 wt%  $\gamma$ -Al<sub>2</sub>O<sub>3</sub> (particle size: 3  $\mu$ m), pH = 3.5, and 3 to 5 wt% polyvinyl alcohol (molecular weight of 57,000 - 186,000). Based on the above-mentioned optimized preparation, Pt/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub> washcoat catalysts of various loadings were deposited inside the stainless-steel capillary microreactors and studied both in the single- and multi-layer catalytic coating systems. The influence of different operating conditions including the reaction temperature, total flow rate, molar ratio of O<sub>2</sub>:CH<sub>4</sub>, and the reproducibility of catalyst were tested. The results demonstrate that in general the methane conversion was improved

with the temperature rise, and presented the highest at an oxygen to methane molar ratio of ca.1.5. An obvious decrease in the methane conversion could be found over the multi-layer systems compared to their respective single-layer counterparts (if the Pt mass in the catalyst was kept equal), due to the more significant internal diffusion limitation in thicker coatings. Among all the tested microreactor geometries washcoated with Pt/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub> catalyst, the highest methane conversion could be obtained in the double serpentine channel microreactor and the lowest presented in the mesh circuit microreactor, which can be explained based on the available coating surface area, flow distribution and residence time property. In order to achieve a desirable methane conversion in microreactors, a proper tuning of the catalytic coating properties (e.g., surface area, Pt loading and thickness), the residence time, the fluid distribution uniformity and other reaction parameters (e.g., temperature and oxygen to methane molar ratio) are required.

**Keywords:** Catalytic methane combustion; Pt/ $\gamma$ -Al<sub>2</sub>O<sub>3</sub> catalyst; microreactor; coating; mass transfer