

University of Groningen

## Electron spin transport in quantum dots and point contacts

Koop, Erik Johan

**IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.**

*Document Version*

Publisher's PDF, also known as Version of record

*Publication date:*

2008

[Link to publication in University of Groningen/UMCG research database](#)

*Citation for published version (APA):*

Koop, E. J. (2008). *Electron spin transport in quantum dots and point contacts*. s.n.

### Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

### Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

*Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.*

# Appendix A

## Wafer inventory

In this Appendix we present the various heterostructures used in this thesis. All values for density and mobility were measured at 4.2 K with samples cooled down in the dark. We present the layer structure from top down.

### A.1 WSUMI301612

This wafer was purchased from Sumitomo Electric Industries, Ltd. Devices from this wafer were used for experiments on quantum fluctuations in the non-local resistance in Chapter 6 and for studies on ohmic contact formation to a 2DEG in Chapter 7. Quantum point contacts fabricated on this wafer never showed any sign of spin splitting in a large in-plane magnetic field.

- 2DEG depth: 75 nm
- Density:  $2.78 \times 10^{15} \text{ m}^{-2}$
- Mobility:  $19.5 \text{ m}^2/\text{Vs}$
- Layer structure:
  - 5 nm GaAs
  - 40 nm  $\text{Al}_{0.27}\text{Ga}_{0.73}\text{As}$  (n-doped with Si at  $2 \times 10^{18} \text{ cm}^{-3}$ )
  - 30 nm  $\text{Al}_{0.27}\text{Ga}_{0.73}\text{As}$
  - 800 nm GaAs

## A.2 WREUT1098

This wafer was grown in the group of D. Reuter and A. D. Wieck at the Ruhr-Universität in Bochum, Germany. Devices from this wafer were used for experiments on point contacts and quantum dots in Chapters 3 and 4, and for studies on ohmic contact formation to a 2DEG in Chapter 7.

- 2DEG Depth: 114 nm
- Density:  $1.5 \times 10^{15} \text{ m}^{-2}$
- Mobility:  $159 \text{ m}^2/\text{Vs}$
- Layer structure:
  - 5.5 nm GaAs
  - 71.9 nm  $\text{Al}_{0.32}\text{Ga}_{0.68}\text{As}$  (n-doped with Si at  $1 \times 10^{18} \text{ cm}^{-3}$ )
  - 36.8 nm  $\text{Al}_{0.32}\text{Ga}_{0.68}\text{As}$
  - 933 nm GaAs

## A.3 WREUT12570

This wafer was grown in the group of D. Reuter and A. D. Wieck at the Ruhr-Universität in Bochum, Germany. Devices from this wafer were used only for studies on ohmic contact formation to a 2DEG in Chapter 7.

- 2DEG Depth: 180 nm
- Density:  $4.54 \times 10^{15} \text{ m}^{-2}$
- Mobility:  $22.9 \text{ m}^2/\text{Vs}$
- Layer structure:
  - 5 nm GaAs
  - 70 nm  $\text{Al}_{0.35}\text{Ga}_{0.65}\text{As}$
  - 70 nm  $\text{Al}_{0.35}\text{Ga}_{0.65}\text{As}$  (n-doped with Si at  $1 \times 10^{18} \text{ cm}^{-3}$ )
  - 35 nm  $\text{Al}_{0.35}\text{Ga}_{0.65}\text{As}$
  - 650 nm GaAs

# Appendix B

## Device fabrication

In this Appendix we will describe the fabrication procedure for the devices that were used in this thesis.

### B.1 Alignment markers

- Preparation:
  - Clean in boiling acetone (10')
  - Rinse in IPA (30")
  - Spin dry
- Resist:
  - Spin 250 nm 950K PMMA (4% in Chlorobenzene) - 4000 rpm (60")
  - Bake at 180 °C (15')
- Exposure:
  - Beam voltage: 10 keV
  - Aperture: 10  $\mu\text{m}$
  - Working area: 200 x 200  $\mu\text{m}$
  - E-beam dose: 200  $\mu\text{C}/\text{cm}^2$
- Developing:
  - Develop in 1:3 MIBK / IPA (60")
  - Rinse in IPA (30")

- Spin dry
- Evaporation:
  - 5 nm Ti
  - 50 nm Au
- Lift-off:
  - Lift-off in acetone (several hours) / acetone spray
  - Rinse in IPA (30'')
  - Spin dry

## B.2 Mesa etching

- Preparation:
  - Clean in boiling acetone (10')
  - Rinse in IPA (30'')
  - Spin dry
- Resist:
  - Spin 70 nm 950K PMMA (2% in Ethyl lactate) - 4000 rpm (60'')
  - Bake at 180 °C (15')
- Exposure:
  - Beam voltage: 10 keV
  - Aperture: 120  $\mu\text{m}$
  - Working area: 2000 x 2000  $\mu\text{m}$
  - E-beam dose: 150  $\mu\text{C}/\text{cm}^2$
- Developing:
  - Develop in 1:3 MIBK / IPA (35'')
  - Rinse in IPA (30'')
  - Spin dry

- Etching:
  - Etch in a 1:1:50 solution of  $H_2SO_4 / H_2O_2 / H_2O$  (50"). The etching rate is approximately 2 nm/s
  - Rinse in  $H_2O$  (30")
  - Spin dry
- Cleaning:
  - Clean in boiling acetone (10')
  - Rinse in IPA (30")
  - Spin dry

### B.3 Ohmic contacts

- Preparation:
  - Clean in boiling acetone (10')
  - Rinse in IPA (30")
  - Spin dry
- Resist:
  - Spin 400 nm 50K PMMA (9% in Chlorobenzene) - 4000 rpm (60")
  - Bake at 180 °C (15')
  - Spin 70 nm 950K PMMA (2% in Ethyl lactate) - 4000 rpm (60")
  - Bake at 180 °C (15')
- Exposure:
  - Beam voltage: 10 keV
  - Aperture: 120  $\mu\text{m}$
  - Working area: 2000 x 2000  $\mu\text{m}$
  - E-beam dose: 200  $\mu\text{C}/\text{cm}^2$
- Developing:
  - Develop in 1:3 MIBK / IPA (60")

- Rinse in IPA (30")
- Spin dry
- Evaporation:
  - 120nm AuGe
  - 30nm Ni
  - 20nm Au
- Lift-off:
  - Lift-off in acetone (several hours) / acetone spray
  - Rinse in IPA (30")
  - Spin dry
- Annealing:
  - Anneal in  $N_2$  atmosphere (50 ml/s) in the oven at 450 °C for typically 5 minutes (see Chapter 7 for more details)

## B.4 Fine gates

- Preparation:
  - Clean in boiling acetone (10')
  - Rinse in IPA (30")
  - Spin dry
- Resist:
  - Spin 70 nm 950K PMMA (2% in Ethyl lactate) - 4000 rpm (60")
  - Bake at 180 °C (15')
- Exposure:
  - Beam voltage: 30 keV
  - Aperture: 10  $\mu\text{m}$
  - Working area: 200 x 200  $\mu\text{m}$

- E-beam dose:  $450 \mu\text{C}/\text{cm}^2$
- Developing:
  - Develop in 1:3 MIBK / IPA (35")
  - Rinse in IPA (30")
  - Spin dry
- Evaporation:
  - 5 nm Ti
  - 15 nm Au
- Lift-off:
  - Lift-off in acetone (overnight) / acetone spray
  - Rinse in IPA (30")
  - Spin dry

## B.5 Large gates

- Preparation:
  - Clean in boiling acetone (10')
  - Rinse in IPA (30")
  - Spin dry
- Resist:
  - Spin 400 nm 50K PMMA (9% in Chlorobenzene) - 4000 rpm (60")
  - Bake at 180 °C (15')
  - Spin 70 nm 950K PMMA (2% in Ethyl lactate) - 4000 rpm (60")
  - Bake at 180 °C (15')
- Exposure:
  - Beam voltage: 10 keV
  - Aperture: 120  $\mu\text{m}$



- Working area: 2000 x 2000  $\mu\text{m}$
- E-beam dose: 200  $\mu\text{C}/\text{cm}^2$
- Developing:
  - Develop in 1:3 MIBK / IPA (60")
  - Rinse in IPA (30")
  - Spin dry
- Evaporation:
  - 5 nm Ti
  - 150 nm Au
- Lift-off:
  - Lift-off in acetone (several hours) / acetone spray
  - Rinse in IPA (30")
  - Spin dry