

University of Groningen

Effects of carbon content and argon flow rate on the triboperformance of self-lubricating WS₂/a-C sputtered coating

Cao, Huatang; De Hosson, J.T.M.; Pei, Yutao T.

IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.

Publication date:
2017

[Link to publication in University of Groningen/UMCG research database](#)

Citation for published version (APA):

Cao, H., De Hosson, J. T. M., & Pei, Y. T. (2017). *Effects of carbon content and argon flow rate on the triboperformance of self-lubricating WS₂/a-C sputtered coating*. Abstract from 44th Int. Conference on Metallurgical Coatings and Thin Films, San Diego, United States.

Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

Effects of carbon content and argon flow rate on the triboperformance of self-lubricating WS₂/a-C sputtered coating

H.T. Cao^{1*}, *J.Th.M De Hosson*² and *Y.T. Pei*¹

1. Department of Advanced Production Engineering, Engineering and Technology Institute Groningen, Faculty of Mathematics and Natural Science, University of Groningen, 9747 AG Groningen, The Netherlands.
2. Department of Applied Physics, Zernike Institute of Advanced Materials, Faculty of Mathematics and Natural Science, University of Groningen, 9747 AG Groningen, The Netherlands.

Huatang.cao@rug.nl

Abstract

Layered transition metal dichalcogenides (TMD) such as WS₂ are materials well-known for their solid lubrication properties^[1]. However, the lubricating property degrades through oxidation or moisture and it is also limited by its low hardness and low load-bearing capacity. In contrast amorphous diamond-like carbon (DLC) films are reported to have many features that contribute to excellent tribological characteristics, such as high hardness, anti-wear property with both low friction coefficient and low wear rate^[2]. The present research aims at depositing WS₂/a-C nanocomposite coatings by magnetron co-sputtering method. The effects of carbon content and argon flow rate on the microstructure and mechanical performance were investigated. The WS₂/a-C nanocomposite tribocoating was scrutinized by electron microscopy and mechanical testing. Transmission electron microscopy reveals feathery WS₂ platelets, randomly distributed in the amorphous carbon matrix. The nanocomposite coating turns out to be more amorphous-like with increasing carbon content. Nanoindentations tests show that the hardness and elastic modulus of the coating increase with increasing carbon addition while decreasing with a higher argon flow from 10 sccm to 25 sccm.

Ball-on-disk tribotests (100Cr6 steel ball as a counterpart) show that the coefficient of friction can be as low as 0.017 in a dry environment (5% relative humidity). It reaches 0.15 in a high humidity surrounding and remains stable within 20000 sliding cycles.

References:

1. S. Prasad, J. Zabinski. Super slippery solids, *Nature* 387, 761-763(1997).
2. A. Nossa, A. Cavaleiro, N.J.M. Carvalho, B.J. Kooi, and J.Th.M. De Hosson, On the microstructure of tungsten disulfide films alloyed with carbon and nitrogen, *Thin Solid Films* 484 (1-2), 389-395(2005).