

University of Groningen

## Properties of organic-inorganic hybrids

Kamminga, Machteld Elizabeth

**IMPORTANT NOTE: You are advised to consult the publisher's version (publisher's PDF) if you wish to cite from it. Please check the document version below.**

*Document Version*

Publisher's PDF, also known as Version of record

*Publication date:*

2018

[Link to publication in University of Groningen/UMCG research database](#)

*Citation for published version (APA):*

Kamminga, M. E. (2018). *Properties of organic-inorganic hybrids: Chemistry, connectivity and confinement*. [Thesis fully internal (DIV), University of Groningen]. Rijksuniversiteit Groningen.

### Copyright

Other than for strictly personal use, it is not permitted to download or to forward/distribute the text or part of it without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license (like Creative Commons).

The publication may also be distributed here under the terms of Article 25fa of the Dutch Copyright Act, indicated by the "Taverne" license. More information can be found on the University of Groningen website: <https://www.rug.nl/library/open-access/self-archiving-pure/taverne-amendment>.

### Take-down policy

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Downloaded from the University of Groningen/UMCG research database (Pure): <http://www.rug.nl/research/portal>. For technical reasons the number of authors shown on this cover page is limited to 10 maximum.

---

## Structures Deposited in the Crystallographic Database

---

The following crystal structures are deposited in the Cambridge Structural Database (CSD) of the Cambridge Crystallographic Data Center (CCDC) and can be obtained from [www.ccdc.cam.ac.uk](http://www.ccdc.cam.ac.uk).

1. $(\text{C}_6\text{H}_5(\text{CH}_2)_4\text{NH}_3)_3\text{Pb}_2\text{I}_7$	100(2) K	$P\bar{1}$	CCDC 1493133
2. $(\text{C}_6\text{H}_5(\text{CH}_2)_3\text{NH}_3)_3\text{Pb}_2\text{I}_7$	100(2) K	$Pca2_1$	CCDC 1493134
3. $(\text{C}_6\text{H}_5\text{CH}_2\text{NH}_3)_2\text{PbI}_4$	100(2) K	$Pbca$	CCDC 1493135
4. $(\text{CH}_3\text{NH}_3)_3\text{Bi}_2\text{I}_9$	300(2) K	$P6_3/mmc$	CCDC 1530227
5. $(\text{CH}_3\text{NH}_3)_3\text{Bi}_2\text{I}_9$	160(2) K	$C2/c$	CCDC 1530228
6. $(\text{CH}_3\text{NH}_3)_3\text{Bi}_2\text{I}_9$	100(2) K	$P2_1$	CCDC 1530229
7. $(\text{C}_6\text{H}_5\text{CH}_2\text{NH}_3)_4\text{Pb}_5\text{I}_{14}\cdot 2\text{H}_2\text{O}$	100(2) K	$P2_1/n$	CCDC 1549803
8. $(\text{C}_6\text{H}_5(\text{CH}_2)_2\text{NH}_3)_2\text{MnCl}_4$	385(2) K	$Aea2$	CCDC 1583817
9. $(\text{C}_6\text{H}_5(\text{CH}_2)_2\text{NH}_3)_2\text{MnCl}_4$	100(2) K	$Pca2_1$	CCDC 1583818
10. $(\text{C}_6\text{H}_5(\text{CH}_2)_2\text{NH}_3)_2\text{MnCl}_4$	430(2) K	$I4/mmm$	CCDC 1583819
11. $\text{CH}_3\text{NH}_3\text{Cu}_2\text{Cl}_5$	100(2) K	$P2_1/n$	CCDC 1839002
12. $(\text{H}_3\text{C})_2\text{C}_6\text{H}_4\text{NH}_3\text{I}_3$	100(2) K	$P2_1/m$	CCDC 1839245
13. $(\text{H}_3\text{C})_2\text{C}_6\text{H}_4\text{NH}_3\text{SnI}_3$	100(2) K	$R3c$	CCDC 1839247
14. $\text{PtSn}_4$	100(2) K	$Ccce$	CCDC 1841794
15. $\text{PtSn}_4$	300(2) K	$Ccce$	CCDC 1841795
16. $\text{Co}_3\text{Sn}_2\text{S}_2$	100(2) K	$R\bar{3}m$	CCDC 1841796
17. $\text{Co}_3\text{Sn}_2\text{S}_2$	300(2) K	$R\bar{3}m$	CCDC 1841797

